
**Glassware — Hydrolytic resistance
of the interior surfaces of glass
containers —**

**Part 1:
Determination by titration method
and classification**

*Verrerie — Résistance hydrolytique des surfaces internes des
récipients en verre —*

Partie 1: Détermination par analyse titrimétrique et classification



This document is a preview generated by ERS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	4
5 Reagents.....	4
6 Apparatus.....	5
7 Sample preparation.....	6
7.1 Sample size.....	6
7.2 Determination of the filling volume.....	6
7.2.1 Flat-bottomed containers ≤20 mm outer flange diameter (except ampoules, syringes and cartridges).....	6
7.2.2 Flat-bottomed containers >20 mm outer flange diameter.....	6
7.2.3 Round-bottomed containers.....	7
7.2.4 Lipped containers.....	7
7.2.5 Ampoules.....	7
7.2.6 Syringes and cartridges.....	7
8 Procedure.....	8
8.1 General.....	8
8.2 Cleaning of samples.....	8
8.3 Filling and heating.....	8
8.4 Analysis of the extraction solutions.....	9
8.5 Test to determine whether the containers have been surface treated.....	10
9 Expression of results.....	10
9.1 Determination.....	10
9.2 Classification.....	10
9.3 Distinction between containers of hydrolytic resistance container class HC _T 1 and hydrolytic resistance container class HC _T 2.....	10
9.4 Designation.....	11
10 Test report.....	11
11 Reproducibility.....	12
Bibliography.....	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 76, *Transfusion, infusion and injection, and blood processing equipment for medical and pharmaceutical use*.

This third edition cancels and replaces the second edition (ISO 4802-1:2010), which has been technically revised in particular by amending

- the subclauses on water (test water and purified water),
- the test procedure, and
- the subclause on autoclave and steam sterilizer respectively.

ISO 4802 consists of the following parts, under the general title *Glassware — Hydrolytic resistance of the interior surfaces of glass containers*:

- *Part 1: Determination by titration method and classification*
- *Part 2: Determination by flame spectrometry and classification*

Introduction

This part of ISO 4802 is largely based on a method of test approved by the International Commission on Glass (ICG), Technical Committee 2, *Chemical Durability and Analysis*, for measuring the hydrolytic resistance of the interior surfaces of glass containers.

The European Pharmacopoeia Commission has adopted the principle of the determination by titration and has set up a classification for glass containers for injectable preparations which is now included in this part of ISO 4802. In addition, this part of ISO 4802 contains a classification of containers other than for injectable preparations.

According to many results of international interlaboratory tests, this part of ISO 4802 specifies the test conditions in more detail than the European Pharmacopoeia in order to increase the reproducibility of the test results. In particular, the autoclaving cycle is described in detail.

Glassware — Hydrolytic resistance of the interior surfaces of glass containers —

Part 1: Determination by titration method and classification

1 Scope

This part of ISO 4802 specifies:

- a) a method for determining the hydrolytic resistance of the interior surfaces of glass containers when subjected to attack by water at $121\text{ °C} \pm 1\text{ °C}$ for $60\text{ min} \pm 1\text{ min}$. The resistance is measured by titration of a known aliquot portion of the extraction solution produced with hydrochloric acid solution, in which case the resistance is inversely proportional to the volume of acid required;
- b) a classification of glass containers according to the hydrolytic resistance of the interior surfaces determined by the methods specified in this part of ISO 4802.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385, *Laboratory glassware — Burettes*

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 719, *Glass — Hydrolytic resistance of glass grains at 98 degrees C — Method of test and classification*

ISO 720, *Glass — Hydrolytic resistance of glass grains at 121 degrees C — Method of test and classification*

ISO 1773, *Laboratory glassware — Narrow-necked boiling flasks*

ISO 3819, *Laboratory glassware — Beakers*

ISO 9187-1, *Injection equipment for medical use — Part 1: Ampoules for injectables*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

ampoule

small, normally flat-bottomed container having stems in many different forms

Note 1 to entry: Ampoules are usually thin-walled and have a capacity normally up to 30 ml. They are intended to be closed, after filling, by flame sealing.