

GEOSÜNTEETTÕKKED. NÕUTAVAD OMADUSED
KASUTAMISEKS KEMIKAALIDE, REOSTATUD VEE JA
TOODETUD VEDELIKE AVATUD MAHUTITE,
MAAPEALSETE JA MAA-ALUSTE SEKUNDAARSETE
KAITSETÕKISTE NING TEISTE KAITSETÕKISTE
EHITAMISEL

Geosynthetic barriers - Characteristics required for use
in the construction of storage lagoons, secondary
containment (above and below ground) and other
containment applications for chemicals, polluted water
and produced liquids

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 16993:2018 sisaldab Euroopa standardi EN 16993:2018 ingliskeelset teksti.	This Estonian standard EVS-EN 16993:2018 consists of the English text of the European standard EN 16993:2018.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 28.03.2018.	Date of Availability of the European standard is 28.03.2018.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 59.080.70, 91.100.50

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Geosynthetic barriers - Characteristics required for use in
the construction of storage lagoons, secondary
containment (above and below ground) and other
containment applications for chemicals, polluted water
and produced liquids**

Géomembranes et géosynthétiques bentonitiques -
Caractéristiques requises pour l'utilisation dans la
construction des bassins de retenue, enceintes de
confinement secondaire (au-dessus et au-dessous du
sol) et autres applications de confinement pour les
produits chimiques, les eaux polluées et les liquides
produits

Geosynthetische Dichtungsbahnen - Geforderte
Eigenschaften für die Anwendung beim Bau von
Speicherbecken, Auffangwannen (ober- und
unterirdisch) und anderen Anwendungen für
Chemikalien, verschmutztes Wasser und produzierte
Flüssigkeiten

This European Standard was approved by CEN on 30 October 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	5
Introduction	6
1 Scope.....	7
2 Normative references.....	7
3 Terms, definitions and abbreviations	10
3.1 Terms and definitions	10
3.2 Abbreviations	12
4 Characteristics and corresponding methods of test.....	12
4.1 General.....	12
4.2 Types of applications.....	13
4.2.1 General.....	13
4.2.2 Application 1: Primary containment in open lagoon	13
4.2.3 Application 2: Cover barrier	13
4.2.4 Application 3: Secondary containment of liquid waste.....	14
4.2.5 Application 3: Secondary containment in a concrete bund	14
4.2.6 Application 4: Secondary containment in a soil bund	15
4.3 Relevant characteristics	15
4.4 Characteristics relevant to specific conditions of use	21
4.4.1 General.....	21
4.4.2 Gas Permeability	21
4.4.3 Burst strength and elongation.....	21
4.4.4 Tear strength	21
4.4.5 Friction characteristics (direct shear and inclined plane tests).....	21
4.4.6 Low temperature behaviour	21
4.4.7 Weathering.....	22
4.4.8 Chemical resistance.....	22
4.4.9 Resistance to wetting and drying	22
4.4.10 Freeze-thaw cycle resistance	22
4.4.11 Resistance to root penetration.....	22
4.5 Release of dangerous substances	22
5 Assessment and verification of constancy of performance (AVCP)	22
5.1 General.....	22
5.2 Type testing.....	23
5.2.1 General.....	23
5.2.2 Test samples, testing and compliance criteria	24
5.2.3 Test reports	24
5.2.4 Shared other party results.....	24
5.2.5 Cascading determination of the product type results	25
5.3 Factory production control (FPC)	26
5.3.1 General.....	26
5.3.2 Requirements	26
5.3.3 Product specific requirements.....	32
5.3.4 Initial inspection of factory and of FPC	33
5.3.5 Continuous surveillance of FPC.....	33

5.3.6	Procedure for modifications.....	33
5.3.7	One-off products, pre-production products (e.g. prototypes) and products produced in very low quantity	33
Annex A	(normative) Durability of geosynthetic barriers.....	35
A.1	General	35
A.1.1	Service Life	35
A.1.2	Type testing of durability	35
A.1.3	Mechanisms of degradation	36
A.1.4	Use of rework material	36
A.1.5	Recycled materials	36
A.2	Weathering	36
A.2.1	General	36
A.2.2	Direct tests and accelerated tests	37
A.2.3	Period of exposure	37
A.3	Products used with a service life up to 5 years.....	38
A.4	Other applications and service life of 25 and 50 years	38
A.4.1	General	38
A.4.2	Tests for PE type of GBR-P	39
A.4.3	Tests for FPO-type of GBR-P.....	40
A.4.4	Tests for EPDM type of GBR-P	41
A.4.5	Tests for GBR-P made of PVC-P	41
A.4.6	Tests for clay geosynthetic barriers (GBR-C)	42
A.5	Durability tests on GBR-P	44
A.5.1	Introduction.....	44
A.5.2	Microbiological resistance	44
A.5.3	Resistance to environmental stress cracking.....	45
A.5.4	Resistance to leaching.....	46
A.5.5	Resistance to oxidation/thermal ageing.....	48
A.6	Evaluation tests on GBR-P and GBR-C	50
A.6.1	General	50
A.6.2	Evaluation by comparison of tensile properties	50
A.6.3	Evaluation by comparison of oxidative induction time (OIT) values	51
A.6.4	Evaluation by change in mass	51
A.6.5	Evaluation by change in water permeability	51
A.7	Durability tests on GBR-B	51
A.7.1	Introduction.....	51
A.7.2	Microbiological resistance	52
A.7.3	Resistance to environmental stress cracking.....	52
A.7.4	Resistance to leaching.....	53
A.7.5	Resistance to oxidation/thermal ageing.....	54
A.7.6	Weathering resistance	55
A.8	Evaluation tests on GBR-B	56
A.8.1	General	56
A.8.2	Evaluation by comparison of tensile properties	56
A.8.3	Evaluation by change in mass	56
A.8.4	Evaluation of water permeability	56
A.8.5	Evaluation of flow resistance at elevated temperature.....	57
A.8.6	Evaluation of flexibility at low temperature.....	57
A.8.7	Evaluation of ring and ball softening point temperature	57
Annex ZA	(informative) Relationship of this European Standard with Regulation (EU) No. 305/2011	58
ZA.1	Scope and relevant characteristics	58

ZA.2 System of Assessment and Verification of Constancy of Performance (AVCP)..... 59
ZA.3 Assignment of AVCP tasks 60
Bibliography..... 62

This document is a preview generated by EVS

European foreword

This document (EN 16993:2018) has been prepared by Technical Committee CEN/TC 189 “Geosynthetics”, the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2018, and conflicting national standards shall be withdrawn at the latest by December 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

For relationship with Regulation (EU) No 305/2011, see informative Annex ZA, which is an integral part of this document.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This document allows manufacturers to describe geosynthetic barriers on the basis of declared values for characteristics relevant to the intended use and if tested to the specified method. It also includes procedures for assessment and verification of constancy of performance (AVCP) including the factory production control.

This document can also be used by designers, end-users and other interested parties as a tool to define relevant and appropriate characteristics for specifications.

Tests for some non-mandated characteristics are still under study and will be included when the standard is revised.

The term “product” used in this document refers to a geosynthetic barrier, including polymeric geosynthetic barriers, clay geosynthetic barriers and bituminous geosynthetic barriers.

This document is part of a group of standards, addressing the requirements for geosynthetic barriers when used in a specific application.

Particular application cases can contain requirements about additional properties and - preferably standardized - test methods, if they are technically relevant and not conflicting with European Standards.

The design life of the product should be determined, since its function may be temporary, as construction expediency, or permanent, for the lifetime of the structure.

1 Scope

This European Standard specifies the characteristics of geosynthetic barriers, including polymeric geosynthetic barriers, clay geosynthetic barriers and bituminous geosynthetic barriers used as fluid barriers and separation layer in the construction of hazardous liquid containment and secondary containment around storage facilities for hazardous liquids and the appropriate test methods to determine these characteristics.

NOTE This document is not applicable to applications where one geosynthetic barrier is manufactured in direct contact with a second geosynthetic barrier in order to reduce the overall permeability of the barrier. Such “multicomponent” products are subject to the required characteristics for the relevant component.

The intended use of these products is to control the leakage of fluids through the construction.

This European Standard is not applicable to geotextiles or geotextile-related products as defined in EN ISO 10318-1.

This European Standard provides for the assessment and verification of constancy of performance (AVCP) of the product to this European Standard including factory production control procedures.

This European Standard defines characteristics to be considered with regard to the presentation of performance.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 495-5:2013, *Flexible sheets for waterproofing — Determination of foldability at low temperature — Part 5: Plastic and rubber sheets for roof waterproofing*

EN 1109:2013, *Flexible sheets for waterproofing — Bitumen sheets for roof waterproofing — Determination of flexibility at low temperature*

EN 1110:2010, *Flexible sheets for waterproofing — Bitumen sheets for roof waterproofing — Determination of flow resistance at elevated temperature*

EN 1296:2000, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roofing — Method of artificial ageing by long term exposure to elevated temperature*

EN 1427:2015, *Bitumen and bituminous binders — Determination of the softening point — Ring and Ball method*

EN 1849-1:1999, *Flexible sheets for waterproofing — Determination of thickness and mass per unit area — Part 1: Bitumen sheets for roof waterproofing*

EN 1849-2:2009, *Flexible sheets for waterproofing — Determination of thickness and mass per unit area — Part 2: Plastic and rubber sheets*

EN 12224:2000, *Geotextiles and geotextile-related products — Determination of the resistance to weathering*

EN 12225:2000, *Geotextiles and geotextile-related products — Method for determining the microbiological resistance by a soil burial test*

EN 12226:2012, *Geosynthetics — General tests for evaluation following durability testing*

EN 12310-1:1999, *Flexible sheets for waterproofing — Part 1: Bitumen sheets for waterproofing - Determination of resistance to tearing (nail shank)*

EN 12311-1:1999, *Flexible sheets for waterproofing — Part 1: Bitumen sheets for roof waterproofing — Determination of tensile properties*

EN 12311-2:2013, *Flexible sheets for waterproofing — Determination of tensile properties — Part 2: Plastic and rubber sheets for roof waterproofing*

EN 12447:2001, *Geotextiles and geotextile-related products — Screening test method for determining the resistance to hydrolysis in water*

EN 13249:2016, *Geotextiles and geotextile-related products — Characteristics required for use in the construction of roads and other trafficked areas (excluding railways and asphalt inclusion)*

EN 13250:2016, *Geotextiles and geotextile-related products — Characteristics required for use in the construction of railways*

EN 13251:2016, *Geotextiles and geotextile-related products — Characteristics required for use in earthworks, foundations and retaining structures*

EN 13252:2016, *Geotextiles and geotextile-related products — Characteristics required for use in drainage systems*

EN 13253:2016, *Geotextiles and geotextile-related products — Characteristics required for use in erosion control works (coastal protection, bank revetments)*

EN 13254:2016, *Geotextiles and geotextile-related products — Characteristics required for the use in the construction of reservoirs and dams*

EN 13255:2016, *Geotextiles and geotextile-related products — Characteristics required for use in the construction of canals*

EN 13256:2016, *Geotextiles and geotextile-related products — Characteristics required for use in the construction of tunnels and underground structures*

EN 13257:2016, *Geotextiles and geotextile-related products — Characteristics required for use in solid waste disposals*

EN 13265:2016, *Geotextiles and geotextile-related products — Characteristics required for use in liquid waste containment projects*

EN 14150:2006, *Geosynthetic barriers — Determination of permeability to liquids*

EN 14151:2010, *Geosynthetics — Determination of burst strength*

EN 14196:2016, *Geosynthetics — Test methods for measuring mass per unit area of clay geosynthetic barriers*

EN 14414:2004, *Geosynthetics — Screening test method for determining chemical resistance for landfill applications*

- EN 14415:2004, *Geosynthetic barriers — Test method for determining the resistance to leaching*
- CEN/TS 14416:2014, *Geosynthetic barriers — Test method for determining the resistance to roots*
- CEN/TS 14417:2014, *Geosynthetic barriers — Test method for the determination of the influence of wetting-drying cycles on the permeability of clay geosynthetic barriers*
- CEN/TS 14418:2014, *Geosynthetic Barriers — Test method for the determination of the influence of freezing-thawing cycles on the permeability of clay geosynthetic barriers*
- EN 14575:2005, *Geosynthetic barriers — Screening test method for determining the resistance to oxidation*
- EN 14576:2005, *Geosynthetics — Test method for determining the resistance of polymeric geosynthetic barriers to environmental stress cracking*
- EN 16416:2013, *Geosynthetic clay barriers — Determination of water flux index — Flexible wall permeameter method at constant head*
- EN ISO 527-1:2012, *Plastics — Determination of tensile properties — Part 1: General principles (ISO 527-1:2012)*
- EN ISO 527-3:1995, *Plastics — Determination of tensile properties — Part 3: Test conditions for films and sheets (ISO 527-3:1995)*
- EN ISO 527-4:1997, *Plastics — Determination of tensile properties — Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastic composites (ISO 527-4:1997)*
- EN ISO 1133-1:2011, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method (ISO 1133-1:2011)*
- EN ISO 1183-1:2012, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method (ISO 1183-1:2012)*
- EN ISO 1183-2:2004, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method (ISO 1183-2:2004)*
- EN ISO 1183-3:1999, *Plastics — Methods for determining the density of non-cellular plastics — Part 3: Gas pycnometer method (ISO 1183-3:1999)*
- EN ISO 3696:1995, *Water for analytical laboratory use — Specification and test methods (ISO 3696:1987)*
- EN ISO 9863-1:2016, *Geosynthetics — Determination of thickness at specified pressures — Part 1: Single layers (ISO 9863-1:2016)*
- EN ISO 9864:2005, *Geosynthetics — Test method for the determination of mass per unit area of geotextiles and geotextile-related products (ISO 9864:2005)*
- EN ISO 10318-1:2015, *Geosynthetics — Part 1: Terms and definitions (ISO 10318-1:2015)*
- EN ISO 10319:2015, *Geosynthetics — Wide-width tensile test (ISO 10319:2015)*
- EN ISO 10773:2011, *Clay geosynthetic barriers — Determination of permeability to gases (ISO 10773:2011)*

EN ISO 11357-6:2013, *Plastics — Differential scanning calorimetry (DSC) — Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT) (ISO 11357-6:2008)*

EN ISO 12236:2006, *Geosynthetics — Static puncture test (CBR test) (ISO 12236:2006)*

EN ISO 12957-1:2005, *Geosynthetics — Determination of friction characteristics — Part 1: Direct shear test (ISO 12957-1:2005)*

EN ISO 12957-2:2005, *Geosynthetics - Determination of friction characteristics — Part 2: Inclined plane test (ISO 12957-2:2005)*

EN ISO 13438:2004, *Geotextiles and geotextile-related products — Screening test method for determining the resistance to oxidation (ISO 13438:2004)*

ISO 34-1:2015, *Rubber, vulcanized or thermoplastic — Determination of tear strength — Part 1: Trouser, angle and crescent test pieces*

ISO 11465:1993, *Soil quality — Determination of dry matter and water content on a mass basis — Gravimetric method*

ASTM D696, *Standard test method for coefficient of linear thermal expansion of plastics between -30 °C and 30 °C*

ASTM D1434, *Standard Test Method for Determining Gas Permeability Characteristics of Plastic Film and Sheeting*

ASTM D4603, *Standard Test Method for Determining Inherent Viscosity of Poly(Ethylene Terephthalate) (PET) by Glass Capillary Viscometer*

ASTM D5890, *Standard test method for swell index of clay mineral component of geosynthetic clay liners*

ASTM D7409, *Standard Test Method for Carboxyl End Group Content of Polyethylene Terephthalate (PET) Yarns*

3 Terms, definitions and abbreviations

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 10318-1 and the following apply.

3.1.1

product

geosynthetic barrier, including polymeric, bituminous and clay barriers