

Microstructure of cast irons - Part 1: Graphite
classification by visual analysis (ISO 945-1:2017)

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 945-1:2018 sisaldab Euroopa standardi EN ISO 945-1:2018 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 945-1:2018 consists of the English text of the European standard EN ISO 945-1:2018.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 14.02.2018.	Date of Availability of the European standard is 14.02.2018.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.080.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN ISO 945-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2018

ICS 77.080.10

Supersedes EN ISO 945-1:2008

English Version

Microstructure of cast irons - Part 1: Graphite classification by visual analysis (ISO 945-1:2017)

Microstructure des fontes - Partie 1: Classification du
graphite par analyse visuelle (ISO 945-1:2017)

Mikrostruktur von Gusseisen - Teil 1:
Graphitklassifizierung durch visuelle Auswertung (ISO
945-1:2017)

This European Standard was approved by CEN on 6 December 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 945-1:2018) has been prepared by Technical Committee ISO/TC 25 “Cast irons and pig irons” in collaboration with Technical Committee CEN/TC 190 “Foundry technology” the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2018, and conflicting national standards shall be withdrawn at the latest by August 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 945-1:2008.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 945-1:2017 has been approved by CEN as EN ISO 945-1:2018 without any modification.

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 General.....	1
4.1 Designation system for classifying graphite in cast irons.....	1
4.2 Form.....	2
4.3 Distribution.....	3
4.4 Size.....	4
4.5 Visual classification of graphite.....	23
5 Sampling and sample preparation.....	23
5.1 Samples taken from a casting.....	23
5.2 Sample preparation.....	23
6 Procedure for graphite classification.....	23
6.1 Procedure for visual classification of graphite.....	23
6.2 Evaluation of the analysis results.....	24
7 Reference images.....	24
7.1 General.....	24
7.2 Reference images for graphite form.....	24
7.3 Reference images for the distribution of graphite (form I).....	24
7.4 Reference images for graphite size.....	24
8 Designation of graphite by form, distribution and size.....	25
8.1 Designation system.....	25
8.2 Designation of different graphite sizes within a casting.....	25
8.3 Designation of mixed graphite forms, distributions and sizes.....	26
8.4 Designation of unclassified graphite forms.....	26
8.5 Nodule count.....	26
9 Report.....	27
Annex A (informative) Typical graphite forms in cast-iron materials — Examples of photomicrographs.....	28
Annex B (informative) Distribution of flake (lamellar) graphite (form I) — Examples of photomicrographs.....	29
Annex C (informative) Common terminology and main occurrences concerning graphite in cast irons.....	30
Bibliography.....	32

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 25, *Cast irons and pig irons*.

This second edition cancels and replaces the first edition (ISO 945-1:2008), which has been technically revised. It also incorporates the Technical Corrigendum ISO 945-1:2008/Cor.1:2010. [Figures 3, 4 and 5](#) have been corrected to a diameter of 120 mm to allow a direct comparison with the microscope display screen.

A list of all the parts in the ISO 945 series can be found on the ISO website.

Introduction

Microstructure designation is a useful feature that provides a means of classifying the graphite form, distribution and size in cast irons.

Graphite classification by visual analysis is a well-established method which is well recognized within the foundry industry as a means of quickly determining the overall graphite microstructure of a cast iron casting.

Microstructure of cast irons —

Part 1: Graphite classification by visual analysis

1 Scope

This document specifies a method of classifying the microstructure of graphite in cast irons by comparative visual analysis.

The purpose of this document is to provide information about the method of graphite classification. It is not intended to give information on the suitability of cast-iron types and grades for any particular application.

The particular material grades are specified mainly by mechanical properties and, in the case of austenitic and abrasion resistant cast irons, by their chemical composition. The interpretation of graphite form and size does not allow a statistically valid statement on the fulfilment of the requirements specified in the relevant material standard.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 General

4.1 Designation system for classifying graphite in cast irons

When cast iron materials are examined under a microscope in accordance with this document, the graphite shall be classified by the following:

- a) its form, designated by Roman numbers I to VI (see [Figure 1](#) and [Annex A](#));
- b) its distribution, designated by capital letters A to E (see [Figure 2](#) and [Annex B](#)); the graphite distribution designation is only specified for grey cast irons (form I);
- c) its size, designated by numbers 1 to 8 (see [Figures 3, 4](#) and [5](#) and [Table 1](#)).

NOTE [Figures 1](#) to [5](#) show only the outlines and not the structure of the graphite.