

Plastics - Artificial weathering including acidic  
deposition (ISO 29664:2010)

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 29664:2017 sisaldab Euroopa standardi EN ISO 29664:2017 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 29664:2017 consists of the English text of the European standard EN ISO 29664:2017.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 15.02.2017.	Date of Availability of the European standard is 15.02.2017.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 83.080.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

Plastics - Artificial weathering including acidic deposition  
(ISO 29664:2010)

Plastiques - Vieillissement artificiel y compris les  
dépôts acides (ISO 29664:2010)

Kunststoffe - Künstliche Bewitterung einschließlich  
saurer Beanspruchung (ISO 29664:2010)

This European Standard was approved by CEN on 17 January 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

## European foreword

The text of ISO 29664:2010 has been prepared by Technical Committee ISO/TC 61 “Plastics” of the International Organization for Standardization (ISO) and has been taken over as EN ISO 29664:2017 by Technical Committee CEN/TC 249 “Plastics” the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2017, and conflicting national standards shall be withdrawn at the latest by August 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

### Endorsement notice

The text of ISO 29664:2010 has been approved by CEN as EN ISO 29664:2017 without any modification.

<b>Contents</b>		<b>Page</b>
<b>Foreword</b> .....		<b>iv</b>
<b>Introduction</b> .....		<b>v</b>
<b>1</b>	<b>Scope</b> .....	<b>1</b>
<b>2</b>	<b>Normative references</b> .....	<b>1</b>
<b>3</b>	<b>Principle</b> .....	<b>1</b>
<b>4</b>	<b>Apparatus</b> .....	<b>2</b>
<b>5</b>	<b>Test specimens</b> .....	<b>4</b>
<b>6</b>	<b>Test conditions</b> .....	<b>4</b>
<b>6.1</b>	<b>Method A</b> .....	<b>4</b>
<b>6.2</b>	<b>Method B</b> .....	<b>8</b>
<b>6.3</b>	<b>Allowed deviations in temperature and humidity</b> .....	<b>9</b>
<b>6.4</b>	<b>Measurement of radiant exposure</b> .....	<b>9</b>
<b>6.5</b>	<b>Determination of changes in properties after exposure</b> .....	<b>9</b>
<b>7</b>	<b>Precision</b> .....	<b>9</b>
<b>8</b>	<b>Test report</b> .....	<b>9</b>
<b>Annex A (informative) Background information</b> .....		<b>11</b>
<b>Annex B (informative) Precision data for coatings</b> .....		<b>15</b>
<b>Bibliography</b> .....		<b>16</b>

## Introduction

This International Standard specifies methods to reproduce the weathering effects that occur when plastics are exposed to heavily polluted outdoor environments. Acidic precipitation can have a significant effect on the photochemical ageing of many polymers. In some cases, this is due to attack on the stabilizers<sup>[5][6]</sup> or fillers like  $\text{CaCO}_3$ <sup>[7][8]</sup> applied in technical polymers. The mechanisms differ from those of harmful gases, which essentially constitute the initial products of acidic precipitation.

Arising from changing industrial air pollution and additionally diffused by the stochastic wind and cloud distribution, acidic precipitation occurs sporadically. Thus, especially regarding acidic precipitation, outdoor weathering effects vary enormously within different years. Therefore, it is practically impossible to obtain reliable outdoor exposure results from just one season. These fluctuations can be avoided through the use of a laboratory test, where all weathering parameters, including the acidic deposition, can be controlled.

In artificial weathering tests for plastics, the action of acidic atmospheric precipitation, which is part of the real world, has generally not been considered.

# Plastics — Artificial weathering including acidic deposition

## 1 Scope

This International Standard describes artificial weathering tests intended to evaluate plastics for use in heavily polluted outdoor environments. Results from this International Standard cannot be used to predict the service life of these plastics.

This International Standard describes two different exposure methods. Use of the methods depends on the form of the plastic product being evaluated.

Method A is intended for products where surface degradation is very important and uses a strong acid spray (pH 1,5) that is applied for a short time.

Method B uses a weaker acid spray (pH 3,5) that is applied over a long period of time so that it can penetrate deeply into the product and is intended for products such as geotextiles and related products.

This International Standard does not cover the influence of special chemicals like agrochemicals.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to daylight under glass, natural weathering or laboratory light sources*

ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance*

ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps*

ISO 4892-3, *Plastics — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps*

## 3 Principle

The combined action of UV radiation, heat, humidity, wetting, and acidic deposition is evaluated in weathering devices conforming to ISO 4892-1, ISO 4892-2 and ISO 4892-3.

The acidic deposition, in some cases, may accelerate the degradation of the polymer itself. In other cases, the degradation is accelerated when the acid deposition attacks the stabilizers in the polymer.

Two different methods combine acidic deposition with artificial weathering. In method A, a strong acid solution is applied once per day. In method B, a weaker acid exposure is integrated in the rain phase.

Both test methods aim for the same physical-chemical degradation mechanism as known to occur from exposure in heavily polluted outdoor environment. To consider different climatic conditions, method A includes