
**Rubber, vulcanized — Determination of
temperature rise and resistance to fatigue
in flexometer testing —**

Part 1:
Basic principles

*Caoutchouc vulcanisé — Détermination de l'élévation de température et
de la résistance à la fatigue dans les essais aux flexomètres —*

Partie 1: Principes fondamentaux



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions	1
4 Test conditions.....	3
5 Test pieces	3
5.1 Form and dimensions	3
5.2 Preparation.....	3
5.3 Time interval between vulcanization and testing.....	4
5.4 Conditioning	4
5.5 Number	4
6 Apparatus	4
6.1 General	4
6.2 Temperature-controlled cabinet.....	4
6.3 Measurement of temperature	4
7 Procedure.....	5
7.1 General	5
7.2 Temperature of test.....	5
7.3 Measurement of temperature rise.....	5
7.4 Determination of fatigue life.....	5
7.5 Determination of limiting fatigue deformability and limiting fatigue stress.....	5
7.6 Determination of creep	6
7.7 Determination of set.....	6
8 Test report.....	6
Annex A (informative) Explanatory notes.....	7
Bibliography.....	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4666-1 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This second edition cancels and replaces the first edition (ISO 4666-1:1982), which has been technically revised.

ISO 4666 consists of the following parts, under the general title *Rubber, vulcanized — Determination of temperature rise and resistance to fatigue in flexometer testing*.

- *Part 1: Basic principles*
- *Part 2: Rotary flexometer*
- *Part 3: Compression flexometer (constant-strain type)*
- *Part 4: Constant-stress flexometer*

Introduction

All rubbers show viscoelastic behaviour. When subjected to cyclic deformation, they absorb a part of the deformation energy and convert this into heat. The heat generated leads to a temperature rise, which can be considerable in the interior of relatively thick components because of the low thermal conductivity of rubbers. In cases where the cyclic deformation is large or the temperature reaches high values, it is possible for damage to the rubber to occur through fatigue-initiated breakdown. The breakdown begins in the interior of the rubber, spreads outwards, and can finally lead to the complete breakdown of the component.

The tests specified in the various parts of this International Standard yield either temperature rise data or the fatigue life of the rubber under given test conditions. Measurement of fatigue life over a range of conditions can be used to determine the limiting fatigue deformability or limiting fatigue stress of the rubber. The instruments used, commonly called flexometers, subject test pieces to cycles of either constant-stress amplitude or constant-strain amplitude.

A distinction should be made between flexometer tests and fatigue tests conducted on thin test pieces undergoing tensile deformation or bending. In the fatigue tests, the temperature rise is generally negligible owing to the rapid dissipation of heat generated, and failure results from the initiation and growth of cracks which ultimately sever the test piece. ISO 132^[1] specifies tests for the determination of flex cracking and cut growth using the De Mattia-type machine. The determination of resistance to tension fatigue is specified in ISO 6943^[3].

This document is a preview generated by EVS

Rubber, vulcanized — Determination of temperature rise and resistance to fatigue in flexometer testing —

Part 1: Basic principles

1 Scope

This part of ISO 4666 establishes general principles for flexometer testing and defines the terms used.

Flexometer testing makes possible predictions regarding the durability of rubbers in finished articles subject to dynamic flexing in service such as tyres, bearings, supports, V-belts, and cable-pulley insert rings. However, owing to the wide variations in service conditions, no simple correlation between the accelerated tests specified in the various parts of this International Standard and service performance can be assumed.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4664-1:—¹⁾, *Rubber, vulcanized or thermoplastic — Determination of dynamic properties — Part 1: General guidance*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4664-1 and the following apply.

3.1

loading

subjection of the test piece to a predetermined stress or strain, either static or cyclic

3.2

pre-stress

σ_p

constant static stress to which the test piece is subjected during the test

NOTE 1 Pre-stress is expressed in pascals.

NOTE 2 Pre-stress can be used to simulate product requirements or simply to hold the test piece in the apparatus.

NOTE 3 The term “mean stress” (ISO 4664-1:—) is equivalent or near equivalent to “pre-stress”.

1) To be published. (Revision of ISO 4664-1:2005)