

Flexible sheets for waterproofing - Waterproofing of concrete bridge decks and other concrete surfaces trafficable by vehicles - Determination of resistance to dynamic water pressure after damage by pre-treatment

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 14694:2017 sisaldab Euroopa standardi EN 14694:2017 ingliskeelset teksti.	This Estonian standard EVS-EN 14694:2017 consists of the English text of the European standard EN 14694:2017.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 29.03.2017.	Date of Availability of the European standard is 29.03.2017.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.100.50

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Flexible sheets for waterproofing - Waterproofing of
concrete bridge decks and other concrete surfaces
trafficable by vehicles - Determination of resistance to
dynamic water pressure after damage by pre-treatment

Feuilles souples d'étanchéité - Étanchéité des tabliers
de ponts en béton et autres surfaces en béton
circulables par les véhicules - Détermination de la
résistance à la pression hydraulique dynamique après
dégradation par prétraitement

Abdichtungsbahnen - Abdichtung von Betonbrücken
und anderen Verkehrsflächen auf Beton - Bestimmung
des Widerstandes gegenüber dynamischem
Wasserdruck nach Schäden infolge Vorbeanspruchung

This European Standard was approved by CEN on 6 February 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

European foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Test methods	5
4.1 Principle	5
4.2 Apparatus and materials	5
4.3 Preparation of test specimens.....	5
4.4 Procedure.....	6
4.5 Expression of results.....	6
4.6 Test report.....	7

European foreword

This document (EN 14694:2017) has been prepared by Technical Committee CEN/TC 254 “Flexible sheets for waterproofing”, the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2017, and conflicting national standards shall be withdrawn at the latest by September 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14694:2005.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

The significant technical changes are the new reference to prEN 17048 in Clause 2, Normative references, and further information about test specimens in Clause 4.3, Preparation of test specimens.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

The purpose of this test is to determine the resistance to pre-treatment by impact puncturing followed by dynamic water pressure testing for sheets in the waterproofing system.

The test is normally performed for single sheets but may also be performed for double sheet systems.

This document is a preview generated by EVS

1 Scope

This European Standard specifies a test method for the evaluation of the resistance to impact puncturing of a sheet or sheet system.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13375, *Flexible sheets for waterproofing - Waterproofing of concrete bridge decks and other concrete surfaces trafficable by vehicles - Specimen preparation*

EN 13416, *Flexible sheets for waterproofing - Bitumen, plastic and rubber sheets for roof waterproofing - Rules for sampling*

EN 14695, *Flexible sheets for waterproofing - Reinforced bitumen sheets for waterproofing of concrete bridge decks and other trafficked areas of concrete - Definitions and characteristics*

prEN 17048, *Flexible sheets for waterproofing - Plastic and rubber sheets for waterproofing of concrete bridge decks and other trafficked areas of concrete - Definitions and characteristics*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13416, EN 14695 and prEN 17048 apply.

4 Test methods

4.1 Principle

Pre-treatment impact puncturing is carried out at room temperature, where a conical weight is allowed to fall freely on to the waterproofing sheet. The degree of penetration is then assessed with the aid of dynamic water pressure testing.

4.2 Apparatus and materials

Equipment for impact puncturing, with a puncturing tool consisting of $(1,0 \pm 0,01)$ kg of steel with a 90° conical point (see Figures 2 and 3).

Concrete slab, according to EN 13375 for supporting the test specimen during impact puncturing.

Suitable frame, for holding the test specimen firmly to the concrete slab.

Equipment for the water pressure test, with a dynamic water pressure applied (see Figures 4 and 5).

4.3 Preparation of test specimens

Take test samples and test pieces in accordance with EN 13416.

Select one test specimen of 400 mm × 200 mm for testing.

In the case of a double sheet system, weld or glue the two sheets together according to manufacturer instructions. Ensure that the sheet or sheet system thickness is within the limits of the equipment used.

Condition the test specimen for at least 24 h at a temperature of $(23 \pm 2) ^\circ\text{C}$.