
**Reaction to fire tests — Measurement of
material properties using a fire
propagation apparatus**

*Essais de réaction au feu — Mesurage des propriétés des matériaux au
moyen d'un appareillage de propagation du feu*



This document is a preview generated by EVS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols	2
5 Principle	3
6 Apparatus	4
6.1 General	4
6.1.1 Dimensions	4
6.1.2 Components	4
6.2 Infrared (IR) heating system	4
6.3 Load cell system	5
6.4 Ignition pilot flame	5
6.5 Ignition timer	5
6.6 Gas analysis system	5
6.6.1 Gas sampling	5
6.6.2 Carbon dioxide/carbon monoxide analysers	6
6.6.3 Inlet air oxygen analyser	6
6.6.4 Optional product analysers for the combustion test	6
6.7 Combustion air distribution system	6
6.7.1 General	6
6.7.2 Air distribution chamber	6
6.7.3 Air supply pipes	6
6.8 Water-cooled shield	6
6.9 Exhaust system	7
6.10 Measuring section instruments	7
6.10.1 Measuring section thermocouple probe	7
6.10.2 Averaging Pitot probe and pressure transducer	7
6.11 Heat flux gauge	7
6.12 Digital data acquisition system	7
7 Hazards	8
7.1 Laboratory safety	8
7.2 Safety precautions	8
7.3 Exhaust system operation	8
8 Test specimen	8
8.1 Specimen holders	8
8.2 Specimen size and preparation	8
8.2.1 Ignition, pyrolysis and combustion tests of horizontal specimens	8
8.2.2 Fire propagation test of vertical, rectangular specimens	9
8.2.3 Fire propagation test of vertical, cable specimens	9
9 Calibration	9
9.1 Radiant-flux heater	9
9.1.1 Routine calibration	9
9.1.2 Positioning of radiant-flux heaters	10
9.2 Gas-analyser calibration	10
9.2.1 Carbon dioxide/carbon monoxide analysers	10

9.2.2	Oxygen analyser	10
9.2.3	Optional hydrocarbon gas analyser	10
9.3	Load cell	10
9.4	Heat release calibration	11
10	Specimen conditioning	11
11	Procedure	11
11.1	Procedure 1 — Ignition test method	11
11.2	Procedure 2 — Combustion test method	12
11.3	Procedure 3 — Pyrolysis test method	13
11.4	Procedure 4 — Fire propagation test method	14
12	Calculation	15
13	Test report	16
13.1	Procedure 1 — Ignition test method	16
13.2	Procedure 2 — Combustion test method	17
13.3	Procedure 3 — Pyrolysis test method	17
13.4	Procedure 4 — Fire propagation test method	17
Annex A (informative)	Laser smoke measuring system	31
Annex B (informative)	Rationale	34
Annex C (informative)	Comparison of results — vertical and horizontal exhaust ducts	41
Annex D (informative)	Heat of gasification	44
Bibliography	46

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12136 was prepared by Technical Committee ISO/TC 92, *Fire safety*, Subcommittee SC 1, *Fire initiation and growth*.

Introduction

This International Standard contains four separate test methods^{[3][4][5][12]}, which are conducted using a fire propagation apparatus (FPA). The ignition, combustion and pyrolysis test methods involve the use of horizontal specimens subjected to a controlled, external radiant heat flux, which can be set from 0 kW/m² to 65 kW/m². The fire propagation test method involves the use of vertical specimens subjected to ignition near the base of the specimen from an external radiant heat flux and a pilot flame. The combustion, pyrolysis and fire propagation test methods can be performed using an inlet air supply that is either normal air or other gaseous mixtures, such as air with added nitrogen, 100 % nitrogen or air enriched with up to 40 % oxygen.

The ignition test method is used to determine the time required for ignition, t_{ign} , of horizontal specimens by a pilot flame as a function of the magnitude of a constant, externally applied radiant heat flux. Measurements also are made of time required until initial fuel vaporization. The surface of these specimens is coated with a thin layer of black paint to ensure complete absorption of the radiant heat flux from the infrared heating system (note that the coating does not itself undergo sustained flaming).

The combustion test method is used to determine the chemical and convective heat release rates, and smoke generation rate when the horizontal test specimen is exposed to an external radiant heat flux.

The pyrolysis test method with a flow of 100 % nitrogen and no ignition can be used to measure the mass loss rate as a function of externally applied radiant heat flux for a horizontal specimen. From these measurements, the heat of gasification of the material can be determined.

The fire propagation test method using 40 % oxygen is used to determine the chemical heat release rate of a burning, vertical specimen during upward fire propagation and burning initiated by a heat flux near the base of the specimen. Chemical heat release rate is derived from the release rates of carbon dioxide and carbon monoxide. Observations also are made of the flame height on the vertical specimen during fire propagation. As discussed in B.5 and B.6, the use of enhanced oxygen in small-scale fire tests can better simulate the flame heat flux occurring in large-scale fires^{[16][18][19][20][21]}. Correlation has been developed between the results from small-scale tests with 40 % oxygen and the results from large-scale tests for a class of materials (see B.6).

Distinguishing features of the FPA include:

- tungsten-quartz external, isolated heaters to provide a radiant flux of up to 65 kW/m² to the test specimen, which remains constant whether the surface regresses or expands;
- provision for combustion or upward fire propagation in prescribed flows of normal air, air enriched with up to 40 % oxygen, air oxygen vitiated, pure nitrogen or mixtures of gaseous suppression agents with the preceding air mixtures;
- the capability of measuring heat release rates and exhaust product flows generated during upward fire propagation on a vertical test specimen 0,305 m high.

The original FPA uses a vertical exhaust duct configuration^[6], which requires laboratories to have available a sufficient ceiling height to accommodate all the system components. Also, the original FPA has the gas sampling and analysis system completely separate from the main apparatus. To reduce this ceiling height constraint and to allow for a more compact arrangement, a horizontal exhaust configuration has been developed as shown in Figures 1 and 2. The FPA with horizontal duct provides equivalent results to those measured using the FPA with vertical duct, as described in Annex C.

The FPA is used to evaluate the flammability of materials and products. It is also designed to obtain the transient response of such materials and products to prescribed heat fluxes in specified inert or oxidizing environments and to obtain laboratory measurements of generation rates of fire products (CO₂, CO, and, if desired, gaseous hydrocarbons) for use in fire safety engineering.

Ignition of the specimen is by means of a pilot flame at a prescribed location with respect to the specimen surface [described in 11.1 e)].

The Fire Propagation test of vertical specimens is not suitable for materials that, on heating, melt sufficiently to form a liquid pool.

This International Standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this International Standard to establish appropriate health and safety practices and to determine the applicability of regulatory limitations prior to use. For specific hazard statements, see Clause 7.

This International Standard specifies small-scale test methods for determining the performance of materials when exposed to fire, which are based on decades of research published in the fire science literature. Parts of this International Standard are based on information contained in ASTM E2058 and NFPA 287.

The following test methods, capable of being performed separately and independently, are included:

- 1) Ignition test, to determine t_{ign} for a horizontal specimen;
- 2) Combustion test, to determine Q_{chem} , Q_{c} , \dot{m} , ΔH_{eff} , and Y_{g} from burning of a horizontal specimen;
- 3) Pyrolysis test, to determine \dot{m} and ΔH_{g} ; and,
- 4) Fire propagation test, to determine Q_{chem} from burning of a vertical specimen.

Reaction to fire tests — Measurement of material properties using a fire propagation apparatus

1 Scope

This International Standard determines and quantifies the flammability characteristics of materials, in relation to their propensity to support fire propagation, by means of a fire propagation apparatus (FPA). Material flammability characteristics that are quantified in this International Standard include time to ignition, chemical and convective heat release rates, mass loss rate, effective heat of combustion, heat of gasification and smoke yield. These properties can be used for fire safety engineering and for fire modelling.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 13943, *Fire safety — Vocabulary*

ISO 14934-3, *Fire tests — Calibration and use of heat flux meters — Part 3: Secondary calibration method*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13943 and the following apply.

3.1

essentially flat surface

surface whose irregularity from a plane does not exceed ± 1 mm

3.2

flashing

existence of flame on or over the surface of the specimen for periods of less than 1 s

3.3

ignition

sustained flaming on or over the surface of the specimen for periods of over 10 s

3.4

fire propagation

increase in the exposed surface area of the specimen that is actively involved in flaming combustion

3.5

smoke yield

mass of smoke particulates generated per unit mass of fuel vaporized