

---

---

**Protective clothing — Protection  
against flame — Method of test for  
limited flame spread**

*Vêtements de protection — Protection contre les flammes — Méthode  
d'essai pour la propagation de flamme limitée*



This document is a preview generated by EBS



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

Page

<b>Foreword</b>	<b>iv</b>
<b>Introduction</b>	<b>v</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>1</b>
<b>4 Principle</b>	<b>2</b>
<b>5 Health and safety of test operators</b>	<b>3</b>
<b>6 Fuel</b>	<b>3</b>
<b>7 Apparatus</b>	<b>3</b>
<b>8 Sampling and sample preparation</b>	<b>10</b>
8.1 Sampling	10
8.1.1 Number of specimens	10
8.1.2 Specimen-holder pin location marks	10
8.1.3 Test specimen size	10
8.1.4 Multilayer specimens (including trim)	11
8.1.5 Seams	11
8.2 Conditioning atmosphere of the test sample	11
<b>9 Procedure</b>	<b>11</b>
9.1 Installation of the test apparatus	11
9.1.1 Test conditions	11
9.1.2 Procedure A — Surface ignition	12
9.1.3 Procedure B — Bottom-edge ignition	12
9.1.4 Detection of flaming debris	13
9.2 Test procedure	13
9.2.1 Procedure A — Surface ignition	13
9.2.2 Procedure B — Bottom-edge ignition	14
<b>10 Test report</b>	<b>14</b>
<b>Annex A (normative) Description and construction of the burner</b>	<b>16</b>
<b>Annex B (informative) Laboratory techniques</b>	<b>17</b>
<b>Annex C (normative) Measurement of damaged/char length</b>	<b>18</b>
<b>Annex D (informative) Precision and results of interlaboratory trials</b>	<b>19</b>
<b>Bibliography</b>	<b>21</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

The committee responsible for this document is ISO/TC 94, *Personal safety — Protective clothing and equipment*, Subcommittee SC 13, *Protective clothing*.

This second edition cancels and replaces the first edition (ISO 15025:2000), of which all clauses, several figures and [Annex C](#) have been technically revised. A new [Clause 8](#) on sampling and sample preparation has been added. A new [Annex D](#) on precision has been added.

To improve precision, the following major modifications have been made from the first edition:

- a) the width of the specimen for Procedure B has been changed from 160 mm to 80 mm;
- b) the gas used has been limited to commercial grade propane;
- c) definitions of several reported observations have been added or revised;
- d) more detailed instructions for preparing hemmed specimens, multilayer specimens and seamed specimens have been added.

## Introduction

The first edition of this document was initially prepared by ISO/TC 38/SC 19 as part of the revision of ISO 6940 and ISO 6941. This specific work item was transferred to Technical Committee ISO/TC 94/SC 13 in April 1997.

This method of test is closely related to the method of test specified in ISO 6941. It uses the same basic equipment but narrower specimen holders and templates for one procedure. Materials which do not burn to the upper or vertical edges of the test specimen used in this test may be classified as producing limited flame spread.

This method assesses the properties of textile fabrics in response to a short contact with a small igniting flame under controlled conditions.

The influence of seams on the behaviour of fabrics can be determined by this method, the seam being positioned within the test specimen so as to be subjected to the test flame.

Whenever practicable, trimmings should be tested as part of the fabric assembly on which they are or will be used.

A list of standards related to this document is given in the Bibliography.



# Protective clothing — Protection against flame — Method of test for limited flame spread

## 1 Scope

This document specifies two procedures (surface ignition and bottom-edge ignition) for determining flame spread properties of vertically oriented flexible materials in the form of single or multicomponent fabrics (coated, quilted, multilayered, sandwich constructions and similar combinations), when subjected to a small defined flame. This test standard does not apply to situations where there is restricted air supply or exposure to large sources of intense heat, for which other test methods are more appropriate.

This test method is not appropriate for materials that demonstrate extensive melting or shrinkage.

## 2 Normative references

There are no normative references in this document.

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO/TR 11610 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

### 3.1

#### **afterflame time**

duration of flaming after removal of ignition source

Note 1 to entry: It is also defined as the length of time for which a *material* continues to flame under the specified test conditions, after the ignition source has been removed

Note 2 to entry: Afterflame time is measured and reported to the nearest second.

### 3.2

#### **afterglow**

persistence of glowing combustion of a *material* (3.10) under specified test conditions, after cessation of afterflaming or, if no afterflaming occurs, after removal of the ignition source

Note 1 to entry: Afterglow is a continuation of combustion with the evolution of heat and light but without flame. Some materials absorb heat during the flame application and continue to emit this absorbed heat inside the charred area after removal of the igniting flame. This glowing inside the charred area without combustion should not be recorded as afterglow.

### 3.3

#### **afterglow time**

duration of *afterglow* (3.2)

Note 1 to entry: It is also defined as the time for which a glowing combustion continues, under specified test conditions after cessation of afterflaming or, if no afterflaming occurs, after removal of the ignition source

Note 2 to entry: Afterglow time is measured and reported to the nearest second.