
**Wrought aluminium and aluminium
alloys — Extruded rods/bars, tubes and
profiles —**

Part 4:
**Profiles — Tolerances on shape and
dimensions**

*Aluminium et alliages d'aluminium corroyés — Barres, tubes et
profilés filés —*

Partie 4: Profilés — Tolérances sur forme et dimensions



This document is a preview generated by EVS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Materials	1
5 Tolerances on shape and dimensions	2
5.1 Dimensional tolerances	2
5.2 Length	10
5.3 Squareness of cut ends	10
6 Tolerances on form	10
6.1 General	10
6.2 Straightness	10
6.3 Convexity/Concavity	11
6.4 Curved cross-section or contour	12
6.5 Twist	14
6.6 Angularity	15
6.7 Corner and fillet radii	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 6362-4 was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 6, *Wrought aluminium and aluminium alloys*.

This second edition cancels and replaces the first edition (ISO 6362-4:1988), which has been technically revised.

ISO 6362 consists of the following parts, under the general title *Wrought aluminium and aluminium alloys — Extruded rods/bars, tubes and profiles*:

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*
- *Part 3: Extruded rectangular bars — Tolerances on shape and dimensions*
- *Part 4: Profiles — Tolerances on shape and dimensions*
- *Part 5: Round, square and hexagonal bars — Tolerances on shape and dimensions*
- *Part 6: Round, square, rectangular and hexagonal tubes — Tolerances on shape and dimensions*
- *Part 7: Chemical composition*

Wrought aluminium and aluminium alloys — Extruded rods/bars, tubes and profiles —

Part 4: Profiles — Tolerances on shape and dimensions

1 Scope

This part of ISO 6362 specifies the tolerances on dimensions and shape of wrought aluminium and aluminium alloy extruded profiles with a cross-section contained within a circumscribing circle not greater than 800 mm.

This part of ISO 6362 applies to extruded profiles for general engineering applications only.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6362-1, *Wrought aluminium and aluminium alloys — Extruded rods/bars, tubes and profiles — Part 1: Technical conditions for inspection and delivery*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6362-1 apply.

4 Materials

For the purposes of this part of ISO 6362, wrought aluminium and aluminium alloys are divided into two groups, which correspond to varying difficulty when manufacturing the products.

The division into Group I and Group II of the most commonly used general engineering alloys is specified in Tables 1 and 2.

Table 1 — Alloy group I

Alloy system	Alloy number
Pure aluminium	1070, 1070A, 1060, 1050, 1050A, 1100, 1200, 1350
Al-Mn system alloy	3003, 3102, 3103, 3203
Al-Mg system alloy	5005, 5005A, 5051A, 5251
Al-Mg-Si system alloy	6005, 6005A, 6005C, 6008, 6012, 6014, 6018, 6023, 6060, 6061, 6063, 6063A, 6065, 6081, 6082, 6182, 6101, 6101A, 6101B, 6106, 6110A, 6261, 6262, 6262A, 6351, 6360, 6463

Table 2 — Alloy group II (all aluminium alloys except those given in alloy group I)

Alloy system	Alloy number
Al-Mg system alloy	5019, 5049, 5052, 5083, 5086, 5154A, 5454, 5754
Al-Cu-Mg system alloy	2007, 2014, 2014A, 2017, 2017A, 2024, 2030
Al-Zn-Mg system alloy	7204, 7003, 7005, 7020, 7021, 7022, 7049A, 7050, 7075, 7108, 7108A