INTERNATIONAL STANDARD

ISO 8535-1

> Sixth edition 2016-11-15

Diesel engines — Steel tubes for highpressure fuel injection pipes —

Part 1:

Requirements for seamless colddrawn single-wall tubes

Moteurs diesels — Tubes en acier pour lignes d'injection de tte p
ces pour . combustible à haute pression —

Partie 1: Exigences pour les tubes monoparoi sans soudure étirés à froid





© ISO 2016, Published in Switzerland

voduced or utilized c te internet or an 'nr ISO's memb All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Contents			Page
Fore	eword		iv
1	Scope	e	1
2	Norm	ative references	1
3	Terms	s and definitions	1
4	Dimensions and tolerances		
	4.1 Diameters		
	4.2	Length	2
5	Material processing		2
	5.1	Steel manufacturing process	
	5.2	Manufacturing of tubes	
	5.3	Surface quality	
		5.3.1 General Signature General Genera	
		5.3.3 Higher quality inside surface (bore grades 0, P, Q, R)	4
	5.4	Surface finish	
	5.5	Minimum mechanical properties of tubes	5
	5.6	Cleanliness	
	5.7	Straightness	
	5.8	Corrosion resistance	
6	Testing		5
	6.1	General	
	6.2 6.3	Scope of tests Dimension tests	
	6.4	Mechanical-property tests	
	6.5	Bending test	6
	6.6	Cold upsetting of tubes	6
	6.7	Surface quality test	6
	6.8	Inside pressure test	
	6.9 6.10	Retesting Test certificate	
_			
7	Desig	Designation	
8		ification and marking	
9		ng	
Ann	ex A (info	ormative) Theoretical maximum pressure for inside pressur	e testing9
Rihl	iogranhy		10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 22, *Road vehicles*, Subcommittee SC 34, *Propulsion, powertrain, and powertrain fluids*.

This sixth edition cancels and replaces the fifth edition (ISO 8535-1:2011), which has been technically revised with the following changes:

- inside diameter sizes 3,5 mm and 3,6 mm have been added to Table 1;
- code 5 and code 6 have been added to Table 4.

A list of parts in the ISO 8535 series can be found on the ISO website.

NOTE The first part of the general title, "Diesel engines", is used for Part 1 only while for Part 2, "Compressionignition engines" is still used but will be replaced at the next revision.

Diesel engines — Steel tubes for high-pressure fuel injection pipes —

Part 1:

Requirements for seamless cold-drawn single-wall tubes

1 Scope

This document specifies dimensions and requirements for seamless cold-drawn single-wall steel tubes for high-pressure fuel injection pipes used on diesel (compression-ignition) engines (class 2) and for fuel injection pump testing (class 1).

This document applies to diesel (compression-ignition) engines.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6507-1, Metallic materials — Vickers hardness test — Part 1: Test method

ISO 6892-1, Metallic materials — Tensile testing — Part 1: Method of test at room temperature

ISO 12345, Diesel engines — Cleanliness assessment of fuel injection equipment

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

4 Dimensions and tolerances

4.1 Diameters

Recommended inside and outside diameters are given in <u>Table 1</u>. Other sizes may be used by agreement between supplier and customer.

Tolerances on inside and outside diameters shall be as follows.

a) Inside diameter, d

 $d \le 4$ mm: ± 0.05 mm for class 2

±0,025 mm for class 1 (these tolerances are in accordance with ISO 4093)

 $d > 4 \text{ mm}: \pm 0.10 \text{ mm}$