
**Implants for surgery — Components for
partial and total knee joint prostheses —**

Part 2:

**Articulating surfaces made of metal,
ceramic and plastics materials**

*Implants chirurgicaux — Éléments de prothèses partielle et totale de
l'articulation du genou —*

*Partie 2: Surfaces articulaires constituées de matériaux métalliques,
céramiques et plastiques*



This document is a preview generated by EVS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 7207-2 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 4, *Bone and joint replacements*.

This second edition cancels and replaces the first edition (ISO 7207-2:1998), which has been technically revised.

ISO 7207 consists of the following parts, under the general title *Implants for surgery — Components for partial and total knee joint prostheses*:

- *Part 1: Classification, definitions and designation of dimensions*
- *Part 2: Articulating surfaces made of metal, ceramic and plastics materials*

Implants for surgery — Components for partial and total knee joint prostheses —

Part 2: Articulating surfaces made of metal, ceramic and plastics materials

1 Scope

This part of ISO 7207 specifies surface finish requirements for the articulating surfaces of total and partial knee joint prostheses classified in ISO 7207-1. This part of ISO 7207 is intended to provide guidance for periodic validation of production processes.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4287, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Terms, definitions and surface texture parameters*

ISO 4288:1996, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Rules and procedures for the assessment of surface texture*

3 Surface finish requirements

3.1 General

All surface finish measurements shall be performed according to the max.-rule in ISO 4288:1996, 5.3. The max.-rule states that no measurement values shall exceed the specified *R_{max}*.

3.2 Knee joint prostheses

3.2.1 Metallic or ceramic femoral components

When measured in accordance with ISO 4287, all articulating surfaces of a metallic or ceramic femoral component shall be measured across the full articulating surface at locations in an approximately square grid of locations no more than 10 mm apart. The component shall have an *R_{max}* value $\leq 0,1 \mu\text{m}$, using a cut-off value of 0,08 mm.

NOTE The patellar flange is considered an articulating surface in bicompartamental, tricompartmental and patellar femoral replacement systems.