

Mechanical properties of fasteners made of carbon steel and alloy steel - Part 3: Flat washers with specified property classes (ISO 898-3:2018)

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 898-3:2018 sisaldab Euroopa standardi EN ISO 898-3:2018 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 898-3:2018 consists of the English text of the European standard EN ISO 898-3:2018.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 27.06.2018.	Date of Availability of the European standard is 27.06.2018.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 21.060.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:  
Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

**Mechanical properties of fasteners made of carbon steel  
and alloy steel - Part 3: Flat washers with specified  
property classes (ISO 898-3:2018)**

Caractéristiques mécaniques des fixations en acier au  
carbone et en acier allié - Partie 3: Rondelles de forme  
plane de classes de qualité spécifiées (ISO 898-3:2018)

Mechanische Eigenschaften von  
Verbindungselementen aus Kohlenstoffstahl und  
legiertem Stahl - Teil 3: Flache Scheiben mit  
festgelegten Festigkeitsklassen (ISO 898-3:2018)

This European Standard was approved by CEN on 16 May 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

## European foreword

This document (EN ISO 898-3:2018) has been prepared by Technical Committee ISO/TC 2 "Fasteners" in collaboration with Technical Committee CEN/TC 185 "Fasteners" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2018, and conflicting national standards shall be withdrawn at the latest by December 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Endorsement notice

The text of ISO 898-3:2018 has been approved by CEN as EN ISO 898-3:2018 without any modification.

# Contents

Page

<b>Foreword</b>	<b>iv</b>
<b>Introduction</b>	<b>v</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>2</b>
<b>4 Symbols</b>	<b>2</b>
<b>5 Designation system for property classes of washers and combination with property classes of bolts, screws, studs and nuts</b>	<b>2</b>
<b>6 Materials</b>	<b>3</b>
<b>7 Mechanical and physical properties</b>	<b>4</b>
<b>8 Test methods</b>	<b>5</b>
8.1 Hardness test	5
8.1.1 General	5
8.1.2 Hardness test on the washer bearing surface	6
8.1.3 Hardness determined on a transverse radial section through the washer	9
8.2 Decarburization test	10
8.2.1 General	10
8.2.2 Microscopic method	10
8.2.3 Hardness method	11
8.3 Carburization test	12
8.3.1 General	12
8.3.2 Test procedure	12
8.3.3 Requirements	12
8.4 Retempering test	12
8.4.1 General	12
8.4.2 Test procedure	12
8.4.3 Requirements	12
<b>9 Marking</b>	<b>13</b>
9.1 General	13
9.2 Marking of washers	13
9.3 Marking of packages	13
<b>Annex A (normative) Ductility test for washers of property class 380HV</b>	<b>14</b>
<b>Bibliography</b>	<b>17</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 2, *Fasteners*.

A list of all parts in the ISO 898 series can be found on the ISO website.

## Introduction

ISO 898 consists of the following parts, under the general title “*Mechanical properties of fasteners made of carbon steel and alloy steel*”:

- *Part 1: Bolts, screws and studs with specified property classes — Coarse thread and fine pitch thread*
- *Part 2: Nuts with specified property classes — Coarse thread and fine pitch thread*
- *Part 5: Set screws and similar threaded fasteners with specified hardness classes — Coarse thread and fine pitch thread*
- *Part 7: Torsional test and minimum torques for bolts and screws with nominal diameters 1 mm to 10 mm*

This document in the ISO 898 series provides a single point of reference for flat washers, in order to standardize market expectations for users, distributors and manufacturers.

This document only deals with flat washers made of carbon steel or alloy steel.

Washers made of stainless steel are not addressed in this document due to their different characteristics and test methods.

# Mechanical properties of fasteners made of carbon steel and alloy steel —

## Part 3: Flat washers with specified property classes

### 1 Scope

This document specifies mechanical and physical properties of flat washers, designed to be used in bolted joints in combination with bolts, screws, studs and nuts with a specified property class in accordance with ISO 898-1 and ISO 898-2.

NOTE 1 These types of washers can also be used with other fasteners such as screws forming their own mating thread.

Washers that conform to the requirements of this document are evaluated at an ambient temperature range of 10 °C to 35 °C. They might not retain the specified mechanical and physical properties at elevated temperatures and/or lower temperatures.

NOTE 2 Washers conforming to the requirements of this document are used in applications ranging from -50 °C to +150 °C. Users are advised to consult an experienced fastener expert for temperatures outside this range and up to a maximum temperature of +300 °C when determining appropriate choices, or for critical applications.

This document is applicable to the following flat captive and non-captive washers made of carbon steel or alloy steel, with thickness from 0,2 mm to 12 mm:

- plain washers (with or without knurls, ribs or chamfers);
- square washers;
- square hole washers;
- shaped plates.

It does not specify requirements for the following properties:

- corrosion resistance;
- weldability.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1891-4, *Fasteners — Terminology — Part 4: Controls, inspection, delivery, acceptance and quality*

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

ISO 6508-1, *Metallic materials — Rockwell hardness test — Part 1: Test method*

ISO 10644, *Screw and washer assemblies made of steel with plain washers — Washer hardness classes 200 HV and 300 HV*



ISO 10669, *Plain washers for tapping screw and washer assemblies — Normal and large series — Product grade A*

ISO 10673, *Plain washers for screw and washer assemblies — Small, normal and large series — Product grade A*

ISO 10684, *Fasteners — Hot dip galvanized coatings*

### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 4 Symbols

For the purposes of this document, the following symbols apply.

$d_1$	clearance hole, mm
$d_2$	outside diameter, mm
$F$	force, N
$G$	depth of the complete decarburization, mm
$r$	radius of the supporting part and pressure part for the ductility test, mm
$t$	nominal thickness of flat washer, mm
$t_{\text{eff}}$	effective thickness of the material measured on the washer, mm
$\alpha$	angle of the supporting part and pressure part for the ductility test, °

### 5 Designation system for property classes of washers and combination with property classes of bolts, screws, studs and nuts

The symbol for property classes of washers is composed of two parts:

- the number to the left is the minimum Vickers hardness value in accordance with [Table 3](#);
- the letters HV to the right represent Vickers hardness.

**EXAMPLE** A steel flat washer with a minimum Vickers hardness of 200 according to [Table 3](#) has the property class designation 200HV.

The designation system of this document may be applied for sizes outside its scope (e.g. for washers with thickness  $t > 12$  mm) provided all applicable requirements in accordance with [Tables 2](#) and [3](#) are met.

Although a great number of property classes is specified in this document, this does not mean that all property classes are appropriate for all washers and/or for all bolts/nuts/washers assemblies. The combination of property classes for flat washers with bolts, screws, studs and nuts is specified in [Table 1](#).