
**Ferrous materials — Heat treatments
— Vocabulary**

Matériaux ferreux — Traitements thermiques — Vocabulaire



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
Annex A (informative) Equivalent terms	31
Bibliography	41

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 17, *Steel*.

This second edition cancels and replaces the first edition (ISO 4885:1996), which has been technically revised.

Ferrous materials — Heat treatments — Vocabulary

1 Scope

This document defines important terms used in the heat treatment of ferrous materials.

NOTE The term ferrous materials include products and workpieces of steel and cast iron.

[Annex A](#) provides an alphabetical list of terms defined in this document, as well as their equivalents in French, German, Chinese and Japanese.

[Table 1](#) shows the various iron-carbon (Fe-C) phases.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

acicular structure

structure which appears in the form of needles in a micrograph

3.2

activity

effective concentration of species under non-ideal (e.g. concentrated) conditions; for *heat treatment* ([3.108](#)), this means the effective concentration of carbon or nitrogen (or both) in heat treatment media and in ferrous materials

Note 1 to entry: Ratio of the vapour pressure of a gas (usually carbon or nitrogen) in a given state (e.g. in *austenite* ([3.12](#)) of specific carbon/nitrogen concentration) to the vapour pressure of the pure gas, as a reference state, at the same temperature.

3.3

ageing

change in the properties of steels depending on time and temperature after hot working or *heat treatment* ([3.108](#)) or after cold-working operation due to the migration of interstitial elements

Note 1 to entry: The ageing phenomenon can lead to higher strength and lower ductility.

Note 2 to entry: The ageing can be accelerated either by cold forming and/or subsequent *heating* ([3.109](#)) to moderate temperatures (e.g. 250 °C) and soaking (e.g. for 1 h) to create the ageing effects.

3.4

air-hardening steel

DEPRECATED: self-hardening steel

steel, the *hardenability* ([3.103](#)) of which is such that *cooling* ([3.45](#)) in air produces a martensitic structure in objects of considerable size