

**Puitkonstruktsioonid. Ehituspuit ja liimpuit. Mõnede füüsikaliste ja mehaaniliste omaduste määramine
KONSOLIDEERITUD TEKST**

Timber structures - Structural timber and glued laminated timber - Determination of some physical and mechanical properties CONSOLIDATED TEXT

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 408:2010+A1:2012 sisaldab Euroopa standardi EN 408:2010+A1:2012 ingliskeelset teksti.	This Estonian standard EVS-EN 408:2010+A1:2012 consists of the English text of the European standard EN 408:2010+A1:2012.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 25.07.2012.	Date of Availability of the European standard is 25.07.2012.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 79.040, 79.060.99, 91.080.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

ICS 91.080.20; 79.040; 79.060.99

English Version

Timber structures - Structural timber and glued laminated timber - Determination of some physical and mechanical properties

Structures en bois - Bois de structure et bois lamellé-collé -
Détermination de certaines propriétés physiques et
mécaniques

Holzbauwerke - Bauholz für tragende Zwecke und
Brettschichtholz - Bestimmung einiger physikalischer und
mechanischer Eigenschaften

This European Standard was approved by CEN on 16 June 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Symbols and abbreviations	6
5 Determination of dimensions of test pieces	8
6 Determination of moisture content of test pieces	8
7 Determination of density of test pieces	8
8 Conditioning of test pieces.....	8
9 Determination of local modulus of elasticity in bending.....	9
9.1 Test piece	9
9.2 Procedure	9
9.3 Expression of results	10
10 Determination of global modulus of elasticity in bending	11
10.1 Test piece	11
10.2 Procedure	11
10.3 Expression of results	12
11 Determination of the shear modulus	13
11.1 Torsion method.....	13
11.1.1 Test piece	13
11.1.2 Procedure	13
11.1.3 Expression of results	16
11.2 Shear field test method	17
11.2.1 Test piece	17
11.2.2 Procedure	17
11.2.3 Expression of results	19
12 Determination of modulus of elasticity in tension parallel to the grain.....	19
12.1 Test piece	19
12.2 Procedure	19
12.3 Expression of results	20
13 Determination of tension strength parallel to the grain.....	20
13.1 Test piece	20
13.2 Procedure	21
13.3 Expression of results	21
14 Determination of modulus of elasticity in compression parallel to the grain	21
14.1 Test piece	21
14.2 Procedure	22
14.3 Expression of results	22
15 Determination of compression strength parallel to grain	22
15.1 Test piece	22
15.2 Procedure	22
15.3 Expression of results	23
16 Determination of tension and compression strengths perpendicular to the grain	23
16.1 Requirements for test pieces	23

16.1.1	Fabrication	23
16.1.2	Surface preparation.....	23
16.2	Procedure.....	24
16.3	Expression of results	27
16.3.1	Compression perpendicular to the grain	27
16.3.2	Tension perpendicular to the grain	27
17	Determination of modulus of elasticity perpendicular to the grain	27
17.1	Requirements for test pieces	27
17.2	Procedure.....	27
17.3	Expression of results	28
17.3.1	Compression perpendicular to the grain	28
17.3.2	Tension perpendicular to the grain	28
18	Determination of shear strength parallel to the grain	29
18.1	Requirements for test pieces	29
18.1.1	Fabrication	29
18.1.2	Surface preparation.....	29
18.2	Procedure.....	30
18.3	Expression of results	31
19	Bending strength parallel to grain.....	32
19.1	Test piece	32
19.2	Procedure.....	32
19.3	Expression of results	33
20	Test report.....	34
20.1	General	34
20.2	Test piece	34
20.3	Test method	34
20.4	Test results	34
Annex A	(informative) Example of compression perpendicular to grain test arrangement	35
Annex B	(informative) Example of tension perpendicular to grain test arrangement with rigid fixings	37
Bibliography	38

Foreword

This document (EN 408:2010+A1:2012) has been prepared by Technical Committee CEN/TC 124 “Timber structures”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2013, and conflicting national standards shall be withdrawn at the latest by January 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1 approved by CEN on 16 June 2012.

The start and finish of text introduced or altered by amendment is indicated in the text by tags **A1** **A1**.

This document supersedes **A1** EN 408:2010. **A1**

In this revised standard a new test is added for the determination of the shear modulus.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This 2010 revision replaces the test for the determination of the shear strength parallel to grain.

The revised edition of 2003 added a global bending modulus of elasticity, whilst renaming the existing test as the local modulus of elasticity. It also includes the methods for determination of shear strength and mechanical properties perpendicular to the grain, previously given in EN 1193, which has now been withdrawn.

The values obtained in any determination of the properties of timber depend upon the test methods used. It is therefore desirable that these methods be standardized so that results from different test centres can be correlated. Moreover, with the adoption of limit state design and with the development of both visual and machine stress grading, attention will be increasingly centred on the determination and monitoring of the strength properties and variability of timber in structural sizes. Again, this can be more effectively undertaken if the basic data are defined and obtained under the same conditions.

This European Standard, which is based originally on ISO 8375, specifies laboratory methods for the determination of some physical and mechanical properties of timber in structural sizes. The methods are not intended for the grading of timber or for quality control.

For the determination of shear modulus, alternative methods have been specified. The choice of which to use will depend upon the objective of the investigation and, to some extent, on the equipment available. Following testing to this standard it is intended that the determination of characteristic values will normally be obtained according to procedures specified in other European Standards.

Attention is drawn to the advantages that may be gained, often with little extra effort, in extending the usefulness of test results by recording additional information on the growth characteristics of the pieces that are tested, particularly at the fracture sections. Generally, such additional information should include grade-determining features such as knots, slope of grain, rate of growth, wane, etc., on which visual grading rules are based, and strength indicating parameters such as localized modulus of elasticity, on which some machine stress grading is based.

1 Scope

This European Standard specifies test methods for determining the following properties of structural timber and glued laminated timber: modulus of elasticity in bending; shear modulus; bending strength; modulus of elasticity in tension parallel to the grain; tension strength parallel to the grain; modulus of elasticity in compression parallel to the grain; compression strength parallel to the grain; modulus of elasticity in tension perpendicular to the grain; tension strength perpendicular to the grain; modulus of elasticity in compression perpendicular to the grain; compression strength perpendicular to the grain and shear strength.

In addition, the determination of dimensions, moisture content, and density of test pieces are specified.

The methods apply to rectangular and circular shapes (of substantially constant cross section) of solid jointed timber or finger-jointed timber and glued laminated timber unless stated otherwise.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 384:2010, *Structural timber — Determination of characteristic values of mechanical properties and density* ^(A1)

EN 13183-1, *Moisture content of a piece of sawn timber — Part 1: Determination by oven dry method*

3 Terms and definitions

Not applicable.

4 Symbols and abbreviations

A	cross-sectional area, in square millimetres;
a	distance between a loading position and the nearest support in a bending test, in millimetres;
b	width of cross section in a bending test, or the smaller dimension of the cross section, in millimetres;
$E_{c,0}$	modulus of elasticity in compression parallel to the grain, in newtons per square millimetre;
$E_{c,90}$	modulus of elasticity in compression perpendicular to the grain, in newtons per square millimetre;
$E_{m,g}$	global modulus of elasticity in bending, in newtons per square millimetre;
$E_{m,l}$	local modulus of elasticity in bending, in newtons per square millimetre;
$E_{t,0}$	modulus of elasticity in tension parallel to the grain, in newtons per square millimetre;
$E_{t,90}$	modulus of elasticity in tension perpendicular to the grain, in newtons per square millimetre;
F	load, in newtons;
$F_{c,90}$	compressive load perpendicular to the grain, in newtons;
$F_{c,90,max}$	maximum compressive load perpendicular to the grain, in newtons;
$F_{c,90,max,est}$	estimated maximum compressive load perpendicular to the grain, in newtons;