
**Rubber hoses and tubing for air
and vacuum systems for internal-
combustion engines — Specification**

*Tuyaux et tubes en caoutchouc pour systèmes d'aération et à vide des
moteurs à combustion interne — Spécifications*



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms, definitions and abbreviated terms	2
4 Classification	2
4.1 Types	2
4.2 Classes	2
5 Hose and tubing bores	3
6 Dimensions and tolerances	3
6.1 Hoses	3
6.2 Tubing	3
7 Requirements for physical properties	4
7.1 Rubber compounds	4
7.1.1 Selection of test pieces	4
7.1.2 Hardness	4
7.1.3 Tensile strength and elongation at break	4
7.1.4 Change in properties after heat-ageing	4
7.1.5 Compression set	5
7.1.6 Resistance to oxygenated fuels	5
7.1.7 Resistance to oil No.3	5
7.2 Hose and tubing	5
7.2.1 Proof pressure	5
7.2.2 Minimum burst pressure	6
7.2.3 Adhesion	6
7.2.4 Ozone resistance	6
7.2.5 Low-temperature flexibility after heat-ageing	6
7.2.6 Amount of extractable products	6
7.2.7 Tear resistance	6
7.2.8 Suction resistance (only for Type A)	6
7.2.9 Resistance to kinking	7
8 Frequency of testing	7
9 Marking	7
10 Recommendations for packaging and storage	7
Annex A (normative) Type and routine tests	10
Annex B (informative) Recommended production tests	11
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Hoses (rubber and plastics)*.

This second edition cancels and replaces the first edition (ISO 11424:1996), which has been technically revised.

The main changes are the following:

- in [6.2](#), inside diameter (ID) for each nominal bore has been included;
- requirement on frequency of testing has been added in [Clause 8](#);
- requirement to mark nominal bore of the hose or tubing has been added in [Clause 9](#);
- recommendations for packaging and storage have been added in [Clause 10](#);
- [Annex A](#) and [Annex B](#) have been added.

Rubber hoses and tubing for air and vacuum systems for internal-combustion engines — Specification

1 Scope

This document specifies requirements for rubber hoses and tubing for use in the various air and vacuum systems found on internal combustion engines. This document does not cover hoses used for direct power-brake actuation in trucks and trailers, nor for air intakes and ducting within the passenger compartment. The highest-temperature hoses are generally used for turbocharger applications. All hoses and tubing remain serviceable down to -40°C .

NOTE Although the term vacuum is generally used, in reality the application is one of reduced air pressure used for the purposes of actuation or monitoring of the various engine-system components. The air carried by the tubing or hoses may be clean and free of contaminants but may also contain oil, fuel and their vapours as contamination, due to the particular installation and application.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37:2011, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 48, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

ISO 188, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 815-1:2014, *Rubber, vulcanized or thermoplastic — Determination of compression set — Part 1: At ambient or elevated temperatures*

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 1629, *Rubber and latices — Nomenclature*

ISO 1817:2015, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 3302-1, *Rubber — Tolerances for products — Part 1: Dimensional tolerances*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies*

ISO 7233:2016, *Rubber and plastics hoses and hose assemblies — Determination of resistance to vacuum*

ISO 7326, *Rubber and plastics hoses — Assessment of ozone resistance under static conditions*

ISO 8033, *Rubber and plastics hoses — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 10619-1:2011, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 1: Bending tests at ambient temperature*

ISO 10619-2:2011, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 2: Bending tests at sub-ambient temperatures*

ISO 19013-1:2005, *Rubber hoses and tubing for fuel circuits for internal combustion engines — Specification — Part 1: Diesel fuels*

3 Terms, definitions and abbreviated terms

For the purposes of this document, the terms and definitions given in ISO 8330 and the abbreviated terms given in ISO 1629 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Classification

4.1 Types

Type A — internally reinforced hose with a working pressure up to 0,3 MPa (3 bar).

Type B — homogeneous tube with a working pressure up to 0,12 MPa (1,2 bar).

4.2 Classes

Class 1 — Long-term working temperature up to 70 °C; maximum working temperature up to 100 °C. Not recommended for applications where resistance to oils, fuel and their vapours is required.

NOTE 1 Typically, styrene-butadiene rubber (SBR) can be used.

Class 2 — Long-term working temperature up to 100 °C; maximum working temperature up to 125 °C. Resistant to oils and their vapours.

NOTE 2 Typically, chloroprene rubber (CR) can be used.

Class 3 — Long-term working temperature up to 100 °C, maximum working temperature up to 125 °C. Resistant to oils, fuels and their vapours.

NOTE 3 Typically, acrylonitrile-butadiene rubber (NBR) can be used.

Class 4 — Long-term working temperature up to 125 °C, maximum working temperature up to 150 °C. Not recommended for applications where resistance to oils, fuels and their vapours is required.

NOTE 4 Typically, ethylene-propylene rubber (EPM or EPDM) can be used.

Class 5 — Long-term working temperature up to 125 °C, maximum working temperature up to 150 °C. Resistant to oils and their vapours.

NOTE 5 Typically, chlorinated or chlorosulfonated polyethylene (CM or CSM) can be used.

Class 6 — Long-term working temperature up to 125 °C, maximum working temperature up to 150 °C. Resistant to oils, fuels and their vapours.

NOTE 6 Typically, epichlorohydrin or hydrogenated nitrile rubbers (CO, ECO or HNBR) can be used.

Class 7 — Long-term working temperature up to 150 °C, maximum working temperature up to 175 °C. Not recommended for applications where resistance to oils, fuels and their vapours is required.

NOTE 7 Typically, silicone rubber (VMQ) can be used.