INTERNATIONAL ISO Le de la constant de 20136 **STANDARD IULTCS/IUC 37**

First edition 2017-03

Cuir — Détermination de la dégradabilité par les micro-organismes



Reference numbers ISO 20136:2017(E) IULTCS/IUC 37:2017(E)



© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

ISO 20136:2017(E) IULTCS/IUC 37:2017(E)

Contents

Forew	ord		iv
Introd	uction	1	v
1	Scope		1
2	Norm	ative references	1
3	Terms and definitions		
4	Symbols and abbreviated terms		
5	Princi	inle	2
	5.1	Method A: assessment of biodegradation by manual titration	2
	5.2	Method B: assessment of biodegradation by infrared detection	2
6	Chem	icals	3
7	Apparatus and materials		
8	Proce	dure	6
	8.1	Collection and preparation of the inoculum	6
	8.2	Preparation of the test material and reference material	6
	8.3	Test conditions and incubation period	6
	8.4	Test equipment	6
		8.4.1 Equipment for the assessment of biodegradation by manual titration	6
		(equipment A)	0 7 (2
	85	Find of the test	ין ר 7
	0.5		/
9	Quantification		
	9.1	Equipment for the assessment of biodegradation by manual titration (equipment A)	8
		9.1.1 Determination of the organic carbon content	б
		9.1.2 Determination of the amount of carbon dioxide produced (Method A)	0 Q
		9.1.5 Correcting for normality of HCL 9.1.4 Percentage of biodegradation from carbon dioxide evolved	0 Q
	92	Equipment for the assessment of biodegradation by IR detection (Method B)	8
	7.2	9.2.1 Determination of the organic carbon content	8
		9.2.2 Determination of the amount of carbon dioxide (CO ₂ produced)	9
		9.2.3 Percentage of biodegradation from CO ₂ data	9
10	Expre	ession of results	10
11	Validi	ity of results	10
12	Test r	enort	10
Annex	A (info	ormative) Determination of the degree and rate of degradation of the material	11
Anney	R (inf	ormative) Determination of the degree and rate of degradation of the indegradation	16
		ormative) Quantitative determination of feather biodegradation	.10
Biblio	graphy	Y	20

ISO 20136:2017(E) IULTCS/IUC 37:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html

This document was prepared by the Chemical Tests Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international method for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

Introduction

One of the big problems faced by the footwear industry is waste treatment. Although this waste, especially in the case of leather, is not considered hazardous by current legislation, it is however produced in large quantities which present a problem for municipal landfill sites.

The aim of the tanning process is to avoid skin putrefaction and increase the resistence of the obtained leather. For this purpose, chemical and biological agents are used which are involved in the denaturation and hardening of the main stromal protein, collagen, thus also producing physicochemical changes in the skin.

There is a wide range of different agents used for leather tanning, which can be based on organic products, vegetable extracts or inorganic products, mostly metals.

The most used tanning agent in the footwear industry is Chromium (III), which gives the skin desirable characteristics, such as elasticity, easy buffing and a good breathability and vapour permeability. However, the traditional tanning industry, and especially chrome tanning, generates wastes that pose an environmental threat. Also, chrome-tanned hides and skins have too long a lifespan, much larger than the useful life of the final products. Therefore, the use of additives that are less harmful to the environment and which generate products that have a certain ease of degradation, once the material has achieved its purpose, would be preferred, thus minimising waste products.

Within this sector, the development of fast biodegradability quantification methods for leather that has been treated with alternative tanning agents is needed in order to predict whether these materials are more biodegradable than their predecessors. The methodology described in this document attempts to allow the completion of this form of analysis in a test time of no more than 35 days.

.he n a te.

this document is a preview demendence of the document is a preview demendence of the document of the document

Leather — Determination of degradability by microorganisms

1 Scope

This document specifies a test method to determine the degree and rate of aerobic biodegradation of hides and skins of different animal origin, whether they are tanned or not, through the indirect determination of CO_2 produced by the degradation of collagen.

The test material is exposed to an inoculum (activated sludge from tannery wastewater) in an aqueous medium.

The conditions established in this document correspond to optimum laboratory conditions to achieve the maximum level of biodegradation. However, they may not necessarily correspond to the optimum conditions or maximum level of biodegradation in the natural medium.

In general, the experimental procedure covers the determination of the degradation degree and rate of the material under controlled conditions, which allows the analysis of the evolved carbon dioxide produced throughout the test. For this purpose, the testing equipment complies with strict requirements with regard to flow, temperature and agitation control.

This method applies to the following materials:

- natural polymers of animal stroma (animal tissue/skins),
- animal hides and skins tanned (leather) using organic or inorganic tanning agents,
- leathers that, under testing conditions, do not inhibit the activity of microorganisms present in the inoculum.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— IEC Electropedia: available at <u>http://www.electropedia.org/</u>

— ISO Online browsing platform: available at http://www.iso.org/obp

3.1

filter pore no. 1

diffuser with pore size from 100 microns to 160 microns

Note 1 to entry: This measurement is standard.

3.2

inoculum activated sludge from tannery wastewater 52