
**Rubber — Determination of
magnesium content of field natural
rubber latex by titration**

*Caoutchouc — Détermination par titrage de la teneur en magnésium
du latex de plantation de caoutchouc naturel*



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Apparatus.....	2
6 Reagents.....	2
7 Procedure.....	3
8 Expression of results.....	4
9 Precision.....	4
10 Test report.....	4
Annex A (informative) Precision.....	5
Bibliography.....	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This second edition cancels and replaces the first edition (ISO 11852:2011), which has been technically revised to be applicable only to field latex. Therefore, all references to concentrated natural rubber latex have been removed and the following changes have been made:

- the title of this document has been changed;
- an introduction has been added to explain the advantages of the method described in this document;
- the definition of natural rubber latex concentrate has been removed from [Clause 3](#);
- the determination of magnesium content of concentrated latex in [Clause 5](#) has been deleted;
- because borax is a substance of high concern and reprotoxic, the buffer solution ([6.4](#)) has been changed from borax buffer solution to ammonium chloride/ammonium hydroxide buffer solution;
- the precision data for concentrated latex in [Annex A](#) have been deleted.

Introduction

In this document, no additional chemical is required to mask the interference from other divalent ions. The end-point determination in this method is easily determined since most, if not all, of the interferences have been removed during the centrifugation process. Furthermore, the chemical used for masking the interference in the alternative method has an unpleasant odour.

Another advantage of this document is that the centrifuge machine used in the method is already available in laboratory for desludging purposes. Hence, no additional cost is incurred by the laboratory to carry out the test.

Rubber — Determination of magnesium content of field natural rubber latex by titration

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This document specifies a titration method for the determination of the magnesium content of field natural rubber latex.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385:2005, *Laboratory glassware — Burettes*

ISO 648:2008, *Laboratory glassware — Single-volume pipettes*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

magnesium content

amount of magnesium, and possibly also other alkaline-earth metals, present in a sample of natural rubber field latex

Note 1 to entry: When ammonia is added to field latex, the calcium and magnesium ions present in varying concentrations in the serum of the latex are, to a large extent, precipitated as ammonium phosphate complexes, which gradually settle out in the sludge. The results of the test method described in this document are expressed as the magnesium content on the assumption, which is not strictly true, that magnesium is the only divalent alkaline-earth ion remaining in the latex after the sludge has been removed. Calcium ions are also present, occasionally in appreciable amounts.

4 Principle

The latex is centrifuged at between 2 500 m/s² (250g) and 5 000 m/s² (500g), using a laboratory centrifuge, for 3 min. A known mass of the resultant latex, free of sludge, is diluted with water, and the residual magnesium content present in the latex is determined by titration with the disodium salt of