

**Hoiatusrõivad professionaalseks
kasutamiseks. Katsemeetodid ja nõuded
KONSOLIDEERITUD TEKST**

High-visibility warning clothing for professional
use - Test methods and requirements
CONSOLIDATED TEXT

EESTI STANDARDI EESSÕNA**NATIONAL FOREWORD**

<p>Käesolev Eesti standard EVS-EN 471:2004+A1:2008 sisaldab Euroopa standardi EN 471:2003+A1:2007 ingliskeelset teksti.</p> <p>Standard on kinnitatud Eesti Standardikeskuse 28.01.2008 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 12.12.2007.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN 471:2004+A1:2008 consists of the English text of the European standard EN 471:2003+A1:2007.</p> <p>This standard is ratified with the order of Estonian Centre for Standardisation dated 28.01.2008 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.</p> <p>Date of Availability of the European standard text 12.12.2007.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

ICS 13.340.10**Võtmesõnad:****Standardite reprodutseerimis- ja levitamisoigus kuulub Eesti Standardikeskusele**

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
 Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

English Version

High-visibility warning clothing for professional use - Test methods and requirements

Vêtements de signalisation à haute visibilité pour usage professionnel - Méthodes d'essai et exigences

Warnkleidung - Prüfverfahren und Anforderungen

This European Standard was approved by CEN on 1 August 2003 and includes Amendment 1 approved by CEN on 10 November 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 Design	8
4.1 Types and classes	8
4.2 Specific design requirements.....	8
4.3 Sizes.....	9
5 Requirements for background material, non-fluorescent material and combined performance materials	9
5.1 Colour performance requirements of new materials	9
5.1.1 Background material	9
5.1.2 Combined performance material.....	9
5.2 Colour after xenon test	10
5.3 A1 Colour fastness of background material and all non-fluorescent material layers after test exposure A1	10
5.3.1 Colour fastness to rubbing.....	10
5.3.2 Colour fastness to perspiration	10
5.3.3 Colour fastness - when laundered, dry cleaned, hypochlorite bleached and hot pressed	10
5.4 Dimensional change of background material and non-fluorescent material	12
5.5 Mechanical properties of background materials.....	12
5.5.1 Tensile strength of woven material.....	12
5.5.2 Bursting strength of knitted materials.....	12
5.5.3 Tensile strength and tear resistance of coated fabrics and laminates	12
5.6 A1 Water vapour resistance A1	12
5.6.1 General.....	12
5.6.2 Background material made from coated fabrics or laminates.....	12
5.6.3 Background material made from textile fabrics	12
5.7 Ergonomics	12
6 Photometric and physical performance requirements for the retroreflective material and combined performance material	13
6.1 Retroreflective performance requirements of new material	13
6.2 Retroreflective performance requirements after test exposure	14
6.2.1 General.....	14
6.2.2 Separate performance material	14
6.2.3 Combined performance material.....	15
6.2.4 Orientation sensitive materials	15
7 Test methods.....	15
7.1 Sampling and conditioning.....	15
7.2 Determination of colour	15
7.3 Method for determination of retroreflective photometric performance	15
7.4 Retroreflection after exposure	16
7.4.1 Abrasion	16
7.4.2 Flexing	16
7.4.3 Folding at cold temperatures	16
7.4.4 Exposure to temperature variation	16
7.4.5 Washing, dry cleaning.....	16

7.5	Retroreflective performance in rainfall	17
8	Marking.....	17
9	Information supplied by the manufacturer	17
Annex A	(informative) Examples for positioning of bands of retroreflective material	18
Annex B	(normative) Positioning of bands of retroreflective material on jackets	23
Annex C	(normative) Method of measuring wet retroreflective performance	24
C.1	Principle.....	24
C.2	Apparatus.....	24
C.3	Procedure.....	24
Annex ZA	(informative) Clauses of this European Standard addressing essential requirements or other provisions of EU Directives.....	26
Bibliography	27

Foreword

This document (EN 471:2003+A1:2007) has been prepared by Technical Committee CEN/TC 162 "Protective clothing including hand and arm protection and lifejackets", the secretariat of which is held by DIN.

This document shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2008 and conflicting national standards shall be withdrawn at the latest by June 2008.

This document includes Amendment 1 approved by CEN on 2007-11-10.

This document supersedes A1 EN 471:2003 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Introduction

This European Standard provides a solution that enables the major issues to be resolved. The performance of the conspicuous materials to be used in "high visibility clothing" is specified together with minimum areas and placement of the materials.

Conspicuity is enhanced by high contrast between the clothing and the ambient background against which it is seen; and by larger areas of the conspicuous materials specified.

Three areas of background and combined performance material colours are defined in an appropriate manner for clothing material, all of which will confer conspicuity against most backgrounds found in urban and rural situations in daylight. However users should consider the prevailing ambient background in which protection is required and select the colour that provides the preferred contrast.

Two levels of separate performance retroreflective materials are included. Higher levels of retroreflection provide greater contrast and visibility of warning clothing when seen in headlights during darkness. When greater conspicuity is required the higher level of retroreflecting material should be used.

Design requirements illustrating the disposition of retroreflective materials are included within the standard. The ergonomics of the wearer should be considered when selecting the most appropriate configuration of retroreflective materials within the garment.

Three classes of warning clothing are specified in terms of the minimum areas of the materials to be incorporated. Whilst the area comprising clothing is obviously dictated by the type of clothing and also the size of the wearer, it should be noted that class 3 clothing offers greater conspicuity against most urban and rural backgrounds than class 2 garments which in turn are significantly superior to class 1 clothing.

Selection and use of high-visibility warning clothing can vary among European countries. It should be based on a risk assessment of the condition in which the warning clothing is to be used. This will involve consideration of the requirements necessary for an observer to understand that a wearer is present. The observer needs both to perceive and to recognise the wearer and then to decide to take appropriate avoidance action. The wearing of a high-visibility garment does not guarantee that the wearer will be visible under all conditions.

Test methods ensure that a minimum level of protection is maintained when the garments are subjected to care procedures. Test methods detailed in this standard are for new materials and not intended for products in use.

Attention is drawn to EN 1150, which specifies characteristics and properties for visibility clothing for non-professional use.

1 Scope

This European Standard specifies requirements for protective clothing capable of signalling the user's presence visually, intended to provide conspicuity of the user in hazardous situations under any light conditions by day and under illumination by vehicle headlights in the dark.

Performance requirements are included for colour and retroreflection as well as for the minimum areas and for the disposition of the materials in protective clothing.

2 Normative references

The following referenced documents are indispensable for the application of this European Standard. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 340, *Protective clothing — General requirements*

EN 343:2003+A1, *Protective clothing - Protection against rain*

EN 530:1994, *Abrasion resistance of protective clothing material — Test methods*

EN 31092, *Textiles — Determination of physiological properties - Measurement of thermal and water- vapour resistance under steady-state conditions (sweating guarded - hotplate test) (ISO 11092:1993)*

EN ISO 3175-2:1998, *Textiles — Dry cleaning and finishing — Part 2: Procedures for tetrachloroethene (ISO 3175-2:1998)*

EN ISO 6330:2000, *Textiles — Domestic washing and drying procedures for textile testing (ISO 6330:2000)*

EN ISO 7854:1997, *Rubber or plastic coated fabrics — Determination of resistance to damage by flexing (ISO 7854:1995)*

EN ISO 13934-1, *Textiles — Tensile properties of fabrics — Part 1: Determination of maximum force and elongation at maximum force using the strip method (ISO 13934-1:1999)*

EN ISO 13938-1, *Textiles — Bursting properties of fabrics — Part 1: Hydraulic method for determination of bursting strength and bursting distension (ISO 13938-1:1999)*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey Scale for assessing change in colour*

ISO 105-A03, *Textiles — Tests for colour fastness — Part A03: Grey Scale for assessing staining*

ISO 105-B02:1994, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon Arc fading lamp test*

ISO 105-C06, *Textiles — Tests for colour fastness — Part C06: Colour fastness to domestic and commercial laundering*

ISO 105-D01, *Textiles — Tests for colour fastness — Part D01: Colour fastness to dry cleaning*

ISO 105-E04, *Textiles — Tests for colour fastness — Part E04: Colour fastness to perspiration*

ISO 105-N01, *Textiles — Tests for colour fastness — Part N01: Colour fastness to bleaching: Hypochlorite*

ISO 105-X11, *Textiles — Tests for colour fastness — Part X11: Colour fastness to hot pressing*

ISO 105-X12, *Textiles — Tests for colour fastness — Part X12: Colour fastness to rubbing*

ISO 4674:1977, *Fabrics coated with rubber or plastics; - Determination of tear resistance*

ISO 4675, *Rubber- or plastics-coated fabrics — Low-temperature bend test*

ISO 15797:2002, *Textiles — Industrial washing and finishing procedures for testing of workwear*

CIE 15.2:1986, *Colorimetry*

CIE 17.4:1987, *International lighting vocabulary*

CIE 54.2:2001, *Retroreflection: Definition and measurement*

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

3.1

high-visibility warning clothing

warning clothing intended to provide conspicuity at all times

3.1.1

fluorescent material

material that emits optical radiation at wavelengths longer than absorbed

3.1.2

background material

coloured fluorescent material intended to be highly conspicuous, but not intended to comply with the requirements of this standard for retroreflective material

3.1.3

retroreflective material

material which is a retroreflector but which is not intended to comply with the requirements of this standard for background material

3.1.4

separate-performance material

material intended to exhibit either background or retroreflective properties but not both

3.1.5

combined-performance material

material intended to exhibit both background and retroreflective properties

3.1.6

orientation sensitive material

material having coefficients of retroreflection that differ by more than 15 % when measured at the two rotation angles $\varepsilon_1 = 0^\circ$ and $\varepsilon_2 = 90^\circ$

3.2

photometric terms

NOTE the photometric terms used in this document are defined in CIE Publication No 17.4:1987 and No 54.2:2001