

Methods of test for dense shaped refractory products -
Part 1: Determination of bulk density, apparent
porosity and true porosity

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 993-1:2018 sisaldab Euroopa standardi EN 993-1:2018 ingliskeelset teksti.	This Estonian standard EVS-EN 993-1:2018 consists of the English text of the European standard EN 993-1:2018.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 05.12.2018.	Date of Availability of the European standard is 05.12.2018.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 81.080

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Methods of test for dense shaped refractory products -
Part 1: Determination of bulk density, apparent porosity
and true porosity

Méthodes d'essai pour produits réfractaires façonnés
denses - Partie 1 : Détermination de la masse
volumique apparente, de la porosité ouverte et de la
porosité totale

Prüfverfahren für dichte geformte feuerfeste
Erzeugnisse - Teil 1: Bestimmung der Rohdichte,
offenen Porosität und Gesamtporosität

This European Standard was approved by CEN on 5 October 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	3
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	5
4 Principle	7
5 Apparatus.....	7
6 Test pieces	7
7 Procedure.....	8
7.1 Determination of mass of dry test piece (m_1)	8
7.2 Soaking of test piece.....	8
7.3 Determination of apparent mass of immersed test piece (m_2)	9
7.4 Determination of mass of soaked test piece (m_3).....	9
7.5 Determination of density of immersion liquid.....	9
8 Expression of results.....	10
8.1 Bulk density	10
8.2 Apparent porosity.....	10
8.3 True porosity	10
9 Test report.....	11
10 Precision and bias.....	12
10.1 Interlaboratory study	12
10.2 Precision data.....	12
10.2.1 Repeatability.....	12
10.2.2 Reproducibility	12
10.2.3 Bias.....	12
Bibliography.....	14

European foreword

This document (EN 993-1:2018) has been prepared by Technical Committee CEN/TC 187 “Refractory products and materials”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2019, and conflicting national standards shall be withdrawn at the latest by June 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 993-1:1995.

It is closely based on the corresponding International Standard, ISO 5017 “Dense shaped refractory products - Determination of bulk density, apparent porosity and true porosity”.

Reproducibility and repeatability data are available only for a limited number of testing methods and materials, but may be complemented in subsequent edition.

The series of standards EN 993 ‘Methods of test for dense shaped refractory products’ consists of 20 Parts, some of which have been withdrawn and replaced by equivalent standards:

- *Part 1: Determination of bulk density and porosity*
- *Part 2: Determination of true density*
- *Part 3: Test methods for carbon-containing refractories*
- *Part 4: Determination of permeability to gases*
- *Part 5: Determination of cold crushing strength*
- *Part 6: Determination of modulus rupture, ambient temperatures*
- *Part 7: Determination of modulus of rupture, elevated temperatures*
- *Part 8: Determination of refractoriness under load – withdrawn – replaced by EN ISO 1893*
- *Part 9: Determination of creep in compression*
- *Part 10: Determination of permanent change in dimensions on heating*
- *Part 11: Determination of resistance to thermal shock (ENV)*
- *Part 12: Determination of pyrometric cone equivalent*
- *Part 13: Specification for pyrometric cones*
- *Part 14: Determination of thermal conductivity (hot wire, cross array) – withdrawn – replaced by EN ISO 8894-1*
- *Part 15: Determination of thermal conductivity (hot wire, parallel)*

- *Part 16: Determination of resistance to acids*
- *Part 17: Determination of bulk density of granular material (mercury method)*
- *Part 18: Determination of bulk density of granular material (water method)*
- *Part 19: Determination of thermal expansion by a differential method*
- *Part 20: Determination of resistance to abrasion at ambient temperature* – withdrawn – replaced by EN ISO 16282

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This document specifies a method for the determination of the bulk density, apparent porosity and true porosity of dense shaped refractory products.

NOTE For shaped insulating refractory products, the bulk density and true porosity are determined in accordance with EN 1094-4.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 993-2, *Methods of test for dense shaped refractory products — Part 2: Determination of true density*

ISO 5022, *Shaped refractory products — Sampling and acceptance testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

bulk density

ρ_b

ratio of the mass of the dry material of a porous body to its bulk volume, expressed in grams per cubic centimetre or in kilograms per cubic metre

3.2

bulk volume

V_b

sum of the volumes of the solid material, the open pores and the closed pores in a porous body

Note 1 to entry: The roughness of the surface limits the accuracy of definition of the bulk volume and, in consequence, of the bulk density. Also, the concept of bulk density becomes less precise when the volume of the test piece diminishes below certain limits or when its texture (size of pores and grains) is too coarse.

3.3

true density

ρ_t

ratio of the mass of the solid material of a porous body to its true volume, expressed in grams per cubic centimetre or in kilograms per cubic metre

3.4

true volume

volume of the solid material in a porous body