INTERNATIONAL STANDARD

First edition 2012-07-01

Paints and varnishes — Lighting and procedure for visual assessments of coatings

Peintures et vernis — Éclairage et mode opératoire pour évaluations



Reference number ISO 13076:2012(E)



© ISO 2012

<text> All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

Case postale 56 • CH-1211 Geneva 20 . Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13076 was prepared by Technical Committee ISO/TC 35, Paints and varnishes, Subcommittee SC 9, nis Rockiew Ro General test methods for paints and varnishes.

© ISO 2012 - All rights reserved

this document is a preview demension of the document is a preview demension of the document oc

Paints and varnishes — Lighting and procedure for visual assessments of coatings

1 Scope

This International Standard specifies the lighting and procedure for the visual assessment of degraded areas, spots or other defects on or in coatings.

It is not applicable to the visual comparison of colour, which may be assessed using ISO 3668.

2 Principle

The panel is visually assessed under specified conditions of illumination for degraded areas, spots or other defects.

3 Apparatus

3.1 Fluorescent lamp, comprising a wide-angle light source with an aluminium-coated reflector positioned to reflect the light downwards (see Figure 1), a colour temperature of 6 500 K and a degree of colour rendering of 9 (corresponding to colour rendering class 1A, i.e. a colour rendering index, *R*_a, of 90 to 100).

NOTE This colour temperature and colour rendering give the light colour 965.

4 Procedure for visual assessment

4.1 General

Either natural or artificial daylight may be used for routine assessments. Precisely controlled artificial lighting shall be used for arbitration purposes, however, since the properties of natural daylight are not constant and evaluations in natural daylight can be influenced by the surroundings.

4.2 Assessment in natural daylight

Diffuse daylight, such as that which falls from a partly cloudy sky on a north-facing test panel (south-facing in the southern hemisphere), should preferably be used. The areas to be assessed, and the areas surrounding them, shall be uniformly illuminated with an illuminance which shall be not less than 2 000 lx. Direct sunlight shall be avoided.

4.3 Assessment under artificial lighting

Assess the coating under a fluorescent lamp as specified in 3.1. Hold the test panel at a distance from the lamp such that the illuminance at the surface of the coating is not less than 750 lx (see Figure 1).

The illuminance shall be measured after setting up the fluorescent lamp.

The panel being assessed may be inclined in any direction. Degraded areas and spots can best be identified when examined at the light/dark boundary produced by the lamp.

Assessments made for arbitration purposes shall always be carried out under artificial light.