

Superconductivity - Part 23: Residual resistance ratio measurement - Residual resistance ratio of Nb superconductors

This document is a preview generated by EVS

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN IEC 61788-23:2018 sisaldab Euroopa standardi EN IEC 61788-23:2018 ingliskeelset teksti.	This Estonian standard EVS-EN IEC 61788-23:2018 consists of the English text of the European standard EN IEC 61788-23:2018.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 05.10.2018.	Date of Availability of the European standard is 05.10.2018.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 17.220, 29.050

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:  
Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

ICS 17.220; 29.050

English Version

Superconductivity - Part 23: Residual resistance ratio  
measurement - Residual resistance ratio of Nb superconductors  
(IEC 61788-23:2018)

Supraconductivité - Partie 23: Mesurage du rapport de  
résistance résiduelle - Rapport de résistance résiduelle des  
supraconducteurs de Nb  
(IEC 61788-23:2018)

Supraleitfähigkeit - Teil 23: Messung des  
Restwiderstandsverhältnisses - Restwiderstandsverhältnis  
von Nb-Supraleitern  
(IEC 61788-23:2018)

This European Standard was approved by CENELEC on 2018-07-10. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization  
Comité Européen de Normalisation Electrotechnique  
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

## European foreword

The text of document 90/400/FDIS, future edition 1 of IEC 61788-23, prepared by IEC/TC 90 "Superconductivity" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN IEC 61788-23:2018.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2019-04-10
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2021-07-10

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

## Endorsement notice

The text of the International Standard IEC 61788-23:2018 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

- IEC 61788-4:2016 NOTE Harmonized as EN 61788-4:2016 (not modified)
- IEC 61788-10:2006 NOTE Harmonized as EN 61788-10:2006 (not modified)

## Annex ZA (normative)

### Normative references to international publications with their corresponding European publications

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 Where an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: [www.cenelec.eu](http://www.cenelec.eu).

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60050-815	-	International Electrotechnical Vocabulary -- Part 815: Superconductivity	--	-

## CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references .....	7
3 Terms and definitions .....	7
4 Principle.....	8
5 Measurement apparatus .....	9
5.1 Mandrel or base plate .....	9
5.2 Cryostat and support of mandrel or base plate .....	9
6 Specimen preparation.....	10
7 Data acquisition and analysis .....	11
7.1 Data acquisition hardware.....	11
7.2 Resistance ( $R_1$ ) at room temperature.....	11
7.3 Residual resistance ( $R_2$ ) just above the superconducting transition.....	11
7.4 Validation of the residual resistance measurement.....	13
7.5 Residual resistance ratio.....	13
8 Uncertainty of the test method.....	13
9 Test report.....	13
9.1 General.....	13
9.2 Test information.....	13
9.3 Specimen information .....	13
9.4 Test conditions .....	14
9.5 RRR value .....	14
Annex A (Informative) Additional information relating to the measurement of RRR.....	15
A.1 Considerations for specimens and apparatus.....	15
A.2 Considerations for specimen mounting orientation .....	16
A.3 Alternative methods for increasing temperature of specimen above superconducting transition temperature .....	16
A.3.1 General .....	16
A.3.2 Heater method.....	16
A.3.3 Controlled methods.....	16
A.4 Other test methods .....	16
A.4.1 General .....	16
A.4.2 Measurement of resistance versus time .....	17
A.4.3 Comparison of ice point and room temperature.....	17
A.4.4 Extrapolation of the resistance to 4,2 K .....	17
A.4.5 Use of magnetic field to suppress superconductivity at 4,2 K.....	18
A.4.6 AC techniques .....	18
Annex B (informative) Uncertainty considerations .....	19
B.1 Overview.....	19
B.2 Definitions.....	19
B.3 Consideration of the uncertainty concept .....	19
B.4 Uncertainty evaluation example for TC 90 standards.....	21

Annex C (informative) Uncertainty evaluation for resistance ratio measurement of Nb superconductors .....	23
C.1 Evaluation of uncertainty.....	23
C.1.1 Room temperature measurement uncertainty.....	23
C.1.2 Cryogenic measurement uncertainty.....	24
C.1.3 Estimation of uncertainty for typical experimental conditions.....	26
C.2 Round robin test summary .....	26
Bibliography.....	28
Figure 1 – Relationship between temperature and resistance near the superconducting transition.....	8
Figure A.1 – Determination of the value of $R_2$ from a resistance versus time plot .....	17
Figure C.1 – Graphical description of the uncertainty of regression related to the measurement of $R_2$ .....	25
Table B.1 – Output signals from two nominally identical extensometers .....	20
Table B.2 – Mean values of two output signals .....	20
Table B.3 – Experimental standard deviations of two output signals.....	20
Table B.4 – Standard uncertainties of two output signals .....	21
Table B.5 – Coefficient of variations of two output signals.....	21
Table C.1 – Uncertainty of measured parameters .....	26
Table C.2 – RRR values obtained by round robin test .....	27

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

## SUPERCONDUCTIVITY –

**Part 23: Residual resistance ratio measurement –  
Residual resistance ratio of Nb superconductors**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61788-23 has been prepared by IEC technical committee 90: Superconductivity.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
90/400/FDIS	90/403/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 61788 series, published under the general title *Superconductivity*, can be found on the IEC website.



The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

**IMPORTANT – The 'color inside' logo on the cover page of this publication indicates that it contains colors which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a color printer.**

This document is a preview generated by EVS

## INTRODUCTION

High-purity niobium is the chief material used to make superconducting radio-frequency cavities. Similar grades of niobium may be used in the manufacture of superconducting wire. Procurement of raw materials and quality assurance of delivered products often use the residual resistance ratio (RRR) to specify or assess the purity of a metal. RRR is defined for non-superconducting metals as the ratio of electrical resistance measured at room temperature (293 K) to the resistance measured for the same specimen at low temperature (~4,2 K). The low-temperature value is often called the residual resistance. Higher purity is associated with higher values of RRR.

Niobium presents special problems due to its transformation to a superconducting state at ~9 K, so DC electrical resistance is effectively zero below this temperature. The definition above would then yield an infinite value for RRR. This document describes a test method to determine the residual resistance value by using a plot of the resistance to temperature as the test specimen is gradually warmed through the superconducting transition in the absence of an applied magnetic field. This results in a determination of the residual resistance at just above superconducting transition, ~10 K, from which RRR is subsequently determined.

International standards also exist to determine the residual resistance ratio of superconducting wires. In contrast to superconducting wires, which are usually a composite of a superconducting material and a non-superconducting material and the RRR value is representative of only the non-superconducting component, here the entire specimen is composed of superconducting niobium. Frequently, niobium is procured as a sheet, bar, tube, or rod, and not as a wire. For such forms, test specimens will likely be a few millimeters in the dimensions transverse to electric current flow. This difference is significant when making electrical resistance measurements, since niobium samples will likely be much longer than that for the same length-to-diameter ratio as a wire, and higher electrical current may be required to produce sufficient voltage signals. Guidance for sample dimensions and electrical connections is provided in Annex A. Test apparatus should also take into consideration aspects such as the orientation of a test specimen relative to the liquid helium surface, accessibility through ports on common liquid helium dewars, design of current contacts, and minimization of thermal gradients over long specimen lengths. These aspects distinguish the present document from similar wire standards.

Other test methods have been used to determine RRR. Some methods use a measurement at a temperature other than 293 K for the high resistance value. Some methods use extrapolations at 4,2 K in the absence of an applied magnetic field for the low resistance value. Other methods use an applied magnetic field to suppress superconductivity at 4,2 K. A comparison between this document and some other test methods is presented in Annex A. It should be noted that systematic differences of up to 10 % are produced by these other methods, which is larger than the target uncertainty of this document. Care should therefore be taken to apply this document or the appropriate corrections listed in Annex A according to the test method used.

Whenever possible, this test method should be transferred to vendors and collaborators who also perform RRR measurements. To promote consistency, the results of inter-laboratory comparisons are described in Annex C.