

Railway applications - Railway rolling stock cables having special fire performance - Thin wall - Part 2: Single core cables

Railway applications - Railway rolling stock cables having special fire performance - Thin wall - Part 2: Single core cables

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 50306-2:2003 sisaldab Euroopa standardi EN 50306-2:2002 ingliskeelset teksti.	This Estonian standard EVS-EN 50306-2:2003 consists of the English text of the European standard EN 50306-2:2002.
Käesolev dokument on jõustatud 15.01.2003 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.	This document is endorsed on 15.01.2003 with the notification being published in the official publication of the Estonian national standardisation organisation.
Standard on kättesaadav Eesti standardiorganisatsioonist.	The standard is available from Estonian standardisation organisation.

Käsitlusala: EN 50306-2 specifies requirements for, and constructions and dimensions of, single core cables, rated 300 V to earth, of the following type: Unscreened (0,5 mm 2 to 2,5 mm 2 single core) All cables have stranded tinned copper conductors and thin wall thickness, halogen-free insulation. They are for use in railway rolling stock as fixed wiring, or wiring where limited flexing in operation is encountered. The requirements provide for a continuous operational life at 105 °C, and a maximum temperature for short-circuit conditions of 160 °C based on a duration of 5 seconds.	Scope: EN 50306-2 specifies requirements for, and constructions and dimensions of, single core cables, rated 300 V to earth, of the following type: Unscreened (0,5 mm 2 to 2,5 mm 2 single core) All cables have stranded tinned copper conductors and thin wall thickness, halogen-free insulation. They are for use in railway rolling stock as fixed wiring, or wiring where limited flexing in operation is encountered. The requirements provide for a continuous operational life at 105 °C, and a maximum temperature for short-circuit conditions of 160 °C based on a duration of 5 seconds.
------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------	------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

ICS 13.220.40, 45.060.01

Võtmesõnad: electric loco, electrically-operated, flame propagation, railroad vehicles, safety, safety requirements, single wire, specification (approval), specifications, surface spread of flame, testing, traffic vehicles, unscreened, wall thicknesses, voltage measurement

English version

**Railway applications -
Railway rolling stock cables having special fire performance -
Thin wall
Part 2: Single core cables**

Applications ferroviaires -
Câbles pour matériel roulant ferroviaire
ayant des performances particulières
de comportement au feu -
Isolation mince
Partie 2: Câbles monoconducteurs

Bahnanwendungen -
Kabel und Leitungen für
Schienenfahrzeuge mit verbessertem
Verhalten im Brandfall -
Reduzierte Isolierwanddicken
Teil 2: Einadrige Kabel und Leitungen

This European Standard was approved by CENELEC on 2002-06-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

Foreword

This European Standard was prepared by Working Group 12, Railway cables, of Technical Committee CENELEC TC 20, Electric cables, as part of the overall programme of work in CENELEC TC 9X, Electrical and electronic applications for railways.

The text of the draft was submitted to the Unique Acceptance Procedure and was approved by CENELEC as EN 50306-2 on 2002-06-01.

The following dates were fixed:

- latest date by which the EN has to be implemented
at national level by publication of an identical
national standard or by endorsement (dop) 2003-07-01
- latest date by which the national standards conflicting
with the EN have to be withdrawn (dow) 2008-07-01

Annexes designated “informative” are given for information only.
In this standard, annexes A and B are informative.

Contents

Introduction	4
1 Scope	4
2 Normative references.....	5
3 Single core cables	6
4 Tests.....	8
Annex A (informative) Guidance on selection of cables for type approval	16
Annex B (informative) Bibliography	16
Table 1 - Requirements for construction	8
Table 2 - Test requirements	10
Table 3 - Pliability test requirements.....	13
Table 4 - Schedule of tests.....	15

Introduction

EN 50306 covers a range of sheathed and unsheathed cables with thin wall thickness insulation, based on halogen-free materials, for use in railway rolling stock. It is divided into four parts:

Part 1: General requirements;

Part 2: Single core cables;

Part 3: Single core and multicore cables (pairs, triples and quads) screened and thin wall sheathed;

Part 4: Multicore and multipair cables standard wall sheathed.

Special test methods referred to in EN 50306 are given in EN 50305. A guide to use is given in EN 50355¹⁾.

The cables in EN 50306-2 are also required in other parts of this series of standards to build up cables with additional screening and sheathing and also in multicore and multipair combinations.

EN 50306-1, General requirements, contains a more extensive introduction to EN 50306 and should be read in conjunction with this European Standard.

1 Scope

EN 50306-2 specifies requirements for, and constructions and dimensions of, single core cables, rated 300 V to earth, of the following type:

Unscreened (0,5 mm² to 2,5 mm² single core)

All cables have stranded tinned copper conductors and thin wall thickness, halogen-free insulation. They are for use in railway rolling stock as fixed wiring, or wiring where limited flexing in operation is encountered. The requirements provide for a continuous operational life at 105 °C, and a maximum temperature for short-circuit conditions of 160 °C based on a duration of 5 seconds.

NOTE 1 Where these single core cables are used as components of sheathed cables, the temperature for continuous operational life depends upon the type of sheath system used. Sheath systems for either 90 °C for 105 °C are defined in other parts of EN 50306.

Under fire conditions the cables exhibit special performance characteristics in respect of maximum permissible flame propagation (flame spread) and maximum permissible emission of smoke and toxic gases. These requirements are specified to permit the cables to satisfy Hazard Levels 2, 3 or 4 of EN 45545-1¹⁾.

NOTE 2 Requirements for the emission of smoke and gases are not specified for cables used for Hazard Level 1 of EN 45545-1.

NOTE 3 EN 45545-1 is still under development and should be consulted.

EN 50306-2 should be used in conjunction with EN 50306-1, General requirements.

¹⁾ At draft stage.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of these references apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 10002-1	Tensile testing of metallic materials - Part 1: Test at ambient temperature
EN 45545-1 ²⁾	Railway applications - Fire protection on railway vehicles Part 1: General
EN 50265-2-1	Common test methods for cables under fire conditions - Test for resistance to vertical flame propagation for a single insulated conductor or cable - Part 2-1: Procedures - 1 kW pre-mixed flame
EN 50267-2-1	Common test methods for cables under fire conditions - Tests on gases evolved during combustion of materials from cables Part 2-1: Procedures - Determination of the amount of halogen acid gas
EN 50267-2-2	Common test methods for cables under fire conditions - Tests on gases evolved during combustion of materials from cables Part 2-2: Procedures - Determination of degree of acidity of gases for materials by measuring pH and conductivity
EN 50268-2	Common test methods for cables under fire conditions - Measurement of smoke density of cables burning under defined conditions Part 2: Procedure
EN 50305	Railway applications - Railway rolling stock cables having special fire performance - Test methods
EN 50306-1	Railway applications-Railway rolling stock cables having special fire performance - Thin wall - Part 1: General requirements
EN 50334	Marking by inscription for the identification of cores of electric cables
EN 60684-2	Flexible insulating sleeving - Part 2: Methods of test (IEC 60684-2)
EN 60811-1-4	Insulating and sheathing materials of electric and optical cables - Common test methods - Part 1-4: General application - Tests at low temperature (IEC 60811-1-4)
EN 60811-2-1	Insulating and sheathing materials of electric and optical cables - Common test methods - Part 2-1: Method specific to elastomeric compounds - Ozone resistance, hot set and mineral oil immersion tests (IEC 60811-2-1)

²⁾ At draft stage.