
**Metallic and other inorganic coatings —
Electrodeposited coatings of tin-cobalt
alloy**

*Revêtements métalliques et autres revêtements inorganiques — Dépôts
électrolytiques d'alliage étain-cobalt*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

This document is a preview generated by EVS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope.....	1
2 Normative references	1
3 Terms and definitions	2
4 Essential information to be supplied by the purchaser to the processor.....	2
5 Designation	3
5.1 General	3
5.2 Designation specification	3
5.3 Basis metal.....	3
5.4 Designation of heat treatment requirements.....	4
5.5 Examples	4
6 Requirements.....	4
6.1 Basis material	4
6.2 Appearance	5
6.3 Undercoats	5
6.4 Thickness	5
6.5 Adhesion	6
6.6 Quality-evaluation test of tin-cobalt alloy coatings	6
6.7 Stress-relief heat treatment prior to electroplating	7
6.8 Hydrogen-embrittlement-relief heat treatment after electroplating	7
7 Sampling	7
Annex A (normative) Methods of measuring the thickness of tin-cobalt alloy coatings	8
Bibliography.....	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 26945 was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*.

This second edition cancels and replaces the first edition (ISO 26945:2008), of which it constitutes a minor revision.

Introduction

Electrodeposited coating of tin-cobalt alloy is characterized by its bright surface which is similar to decorative chromium coating. Hardness and wear-resistance properties of tin-cobalt alloy coatings are not equivalent to those of chromium coatings, but are similar to those of tin-nickel alloy coatings (see ISO 2179). Thus, tin-cobalt coatings may be regarded, as far as surface lustre is concerned, as one of the possible alternatives to chromium coating. Due to its higher current efficiency (more than 70 %), tin-cobalt alloy coatings can be applied by rack-and-barrel plating processes to a wide range of complicated shapes and sizes, e.g. nuts, bolts, rivets, etc.

This document is a preview generated by EVS

Metallic and other inorganic coatings — Electrodeposited coatings of tin-cobalt alloy

WARNING — This International Standard may not be compliant with some countries' health and safety legislations and calls for the use of substances and/or procedures that may be injurious to health if adequate safety measures are not taken. This International Standard does not address any health hazards, safety or environmental matters and legislations associated with its use. It is the responsibility of the user of this International Standard to establish appropriate health, safety and environmentally acceptable practices and take suitable actions to comply with any national and international regulations. Compliance with this International Standard does not in itself confer immunity from legal obligations.

1 Scope

This International Standard specifies electrodeposited coatings of tin-cobalt alloy of approximate composition 75 % (mass fraction) to 80 % (mass fraction) tin, remainder cobalt, as a substitute for decorative chromium coatings of 0,1 μm to 0,3 μm thickness. Hardness and wear resistance properties of the coatings obtained are not equivalent to those of chromium coatings, but similar to those of tin-nickel alloy coatings.

Tin-cobalt alloy coatings can be applied by rack or barrel plating processes.

This International Standard does not specify requirements for the surface condition of the basis metal prior to electroplating.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1463, *Metallic and oxide coatings — Measurement of coating thickness — Microscopical method*

ISO 2064, *Metallic and other inorganic coatings — Definitions and conventions concerning the measurement of thickness*

ISO 2080, *Metallic and other inorganic coatings — Surface treatment, metallic and other inorganic coatings — Vocabulary*

ISO 2819, *Metallic coatings on metallic substrates — Electrodeposited and chemically deposited coatings — Review of methods available for testing adhesion*

ISO 3497, *Metallic coatings — Measurement of coating thickness — X-ray spectrometric methods*

ISO 4519, *Electrodeposited metallic coatings and related finishes — Sampling procedures for inspection by attributes*

ISO 4541, *Metallic and other non-organic coatings — Corrod-kote corrosion test (CORR test)*

ISO 9220, *Metallic coatings — Measurement of coating thickness — Scanning electron microscope method*

ISO 9587, *Metallic and other inorganic coatings — Pretreatment of iron or steel to reduce the risk of hydrogen embrittlement*

ISO 9588, *Metallic and other inorganic coatings — Post-coating treatments of iron or steel to reduce the risk of hydrogen embrittlement*

ISO 10289, *Methods for corrosion testing of metallic and other inorganic coatings on metallic substrates — Rating of test specimens and manufactured articles subjected to corrosion tests*

ISO 10587, *Metallic and other inorganic coatings — Test for residual embrittlement in both metallic-coated and uncoated externally-threaded articles and rods — Inclined wedge method*

ISO 15724, *Metallic and other inorganic coatings — Electrochemical measurement of diffusible hydrogen in steels — Barnacle electrode method*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 2064, ISO 2080, ISO 9587 and ISO 9588 apply.

4 Essential information to be supplied by the purchaser to the processor

When ordering articles to be processed in accordance with this International Standard, the purchaser shall provide the following information in writing, in, for example, the contract, purchase order, or on the engineering drawing:

- a) the number of this International Standard, ISO 26945, and article designation;
- b) the nature, condition and finish of the basis metal if they are likely to affect the serviceability and/or appearance of the coating (see 6.1);
- c) the significant surface of the article to be electroplated, indicated, for example, by drawings or by the provision of suitably marked samples;
- d) additional part of surfaces where the minimum thickness requirements apply;
- e) positions where unavoidable contact marks and other defects are acceptable (see 6.2);
- f) any requirements for special pretreatment (see 6.1);
- g) tensile strength of parts and requirements for heat treatment before and/or after electrodeposition (see 6.7 and 6.8);
- h) requirements, nature and thickness of undercoats (see 6.1 and 6.3);
- i) requirements for thickness, quality-evaluation test for controlling the quality and continuity of the coating and test method(s) to be used, and adhesion testing (see 6.4, 6.5 and 6.6);
- j) finish required, e.g. bright, dull or another type, accompanied by approved samples of the finish (see 6.2);
- k) the sampling plan to be adopted, and the acceptance levels (see Clause 7);
- l) any additional essential information.