

Pigments and extenders - Methods of dispersion and assessment of dispersibility in plastics - Part 6: Determination by film test (ISO 23900-6:2015)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 23900-6:2018 sisaldab Euroopa standardi EN ISO 23900-6:2018 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 23900-6:2018 consists of the English text of the European standard EN ISO 23900-6:2018.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 19.09.2018.	Date of Availability of the European standard is 19.09.2018.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 87.060.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Pigments and extenders - Methods of dispersion and
assessment of dispersibility in plastics - Part 6:
Determination by film test (ISO 23900-6:2015)**

Pigments et matières de charge - Méthodes de
dispersion et évaluation de l'aptitude à la dispersion
dans les plastiques - Partie 6: Détermination par essai
de film (ISO 23900-6:2015)

Pigmente und Füllstoffe - Dispergierv Verfahren und
Beurteilung der Dispergierbarkeit in Kunststoffen -
Teil 6: Bestimmung mit dem Folientest (ISO 23900-
6:2015)

This European Standard was approved by CEN on 12 August 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

The text of ISO 23900-6:2015 has been prepared by Technical Committee ISO/TC 256 "Pigments, dyestuffs and extenders" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 23900-6:2018 by Technical Committee CEN/TC 298 "Pigments and extenders" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2019, and conflicting national standards shall be withdrawn at the latest by March 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13900-6:2012.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 23900-6:2015 has been approved by CEN as EN ISO 23900-6:2018 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Terms and definitions	1
3 Principle	3
4 Materials	4
4.1 Concentrate.....	4
4.2 Basic test polymer.....	4
4.3 Test mixture.....	4
5 Apparatus	5
6 Preparation of test mixtures	5
6.1 General.....	5
6.2 Test mixture.....	5
7 Procedure	5
7.1 Calibration.....	5
7.2 Size ranges and resolution.....	6
7.3 Pre-conditioning.....	7
7.4 Test procedure.....	8
7.4.1 Production of the test polymer film.....	8
7.4.2 Production of the test mixture film.....	8
8 Evaluation	9
9 Test report	9
10 Precision	9
Bibliography	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 256, *Pigments, dyestuffs and extenders*.

ISO 23900 consists of the following parts, under the general title *Pigments and extenders — Methods of dispersion and assessment of dispersibility in plastics*:

- *Part 1: General introduction*
- *Part 2: Determination of colouristic properties and ease of dispersion in plasticized polyvinyl chloride by two-roll milling*
- *Part 3: Determination of colouristic properties and ease of dispersion of black and colour pigments in polyethylene by two-roll milling*
- *Part 4: Determination of colouristic properties and ease of dispersion of white pigments in polyethylene by two-roll milling*
- *Part 5: Determination by filter pressure value test*
- *Part 6: Determination by film test*

Pigments and extenders — Methods of dispersion and assessment of dispersibility in plastics —

Part 6: Determination by film test

1 Scope

This part of ISO 23900 specifies a method assessing the degree of dispersion of colorants¹⁾ and/or extenders in a thermoplastic polymer.

The method is suitable for testing colorants and/or extenders in the form of concentrates or compounds in all polymers used for extrusion processes.

NOTE Defects such as gels, black specks, holes in the test film are not in the scope of this part of ISO 23900.

The film test result determined according to this method is valid only for the equipment, conditions and test polymer being used. The use of test conditions differing from those specified might give different results. The preparation methods of concentrates or compounds are not specified in this part of ISO 23900. The results obtained for individual colorants and/or extenders are therefore comparable only when the same conditions of preparation for concentrates or compounds and a comparable detection system are used.

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

2.1

speck

defect caused by agglomerates, aggregates and primary particles of the colorant and/or extender, impurities of basic test polymer

2.2

primary particle of the colorant

smallest single unit detectable by physical methods

Note 1 to entry: Suitable physical methods are, for example, optical and electron microscopy.

2.3

aggregate

particle comprising strongly bonded or fused particles where the resulting external surface area may be significantly smaller than the sum of calculated surface areas of the individual components

Note 1 to entry: The forces holding an aggregate together are strong forces, for example, covalent bonds, or those resulting from sintering or complex physical entanglement.

Note 2 to entry: Aggregates are also termed secondary particles and the original source particles are termed primary particles.

[SOURCE: ISO/TS 27687:2008, 3.3]

1) For the definition of colorant see ISO 4618:2014, 2.60 colouring material.