
**Plain bearings — Metallic multilayer
plain bearings —**

Part 2:

**Destructive testing of bond for bearing
metal layer thicknesses greater than
or equal to 2 mm**

Paliers lisses — Paliers lisses métalliques multicouches —

*Partie 2: Détermination, par essai destructif, de l'adhérence du
matériau antifriction d'épaisseur supérieure ou égale à 2 mm*



This document is a preview generated by EVS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Principle	1
4 Test equipment	1
4.1 General.....	1
4.2 Testing apparatus.....	2
5 Specimen	2
5.1 General.....	2
5.2 Specimen machining sequence.....	4
6 Procedure	5
7 Evaluation	5
7.1 General.....	5
7.2 Designation.....	6
7.3 Test report.....	6
8 Application for quality control and process qualification	7
8.1 General.....	7
8.2 Quality control.....	7
8.3 Process qualification.....	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4386-2 was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 2, *Materials and lubricants, their properties, characteristics, test methods and testing conditions*.

This second edition cancels and replaces the first edition (ISO 4386-2:1982), which has been technically revised.

ISO 4386 consists of the following parts, under the general title *Plain bearings — Metallic multilayer plain bearings*:

- *Part 1: Non-destructive ultrasonic testing of bond of thickness greater than or equal to 0,5 mm*
- *Part 2: Destructive testing of bond for bearing metal layer thicknesses greater than or equal to 2 mm*
- *Part 3: Non-destructive penetrant testing*

Introduction

Long years of experience with bond tests led to an adaptation of this part of ISO 4386. The test apparatus has been modified, to reduce the negative local bending stress influence on the specimen. The geometry of the test specimen has been modified to avoid negative influence due to tolerances. A description of the specimen machining sequence has been added to get a more uniform specimen. A subclause on the application for quality control has been added.

Plain bearings — Metallic multilayer plain bearings —

Part 2:

Destructive testing of bond for bearing metal layer thicknesses greater than or equal to 2 mm

1 Scope

This part of ISO 4386 specifies a tensile test method for determination of the bond strength between the bearing metal and the backing. The test can be applied to multilayer plain bearings with bearing metals based on lead, tin, copper or aluminium. For tested layer thicknesses of ≥ 2 mm, a raw lining thickness of a minimum additional 1 mm is necessary.

The backings are from steel, cast steel or copper alloys. The bond strength test does not apply to bearings with cast iron backing.

The test applies to all thrust bearings and to journal bearings with an inner diameter of backing ≥ 90 mm.

The test can be used for comparative investigations into the influence on the bond strength of various processes and types of material. In addition, the test is suitable for production control and for process qualification of bearing production.

For non-destructive ultrasonic testing of the bond between bearing metal and backing for bearing metal layer thicknesses ≥ 2 mm, see ISO 4386-1.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4381, *Plain bearings — Tin casting alloys for multilayer plain bearings*

3 Principle

During the tensile testing carried out vertically to the bond surface, the bond strength R_{Ch} , in newtons per square millimetre, is the quotient of the maximum force, F_{max} , in newtons and the bond surface, A , in square millimetres, of the specimen (see Table 2).

NOTE The subscript “Ch” refers to the test method proposed by Chalmers.

$$R_{Ch} = \frac{F_{max}}{A} \quad (1)$$

4 Test equipment

4.1 General

A calibrated tensile testing machine shall be used with apparatus in accordance with Table 1.

By means of careful adjustment of the apparatus, it shall be ensured that the force is acting vertically to the bond surface in order to avoid incorrect measurements.