Common test methods for cables under fire conditions -Heat release and smoke production measurement on cables during flame spread test - Test apparatus, A Dreview development of the procedures, results



FESTI STANDARDI FESSÕNA

teate avaldamisel EVS Teatajas.

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 50399:2011 sisaldab Euroopa standardi EN 50399:2011 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 30.04.2011 käskkirjaga ja jõustub sellekohase

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 15.04.2011.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 50399:2011 consists of the English text of the European standard EN 50399:2011.

This standard is ratified with the order of Estonian Centre for Standardisation dated 30.04.2011 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 15.04.2011.

The standard is available from Estonian standardisation organisation.

ICS 13.220.40, 29.060.20

Standardite reprodutseerimis- ja levitamisõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega: Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation: Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: 605 5050; E-mail: info@evs.ee

EUROPEAN STANDARD

EN 50399

NORME EUROPÉENNE EUROPÄISCHE NORM

April 2011

ICS 13.220.40; 29.060.20

English version

Common test methods for cables under fire conditions Heat release and smoke production measurement on cables during flame spread test Test apparatus, procedures, results

Méthodes d'essai communes aux câbles soumis au feu -

Mesure de la chaleur et de la fumée dégagées par les câbles au cours de l'essai de propagation de la flamme -Appareillage d'essai, procédure et résultats Allgemeine Prüfverfahren für das Verhalten von Kabeln und isolierten Leitungen im Brandfall -Messung der Wärmefreisetzung und Raucherzeugung während der Prüfung der Flammenausbreitung -Prüfeinrichtung, Prüfverfahren und Prüfergebnis

This European Standard was approved by CENELEC on 2011-02-28. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization Comité Européen de Normalisation Electrotechnique Europäisches Komitee für Elektrotechnische Normung

Management Centre: Avenue Marnix 17, B - 1000 Brussels

Foreword

This European Standard was prepared by the Technical Committee CENELEC TC 20, Electric cables.

The text of the draft was submitted to the formal vote and was approved by CENELEC as EN 50399 on 2011-02-28.

The following dates were fixed:

latest date by which the EN has to be implemented at national level by publication of an identical national standard or by endorsement

(dop) 2012-02-28

latest date by which the national standards conflicting with the EN have to be withdrawn

Contents

Intro	oducti	on	5
1	Scop	e	7
2	Normative references		7
3	Term	rms and definitions	
4	Test apparatus		8
-	4.1	General	
	4.2	Air input	
	4.3	Hood	
	4.4	Exhaust duct	
	4.5	Instrumentation in the exhaust duct	
	4.6	Extracting ventilator	
	4.7	Smoke production measuring equipment	11
	4.8	Combustion gas analysis equipment	
5	Qualification of test apparatus		
	5.1	General	12
	5.2	Flow distribution measurements	12
	5.3	Sampling delay time measurement	13
	5.4	Commissioning calibrations	13
	5.5	Routine calibration	
6	Test procedure		
	6.1	Initial test conditions	14
	6.2	Test sample	14
	6.3	Sample conditioning	
	6.4	Determination of the number of test pieces	
	6.5	Mounting of the test sample	
	6.6	Exhaust volume flow	
	6.7	Ignition source	
	6.8	Flame application time	
	6.9	Testing operations	
	6.10	Observations and measurements during the test	
7	Determination of parameters derived from the test		
	7.1	Calculation of HRR and SPR parameters	
	7.2	Determination of extent of flame spread (FS)	
8	Test report		
	8.1	General	
	8.2	Contents	
Ann	ex A (normative) Calculation of heat release	
	A.1	Volume flow	31
	A.2	Generated heat effect	31
	A.3	Calculation of the mole fraction of water vapour in the air	33
Ann	Annex B (normative) Smoke production		
Ann	ex C (informative) Additional information on Revnolds number in Figure 5	35

Introduction

EN 50399 specifies the test apparatus and test procedures for the assessment of the reaction to fire performance of cables to enable classification under the Construction Products Directive [1] to be achieved.

The test method describes an intermediate scale fire test of multiple cables mounted on a vertical cable ladder and is carried out with a specified ignition source to evaluate the burning behaviour of such cables and enable a direct declaration of performance. The test provides data for the early stages of a cable fire from ignition of cables. It addresses the hazard of propagation of flames along the cable, the potential, by the measurement of the heat release rate, for the fire to affect areas adjacent to the compartment of origin, and the hazard, by the measurement of production of light obstructing smoke, of reduced visibility in the room of origin and surrounding enclosures.

The following parameters may be determined under defined conditions during the test:

- a) flame spread;
- b) heat release rate;
- c) total heat release;
- d) smoke production rate;
- e) total smoke production;
- f) fire growth rate index;
- g) occurrence of flaming droplets/particles .

The apparatus is based upon that of EN 60332-3-10 but with additional instrumentation to measure heat release and smoke production during the test. It has been demonstrated [3] that the utilisation of these additional measurement techniques, proven for other standard tests, e.g. for building products, are appropriate for assessing the reaction to fire performance of electric cables. These techniques include heat release and smoke production measurements. Compared with existing test methods described in EN 60332-3-10, they enable a more comprehensive assessment system, which is both more precise and sensitive, and enables a wider range of fire performance levels.

Care should be exercised in relating the parameters measured to different safety levels in actual cable installations as the actual installed configuration of the cables may be a major determinant in the level of flame spread, heat release and smoke production occurring in an actual fire. These parameters depend upon a number of features, such as

- the volume of combustible material exposed to the fire and to any flaming or heat which may be produced by the combustion of the cables;
- b) the geometrical configuration of the cables and their relationship to an enclosure;
- c) the temperature at which it is possible to ignite the gases emitted from the cables;
- the quantity of combustible gas released from the cables for a given temperature rise;
- e) the volume of air passing through the cable installation;
- f) the construction of the cable, e.g. armoured or unarmoured, multi or single core.

All of the foregoing assumes that the cables are able to be ignited when involved in an external fire.

The conditions of cable mounting, including volume of material exposed and geometrical configuration of the cables on the test ladder, and volume of airflow through the chamber have been chosen to be in accordance with that required by the Commission Decision 2006/751/EC [2]. CENELEC has not been involved in the definition of these parameters. These standardised conditions provide the basis for classification but do not necessarily correspond to conditions found in a particular cable installation.

NOTE Further information on the use of standardised conditions for classification with respect to product end-use application may be found in European Commission Guidance Paper G [4].

EN 50399 gives details of the apparatus to be used in conjunction with the equipment described in to c procedu. EN 60332-3-10 in order to carry out the measurement of heat release and smoke production during the test. Details of the test procedures are also given.

1 Scope

EN 50399 specifies the apparatus and methods of test for the assessment of vertical flame spread, heat release, smoke production and occurrence of flaming droplets/particles of vertically-mounted bunched wires or cables, electrical or optical, under defined conditions.

NOTE For the purpose of this standard the term "electric wire or cable" covers all insulated metallic conductor cables used for the conveyance of energy or signals.

EN 50399 details the apparatus and the arrangement and calibration of the instrumentation to be installed in order to measure the heat release and the smoke production during the test. The combustion gases are collected in a hood above the test chamber and conveyed through an exhaust system, which allows the measurement of heat release rate and smoke production. Test procedures to be used for type approval testing for classification of cables in Euroclasses $B1_{ca}$, $B2_{ca}$, C_{ca} and D_{ca} are given. Cable installation on the test ladder and the volume of air passing through the chamber are in accordance with the Commission Decision 2006/751/EC [2] which is reflected in the requirements of this standard.

The apparatus described in this standard shall be used in conjunction with that described in EN 60332-3-10.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 60332-3-10, Tests on electric and optical fibre cables under fire conditions – Part 3-10: Test for vertical flame spread of vertically-mounted bunched wires or cables – Apparatus (IEC 60332-3-10)

EN 60584-1, Thermocouples – Part 1: Reference tables (IEC 60584-1)

EN ISO 13943:2010, -Fire safety - Vocabulary (ISO 13943:2008)

ISO 3966, Measurement of fluid flow in closed conduits – Velocity area method using Pitot static tubes

3 Terms and definitions

For the purpose of this document, the terms and definitions given in EN ISO 13943:2010 and the following apply.

3.1

heat release rate

HRR

thermal energy released per unit time by an item during combustion under specified conditions

3.2

total heat release

THR

integrated value of the heat release rate over a defined period

3.3

smoke production rate

SPR

smoke production per unit time