
**Rubber, vulcanized or
thermoplastic — Determination of
rebound resilience**

*Caoutchouc vulcanisé ou thermoplastique — Détermination de la
résilience de rebondissement*



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Pendulum method	2
5.1 Apparatus	2
5.1.1 General	2
5.1.2 Oscillatory device	3
5.1.3 System for following the motion of the hammer	3
5.1.4 Test piece holder	3
5.1.5 Temperature control	4
5.1.6 Adjustment of oscillatory device	5
5.2 Test pieces	6
5.2.1 Preparation	6
5.2.2 Dimensions	7
5.2.3 Measurement of dimensions	7
5.2.4 Number of test pieces	7
5.2.5 Time-interval between forming and testing	7
5.2.6 Conditioning	7
5.3 Temperature of test	7
5.4 Procedure	7
5.4.1 Thermal conditioning and mounting of test piece	7
5.4.2 Mechanical conditioning of test piece	8
5.4.3 Measurement of rebound resilience	8
5.4.4 Calculation and expression of results	8
5.5 Precision	8
5.6 Test report	8
6 Tripsometer method	9
6.1 Apparatus	9
6.1.1 General	9
6.1.2 Pendulum	10
6.1.3 System for following the motion of the disc	10
6.1.4 Test piece holder	11
6.1.5 Temperature control	12
6.1.6 Adjustment of oscillatory device	13
6.2 Test pieces	15
6.2.1 Preparation	15
6.2.2 Dimensions	15
6.2.3 Measurement of dimensions	15
6.2.4 Number of test pieces	15
6.2.5 Time-interval between forming and testing	15
6.2.6 Conditioning	15
6.3 Temperature of test	16
6.4 Procedure	16
6.4.1 Thermal conditioning and mounting of test piece	16
6.4.2 Mechanical conditioning of test piece	16
6.4.3 Measurement	16
6.4.4 Calculation and expression of results	16
6.5 Precision	17
6.6 Test report	17

Annex A (informative) Use of non-standard test pieces	18
Annex B (informative) Apparatus designs	21
Annex C (informative) Mounting system for the disc of the tripsometer	22
Annex D (informative) Precision	24
Annex E (informative) Calculation method for the tripsometer's impact velocity	28
Bibliography	31

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This fourth edition cancels and replaces the third edition (ISO 4662:2009), which has been technically revised to add the calculation of the impact velocity for tripsometer method ([Annex E](#)). It also incorporates the Technical Corrigendum ISO 4662:2009/Cor.1:2010.

Introduction

When rubber is deformed, an energy input is involved; part of which is returned when the rubber returns to its original shape. That part of the energy which is not returned as mechanical energy is dissipated as heat in the rubber.

The ratio of the energy returned to the energy applied is termed the resilience. When the deformation is an indentation due to a single impact, this ratio is termed the rebound resilience.

The value of the rebound resilience for a given material is not a fixed quantity, but varies with temperature, strain distribution (determined by the type of indenter and test piece and by their dimensions), strain rate (determined by the velocity of the indenter), strain energy (determined by the mass and velocity of the indenter) and strain history. Strain history is particularly important in the case of filler-loaded polymers, where the stress-softening effect necessitates a mechanical conditioning.

This variation of resilience with conditions is an inherent property of polymers, which can therefore only be fully evaluated if tests are carried out over a wide range of conditions. The factors described can have a different quantitative influence on resilience. While temperature can critically affect resilience near transition regions of the material tested, factors connected with time and amplitude of indentation have only moderate effects, and fairly wide tolerances may be admissible for them.

Ideally, rebound resilience should be measured on a test piece the back surface of which is bonded to a rigid support in order to avoid friction losses due to slippage during the impact. Since the use of bonded test pieces is impractical in many applications, unbonded test pieces are used. Frictional losses are avoided by secure clamping of the test piece.

To approach these ideal conditions in a practical apparatus, limitations are put upon the hardness (see ISO 48) of the rubber that can be tested: on the hard side to avoid unusual requirements of rigidity in the apparatus; on the soft side to avoid difficulties in clamping.

If a defined set of mechanical conditions and an appropriate apparatus are selected, a standard value of rebound resilience at any temperature can be obtained with a satisfactory degree of reproducibility.

Rubber, vulcanized or thermoplastic — Determination of rebound resilience

WARNING 1 — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

WARNING 2 — Certain procedures specified in this document might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This document specifies two methods for determining the rebound resilience of rubber the hardness of which lies between 30 IRHD and 85 IRHD. They are the pendulum method and the tripsometer method.

With the pendulum method, a mass with a spherical end impacts a flat test piece, firmly held but free to bulge. The kinetic energy of the impacting mass is measured immediately before and after impact.

With the tripsometer method, a flat test piece is impacted by a hemisphere mounted on the periphery of a disc which is supported on an axle and caused to rotate by an off-axis mass. The kinetic energy of the impacting mass is measured immediately before and after impact.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

rebound resilience

ratio between the returned and the applied energy of a moving mass which impacts a test piece

Note 1 to entry: It is usually expressed as a percentage.