

METALLIVALU. TEMPERMALMID

Founding - Malleable cast irons

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN 1562:2019 sisaldab Euroopa standardi EN 1562:2019 ingliskeelset teksti.	This Estonian standard EVS-EN 1562:2019 consists of the English text of the European standard EN 1562:2019.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 20.03.2019.	Date of Availability of the European standard is 20.03.2019.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 77.080.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

## Founding - Malleable cast irons

Fonderie - Fontes malléables

Gießereiwesen - Temperguss

This European Standard was approved by CEN on 16 February 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

<b>Contents</b>	<b>Page</b>
<b>European foreword</b> .....	<b>3</b>
<b>Introduction</b> .....	<b>4</b>
<b>1 Scope</b> .....	<b>5</b>
<b>2 Normative references</b> .....	<b>5</b>
<b>3 Terms and definitions</b> .....	<b>5</b>
<b>4 Designation</b> .....	<b>6</b>
<b>5 Order information</b> .....	<b>6</b>
<b>6 Manufacture</b> .....	<b>7</b>
<b>7 Requirements</b> .....	<b>7</b>
7.1 General.....	7
7.2 Tensile strength and elongation.....	7
7.3 0,2 % Proof strength.....	7
7.4 Brinell hardness.....	7
7.5 Impact energy.....	7
<b>8 Samples</b> .....	<b>11</b>
8.1 General.....	11
8.2 Cast samples.....	11
8.2.1 Size of test pieces.....	11
8.2.2 Frequency and number of tests.....	12
8.2.3 Separately cast samples.....	13
8.2.4 Side-by-side cast samples.....	13
<b>9 Test methods</b> .....	<b>13</b>
9.1 Tensile test.....	13
9.2 0,2 % proof strength.....	13
9.3 Brinell hardness.....	13
9.4 Impact test.....	13
<b>10 Retests</b> .....	<b>14</b>
10.1 Need for retests.....	14
10.2 Test validity.....	14
10.3 Non-conforming test results.....	15
10.4 Heat treatment of samples and castings.....	15
<b>11 Inspection documentation</b> .....	<b>15</b>
<b>Annex A (informative) Comparison of malleable cast iron material designations according EN 1560 and ISO/TR 15931 [1], [6]</b> .....	<b>16</b>
<b>Annex B (informative) Un-notched impact test</b> .....	<b>17</b>
<b>Annex C (informative) Significant technical changes between this European standard and the previous edition</b> .....	<b>19</b>
<b>Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of Directive 2014/68/EU aimed to be covered</b> .....	<b>20</b>
<b>Bibliography</b> .....	<b>21</b>

## European foreword

This document (EN 1562:2019) has been prepared by Technical Committee CEN/TC 190 “Foundry technology”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2019 and conflicting national standards shall be withdrawn at the latest by September 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1562:2012.

Within its programme of work, Technical Committee CEN/TC 190 requested CEN/TC 190/WG 6 “Malleable cast iron” to revise EN 1562:2012.

This document has been prepared under a standardization request given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

Annex C provides details of significant technical changes between this European Standard and the previous edition.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Introduction

This document classifies malleable cast irons into two groups. The first group is concerned with decarburized irons referred to as whiteheart malleable cast iron. The second group is non-decarburized irons referred to as blackheart malleable cast iron. Both groups, except completely decarburized whiteheart malleable cast iron, contain free carbon as graphite, called temper carbon. Both groups have grades with structures that can range from ferrite to pearlite and/or other transformation products of austenite.

Materials are designated in terms of tensile strength and percentage elongation.

Weldability is an important property of malleable cast irons.

Malleable cast irons have good impact resistance and ductility at low temperatures.

In this document, a designation system by number, as established in EN 1560 [1], is given.

NOTE This designation system by number is based on the principles and the structure as set out in EN 10027-2 [2] and so corresponds with the European numbering system for steel and other materials.

Some malleable cast iron grades can be used for pressure equipment.

The permitted material grades of malleable cast iron for pressure applications and the conditions for their use are given in specific product or application standards.

For the design of pressure equipment, specific design rules apply.

Annex ZA gives information relating to the conformance of permitted malleable cast iron grades to the Pressure Equipment Directive 2014/68/EU.

## 1 Scope

This document defines grades and the corresponding requirements for malleable cast irons.

This document specifies five grades of whiteheart malleable cast iron and nine grades of blackheart malleable cast iron, based on mechanical properties measured on cast samples (which are test pieces).

This document specifies Brinell hardness values determined only when these values are requested by the purchaser.

This document does not cover technical delivery conditions for malleable cast iron castings. Reference can be made to EN 1559-1 [3] and EN 1559-3 [4].

This document does not cover chemical composition, except phosphorus (see Clause 6).

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 764-5:2014, *Pressure equipment — Part 5: Inspection documentation of metallic materials and compliance with the material specification*

EN 10204:2004, *Metallic products — Types of inspection documents*

EN ISO 148-1:2016, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1:2016)*

EN ISO 6506-1:2014, *Metallic materials — Brinell hardness test — Part 1: Test method (ISO 6506-1:2014)*

EN ISO 6892-1:2016, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2016)*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

### 3.1

#### **malleable cast iron**

cast material, mainly iron and carbon based, which solidifies in the as-cast condition with a graphite-free (white) structure and achieves its final properties after a heat treatment

### 3.2

#### **whiteheart malleable cast iron**

cast material, mainly iron and carbon based, which is cast white and then given a heat treatment in a decarburizing atmosphere to produce a material which is partially or entirely decarburized

Note 1 to entry: Any remaining graphite is in the form of temper carbon.