
Specifications for compostable plastics

Spécifications pour les plastiques compostables



This document is a preview generated by EVS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Principle	3
5 Basic requirements	3
6 Detailed requirements	4
6.1 General	4
6.2 Disintegration during composting	4
6.3 Ultimate aerobic biodegradation	4
6.4 No adverse effects on ability of compost to support plant growth and compliance with regional and/or national regulations	5
7 Marking and labelling	5
8 Test report	6
Annex A (informative) Examples of maximum concentrations of regulated metals and other toxic substances	7
Bibliography	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17088 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

This second edition cancels and replaces the first edition (ISO 17088:2008), of which it constitutes a minor revision to clarify the wording of the second paragraph in Subclause 6.3.1.

Introduction

Management of solid wastes is a problem of growing interest around the world. Cities, towns and countries are attempting to divert more materials from disposal (landfills and incineration without energy recovery) by performing different recovery options in order to transform waste into usable products. Plastics recovery technologies include material recovery (mechanical recycling, chemical or feedstock recycling, and biological or organic recycling) and the recovery of energy in the form of usable heat under controlled combustion conditions.

As interest in composting (biological or organic recycling) grows, it will be necessary to identify correctly plastics, and products made from plastics, which will disintegrate and biodegrade satisfactorily under composting conditions and will not leave any persistent or toxic residues.

Specifications for compostable plastics

WARNING — Sewage, activated sludge, soil and compost might contain potentially pathogenic organisms. Therefore appropriate precautions should be taken when handling them. Toxic test compounds and those whose properties are unknown should be handled with care. The handling of these materials in the context of the application of this International Standard might be further controlled by national and/or regional legislation.

1 Scope

This International Standard specifies procedures and requirements for the identification and labelling of plastics, and products made from plastics, that are suitable for recovery through aerobic composting. The four following aspects are addressed:

- a) biodegradation;
- b) disintegration during composting;
- c) negative effects on the composting process and facility;
- d) negative effects on the quality of the resulting compost, including the presence of high levels of regulated metals and other harmful components.

This specification is intended to establish the requirements for the labelling of plastic products and materials, including packaging made from plastics, as “compostable” or “compostable in municipal and industrial composting facilities” or “biodegradable during composting” (for the purposes of this International Standard, these three expressions are considered to be equivalent). The labelling will, in addition, have to conform to all international, regional, national or local regulations (e.g. European Directive 94/62/EC).

NOTE The recovery of compostable plastics through composting can be carried out under the conditions found in well-managed composting plants, where the temperature, water content, aerobic conditions, carbon/nitrogen ratio and processing conditions are optimized. Such conditions are generally obtained in industrial and municipal composting plants. Under these conditions, compostable plastics will disintegrate and biodegrade at rates comparable to yard trimmings, kraft paper bags and food scraps.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies

ISO 472, *Plastics — Vocabulary*

ISO 14855-1, *Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions — Method by analysis of evolved carbon dioxide — Part 1: General method*

ISO 14855-2, *Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions — Method by analysis of evolved carbon dioxide — Part 2: Gravimetric measurement of carbon dioxide evolved in a laboratory-scale test*

ISO 16929, *Plastics — Determination of the degree of disintegration of plastic materials under defined composting conditions in a pilot-scale test*

ISO 20200, *Plastics — Determination of the degree of disintegration of plastic materials under simulated composting conditions in a laboratory-scale test*

EN 13432:2000, *Packaging — Requirements for packaging recoverable through composting and biodegradation — Test scheme and evaluation criteria for the final acceptance of packaging*

ASTM D5338, *Standard Test Method for Determining Aerobic Biodegradation of Plastic Materials Under Controlled Composting Conditions, Including Thermophilic Temperatures*

ASTM D6400, *Standard Specification for Compostable Plastics*

OECD Guidelines for the Testing of Chemicals — Guideline 208: *Terrestrial Plants, Growth Test*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472 and the following apply.

3.1

biodegradable during composting

synonymous with “compostable” (see definition of “compostable plastic”)

3.2

catalyst

substance, used in small proportion, that augments the rate of a chemical reaction and, in theory, remains unchanged chemically at the end of the reaction

3.3

compost

organic soil conditioner obtained by biodegradation of a mixture consisting principally of vegetable residues, occasionally with other organic material and having a limited mineral content

3.4

compostable plastic

plastic that undergoes degradation by biological processes during composting to yield CO₂, water, inorganic compounds and biomass at a rate consistent with other known compostable materials and leave no visible, distinguishable or toxic residue

3.5

composting

aerobic process designed to produce compost

3.6

disintegration

physical breakdown of a material into very small fragments

3.7

filler

relatively inert solid material added to a plastic to modify its strength, permanence, working properties or other qualities, or to lower costs

3.8

theoretical amount of evolved carbon dioxide

ThCO₂

maximum theoretical amount of carbon dioxide evolved after completely oxidizing a chemical compound, calculated from the molecular formula and expressed as milligrams of carbon dioxide evolved per milligram or gram of test compound

3.9

total dry solids

amount of solids obtained by taking a known volume of test material or compost and drying at about 105 °C to constant mass