
Reaction to fire tests — Spread of flame —

Part 2:

Lateral spread on building products in vertical
configuration

Essais de réaction au feu — Propagation du feu —

*Partie 2: Propagation latérale sur les produits de bâtiment en position
verticale*



Contents

Page

1	Scope.....	1
2	Normative reference.....	1
3	Definitions.....	1
4	Principles of the test.....	2
5	Suitability of a product for testing.....	2
6	Test specimens	3
7	Test apparatus	5
8	Test environment	9
9	Additional equipment and instrumentation.....	9
10	Setting-up and calibration procedure	12
11	Test procedure	16
12	Expression of fire performance of a product.....	17
13	Test report	17

Annexes

A	Safety precautions.....	18
B	Specimen construction.....	19
C	Calibration of the working heat flux meter	20
D	Guidelines for reporting and follow-up of results of fire test procedures.....	21
E	Variability of test results	22
F	Bibliography	23

© ISO 1996

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 5658-2 was prepared by Technical Committee ISO/TC 92, *Fire safety*, Subcommittee SC 1, *Reaction to fire*.

ISO 5658 consists of the following parts, under the general title *Reaction to fire tests — Spread of flame*:

- *Part 1: Guidance on flame spread*
(Technical Report)
- *Part 2: Lateral spread on building products in vertical configuration*
- *Part 3: Lateral ignition and flame spread of building products in vertical configuration (LIFT) method*
(Technical Report)
- *Part 4: Intermediate scale spread of flame*

Annex A forms an integral part of this part of ISO 5658. Annexes B to F are for information only.

Introduction

This part of ISO 5658 is based on the method of the International Maritime Organization (IMO) published as IMO Resolution A.653(16)^[5], and has been developed as an International Standard in order to allow its wider use. The major differences between ISO 5658-2 and the IMO test are that ISO 5658-2 is limited in scope to testing the spread of flame over vertical specimens and does not include the stack for estimating heat release rate.

ISO/TR 5658-1 describes the development of standard tests for flame spread and explains the theory of flame spread for various orientations. The relationship, both theoretical and mathematical, which exists between ISO 5658-2 and ISO/TR 5658-3 is also explained.

ISO 5658-2 provides a simple method by which lateral surface spread of flame on a vertical specimen can be determined for comparative purposes. This method is particularly useful for research, development and quality control purposes.

ISO/TR 5658-3 provides a more scientific method by which the ignitability and spread of flame parameters of building products can be determined. The data derived from this test are suitable for use in fire growth (mathematical) models. The same test apparatus is used for the procedures specified in this part of ISO 5658 and ISO/TR 5658-3.

Fire is a complex phenomenon: its behaviour and its effects depend upon a number of interrelated factors. The behaviour of materials and products depends upon the characteristics of the fire, the method of use of the materials and the environment to which they are exposed. The methodology of "reaction to fire" tests is explained in ISO/TR 3814^[1].

A test such as is specified in this part of ISO 5658 deals only with a simple representation of a particular aspect of the potential fire situation typified by a radiant heat source and flame; it cannot alone provide any direct guidance on behaviour or safety in fire.

A precision statement based on an interlaboratory trial using this test method is given in annex E.

This test procedure does not rely on the use of asbestos-based materials.

The attention of all users of the test is drawn to the following caution.

CAUTION — So that suitable precautions may be taken to safeguard health, the attention of all concerned in fire tests is drawn to the possibility that toxic or harmful gases may be evolved during exposure of test specimens. The advice on safety given in annex A should also be noted.

Reaction to fire tests — Spread of flame —

Part 2:

Lateral spread on building products in vertical configuration

1 Scope

1.1 This part of ISO 5658 specifies a method of test for measuring the lateral spread of flame along the surface of a specimen of a product orientated in the vertical position. It provides data suitable for comparing the performance of essentially flat materials, composites or assemblies, which are used primarily as the exposed surfaces of walls.

1.2 This part of ISO 5658 is applicable to the measurement and description of the properties of materials, products or assemblies in response to radiative heat in the presence of a pilot flame under controlled laboratory conditions. It should not be used alone to describe or appraise the fire hazard or fire risk of materials, products or assemblies under actual fire conditions.

2 Normative reference

The following standard contains provisions which, through reference in this text, constitute provisions of this part of ISO 5658. At the time of publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this part of ISO 5658 are encouraged to investigate the possibility of applying the most recent edition of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO/IEC Guide 52:1990, *Glossary of fire terms and definitions*.

3 Definitions

For the purposes of this part of ISO 5658, the definitions given in ISO/IEC Guide 52 and the following definitions apply.

3.1 assembly: Fabrication of materials and/or composites, for example sandwich panels.

NOTE 1 The assembly may include an air gap.

3.2 average heat for sustained burning: Average of the values of heat for sustained burning, expressed in megajoules per square metre (MJ/m²), measured at a number of specified positions.

3.3 backing board: Non-combustible board with the same dimensions as the specimen, used in every test to back the specimen (see 9.7).

3.4 composite: Combination of materials which are generally recognized in building construction as discrete entities, for example coated or laminated materials.

3.5 critical heat flux at extinguishment: Incident heat flux, expressed in kilowatts per square metre (kW/m²), at the surface of a specimen at the point along its horizontal centreline where the flame ceases to advance and may subsequently go out. The heat flux value reported is based on interpolations of measurements with a non-combustible calibration board.

3.6 exposed surface: That surface of the specimen subjected to the heating conditions of the test.

3.7 flame front: Furthest extent of travel of a sustained flame centrally along the length of the test specimen.

3.8 flashing: Existence of flame on or over the surface of the specimen for periods of less than 1 s.