
**Petroleum, petrochemical and natural
gas industries — Composite repairs
for pipework — Qualification and
design, installation, testing and
inspection**

*Industries du pétrole, de la pétrochimie et du gaz naturel —
Réparations en matériau composite pour canalisations — Conformité
aux exigences de performance et conception, installation, essai et
inspection*



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

| | |
|---|-----------|
| Foreword | v |
| Introduction | vi |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions | 2 |
| 4 Symbols and abbreviated terms | 6 |
| 4.1 Symbols | 6 |
| 4.2 Abbreviated terms | 9 |
| 5 Applications | 9 |
| 6 Summary of key issues | 11 |
| 7 Qualification and design | 13 |
| 7.1 Repair feasibility assessment | 13 |
| 7.2 Repair class | 14 |
| 7.3 Repair design lifetime | 14 |
| 7.4 Required data | 15 |
| 7.4.1 Background | 15 |
| 7.4.2 Original equipment design data | 15 |
| 7.4.3 Maintenance and operational histories | 15 |
| 7.4.4 Service condition data | 15 |
| 7.4.5 Repair system qualification data | 16 |
| 7.5 Design methodology | 17 |
| 7.5.1 Overview | 17 |
| 7.5.2 Environmental compatibility | 19 |
| 7.5.3 Design temperature effects | 19 |
| 7.5.4 Design based on substrate load sharing (defect type A) | 21 |
| 7.5.5 Design based on repair laminate allowable strains (defect type A) | 23 |
| 7.5.6 Design based on repair-allowable stresses determined by performance testing (defect type A) | 24 |
| 7.5.7 Design of repairs for through-wall defects (defect type B) | 25 |
| 7.5.8 Axial extent of repair | 28 |
| 7.5.9 Optional design considerations | 30 |
| 7.5.10 Dent and/or gouge type defects | 34 |
| 7.5.11 Fretting type defects | 34 |
| 7.5.12 Delamination or blister type defects | 34 |
| 7.5.13 Repair of other components | 35 |
| 7.5.14 Design output | 38 |
| 7.6 Re-qualification of the repair system | 38 |
| 7.6.1 Overview | 38 |
| 7.6.2 For type A defect repairs | 38 |
| 7.6.3 For type B defect repairs | 38 |
| 8 Installation | 39 |
| 8.1 Storage conditions | 39 |
| 8.2 Documentation prior to repair application | 39 |
| 8.2.1 Method statement | 39 |
| 8.2.2 Work pack | 39 |
| 8.3 Installer qualifications | 40 |
| 8.4 Installation procedure | 40 |
| 8.5 Repair completion documentation | 41 |
| 8.6 Live repairs | 43 |
| 8.7 Repair of clamps, piping components, tanks, or vessels | 43 |
| 8.8 Environmental considerations | 43 |

| | | |
|------------------------------|--|-----------|
| 9 | Testing and inspection | 43 |
| 9.1 | General | 43 |
| 9.2 | Allowable defects for the repair system | 44 |
| 9.3 | Repair of defects within the repair system | 47 |
| 9.4 | Inspection methods | 48 |
| 9.5 | Repair system maintenance and remedial options | 48 |
| 9.5.1 | Overview | 48 |
| 9.5.2 | Condition of the repair - visual inspection | 48 |
| 9.5.3 | Condition of the pipe substrate | 49 |
| 9.5.4 | Remedial options | 49 |
| 9.5.5 | Extension (revalidation) of repair design lifetime | 49 |
| 9.5.6 | Future modifications | 50 |
| 10 | System testing | 50 |
| 11 | Decommissioning | 51 |
| Annex A (normative) | Design data sheet | 52 |
| Annex B (normative) | Qualification data | 55 |
| Annex C (normative) | Short-term pipe spool survival test | 59 |
| Annex D (normative) | Measurement of γ_{LCL} for through-wall defect calculation | 61 |
| Annex E (normative) | Measurement of performance test data | 64 |
| Annex F (normative) | Measurement of impact performance | 67 |
| Annex G (normative) | Measurement of the degradation factor | 68 |
| Annex H (informative) | Axial extent of repair look-up table | 70 |
| Annex I (normative) | Installer qualification | 72 |
| Annex J (informative) | Installation requirements and guidance | 75 |
| Annex K (informative) | Design considerations | 77 |
| Annex L (informative) | Management of the integrity of composite repair systems to pipework and vessels | 82 |
| Bibliography | | 86 |

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 6, *Processing equipment and systems*.

This second edition cancels and replaces the first edition (ISO 24817:2015), which has been technically revised.

This corrected version of ISO 24817:2017 incorporates the following correction:

- in [7.5.7](#), [Formula \(15\)](#), “D4” has been replaced by “D⁴”.

Introduction

The objective of this document is to ensure that pipework, pipelines, tanks and vessels repaired using composite systems that are qualified, designed, installed and inspected using this document will meet the specified performance requirements. Repair systems are designed for use within the petroleum, petrochemical and natural gas industries, and also within utility service applications. The main users of this document will be plant and equipment owners of the pipework and vessels, design contractors, suppliers contracted to provide the repair system, certifying authorities, installation, maintenance and inspection contractors.

Petroleum, petrochemical and natural gas industries — Composite repairs for pipework — Qualification and design, installation, testing and inspection

1 Scope

This document gives requirements and recommendations for the qualification and design, installation, testing and inspection for the external application of composite repair systems to corroded or damaged pipework, pipelines, tanks and vessels used in the petroleum, petrochemical and natural gas industries.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 75-3, *Plastics — Determination of temperature of deflection under load — Part 3: High-strength thermosetting laminates and long-fibre-reinforced plastics*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-4, *Plastics — Determination of tensile properties — Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastic composites*

ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 10952, *Plastics piping systems — Glass-reinforced thermosetting plastics (GRP) pipes and fittings — Determination of the resistance to chemical attack for the inside of a section in a deflected condition*

ISO 11357-2, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature and glass transition step height*

ISO 11359-2, *Plastics — Thermomechanical analysis (TMA) — Part 2: Determination of coefficient of linear thermal expansion and glass transition temperature*

ISO 14692, *Petroleum and natural gas industries — Glass-reinforced plastics (GRP) piping*

ASTM C581, *Standard Practice for Determining Chemical Resistance of Thermosetting Resins Used in Glass-Reinforced Structures Intended for Liquid Service*

ASTM D543, *Standard Practices for Evaluating the Resistance of Plastics to Chemical Reagents*

ASTM D696, *Standard Test Method for Coefficient of Linear Thermal Expansion of Plastics Between Minus 30°C and 30°C with a Vitreous Silica Dilatometer*

ASTM D1598, *Standard Test Method for Time-to-Failure of Plastic Pipe under Constant Internal Pressure*

ASTM D1599, *Standard Test Method for Resistance to Short-Time Hydraulic Pressure of Plastic Pipe, Tubing, and Fittings*

ASTM D2583, *Standard Test Method for Indentation Hardness of Rigid Plastics by Means of a Barcol Impressor*

ASTM D2992, *Standard Practice for Obtaining Hydrostatic or Pressure Design Basis for Fiberglass (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe and Fittings*

ASTM D3039, *Standard Test Method for Tensile Properties of Polymer Matrix Composite Materials*

ASTM D3165, *Standard Test Method for Strength Properties of Adhesives in Shear by Tension Loading of Single-Lap-Joint Laminated Assemblies*

ASTM D3681, *Standard Test Method for Chemical Resistance of Fiberglass (Glass-Fiber-Reinforced Thermosetting Resin) Pipe in a Deflected Condition*

ASTM D5379, *Standard Test Method for Shear Properties of Composite Materials by the V-Notched Beam Method*

ASTM D6604, *Standard Practice for Glass Transition Temperatures of Hydrocarbon Resins by Differential Scanning Calorimetry*

ASTM E831, *Standard Test Method for Linear Thermal Expansion of Solid Materials by Thermomechanical Analysis*

ASTM E1640, *Standard Test Method for Assignment of the Glass Transition Temperature by Dynamic Mechanical Analysis*

ASTM E2092, *Standard Test Method for Distortion Temperature in Three-Point Bending by Thermomechanical Analysis*

ASTM G8, *Standard Test Methods for Cathodic Disbonding of Pipeline Coatings*

BS 7910, *Guide to methods for assessing the acceptability of flaws in metallic structures*

EN 59, *Methods of testing plastics — Glass reinforced plastics — Measurement of hardness by means of a Barcol impressor (BS 2782-10, Method 1001, Measurement of hardness by means of a Barcol impressor)*

EN 1465, *Adhesives — Determination of tensile lap shear strength of rigid-to-rigid bonded assemblies*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

anisotropic

exhibiting different physical properties in different directions

3.2

Barcol hardness

measure of surface hardness using a surface impresser

3.3

blister

air void between layers within the laminate visible on the surface as a raised area

3.4

composite

thermoset resin system that is reinforced by fibres

3.5

crack

split in the laminate extending through the wall (perpendicular to the surface) such that there is actual separation with opposite surfaces visible