
**Hygrothermal performance of
building materials and products —
Determination of hygroscopic
sorption properties**

*Performance hygrothermique des matériaux et produits pour le
bâtiment — Détermination des propriétés de sorption hygroscopique*



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions, symbols and units	1
3.1 Terms and definitions	1
3.2 Symbols and units	2
4 Principle	2
4.1 Sorption curve	2
4.2 Desorption curve	2
5 Apparatus	3
5.1 Desiccator method	3
5.2 Climatic chamber method	3
6 Test specimens	3
6.1 Specification of the test specimens	3
6.2 Number of test specimens	3
7 Procedure	3
7.1 Test conditions	3
7.2 Desiccator method	4
7.3 Climatic chamber method	5
8 Calculation and expression of results	6
8.1 Hygroscopic sorption	6
8.2 Equilibrium moisture content curves	6
9 Accuracy of measurement	7
9.1 Error in moisture content	7
9.2 Control of environmental conditions	7
10 Test report	8
Annex A (informative) Air relative humidities above saturated solutions in equilibrium	9
Annex B (informative) Preparation of saturated solutions	12
Annex C (informative) Example of the procedure for determining a point on a sorption curve	15
Annex D (informative) Method using a glass jar	16
Bibliography	18

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12571 was prepared by the European Committee for Standardization (CEN) in collaboration with Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 1, *Test and measurement methods* in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 12571:2000), which has been technically revised.

[Annexes A](#) to [D](#) of this International Standard are for information only.

Hygrothermal performance of building materials and products — Determination of hygroscopic sorption properties

1 Scope

This International Standard specifies two alternative methods for determining hygroscopic sorption properties of porous building materials and products:

- a) using desiccators and weighing cups (desiccator method);
- b) using a climatic chamber (climatic chamber method).

The desiccator method is the reference method.

This International Standard does not specify the method for sampling.

The methods specified in this International Standard can be used to determine the moisture content of a sample in equilibrium with air at a specific temperature and humidity.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9346, *Hygrothermal performance of buildings and building materials — Physical quantities for mass transfer — Vocabulary*

ISO 12570, *Hygrothermal performance of building materials and products — Determination of moisture content by drying at elevated temperature*

3 Terms and definitions, symbols and units

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 9346 and the following apply.

3.1.1

equilibrium moisture content

moisture content of a porous material in equilibrium with the environment and the relative humidity of the ambient air, at a specified temperature

3.1.2

moisture content mass by mass

mass of evaporable water divided by mass of dry material

3.1.3

moisture content volume by volume

volume of evaporable water divided by volume of dry material

3.1.4

moisture content mass by volume

mass of evaporable water divided by volume of dry material

Note 1 to entry: The mass of water is determined by weighing the specimen before and after drying at the appropriate drying temperature until constant mass is reached.

3.1.5

sorption curve

curve established at a series of increasing equilibrium relative humidities at a given temperature

3.1.6

desorption curve

curve established at a series of decreasing equilibrium relative humidities at a given temperature

3.2 Symbols and units

Symbol	Quantity	Unit
m	mass of test specimen	kg
m_0	mass of dried test specimen	kg
u	moisture content mass by mass	kg/kg
ψ	moisture content volume by volume	m ³ /m ³
w	moisture content mass by volume	kg/m ³

4 Principle

4.1 Sorption curve

The specimen is dried to constant mass. While maintaining a constant temperature, the specimen is placed consecutively in a series of test environments, with relative humidity increasing in stages. The moisture content is determined when equilibrium with each environment is reached. Equilibrium with the environment is established by weighing the specimen until constant mass is reached. A minimum of four test atmospheres shall be selected in the humidity range under consideration.

After establishing the moisture content at each relative humidity the sorption curve can be drawn.

4.2 Desorption curve

The starting point for desorption is a relative humidity of at least 95 %. This might be the last point of the sorption curve or might be reached by sorption from a dried test specimen. While maintaining a constant temperature, the specimen is placed consecutively in a series of test environments, with relative humidity decreasing in stages. The moisture content is determined when equilibrium with each environment is reached. Equilibrium with the environment is established by weighing the specimen until constant mass is reached. A minimum of four test atmospheres shall be selected in the humidity range under consideration. Finally, the specimen is dried to constant mass.

After establishing the moisture content at each relative humidity the desorption curve can be drawn.

NOTE A defined starting point for desorption has been chosen for better reproducibility.

5 Apparatus

5.1 Desiccator method

The test apparatus shall include:

- a) **weighing cups** which do not absorb water and with tight-fitting lids;
- b) **balance**, capable of weighing to an accuracy of $\pm 0,01$ % of the mass of the test specimen;
 NOTE If larger weighing cups are used, the weighing accuracy can be determined with respect to the total mass and the required accuracy of the test results.
- c) **drying oven**, in accordance with ISO 12570;
- d) **desiccator**, capable of maintaining the relative humidity within ± 2 % relative humidity;
- e) **constant-temperature chamber**, capable of maintaining the specified test temperature to an accuracy of $\pm 0,5$ K.

5.2 Climatic chamber method

The test apparatus shall include:

- a) **weighing cups** which do not absorb water;
- b) **balance**, capable of weighing to an accuracy of $\pm 0,01$ % of the mass of the test specimen;
 NOTE If larger weighing cups are used, the weighing accuracy can be determined with respect to the total mass and the required accuracy of the test results.
- c) **drying oven**, in accordance with ISO 12570;
- d) **climatic chamber**, capable of maintaining the relative humidity within ± 5 % relative humidity and the temperature within ± 2 K over the whole test area.

6 Test specimens

6.1 Specification of the test specimens

A test specimen shall be representative of the product and have a mass of at least 10 g. Specimens of materials with a dry density less than 300 kg/m^3 shall have an area of at least $100 \text{ mm} \times 100 \text{ mm}$. If it can be demonstrated from other references that the result will not be affected, a test specimen can be cut or crushed into smaller pieces to reduce the time to reach equilibrium with the environment.

6.2 Number of test specimens

A minimum of three specimens shall be tested. The procedure in [Clause 7](#) shall be applied to each specimen.

7 Procedure

7.1 Test conditions

Reference sorption curves shall be established at a temperature of $(23 \pm 0,5)^\circ\text{C}$ or $(27 \pm 0,5)^\circ\text{C}$ in tropical countries. If agreed between the parties, sorption curves can be established at other temperatures for specific applications.

7.2 Desiccator method

7.2.1 General

Make up the appropriate saturated aqueous solution to achieve the necessary relative humidity in the desiccator.

Standard air relative humidities to be selected for measuring sorption curves are shown in [Table 1](#). Choose 5 or more conditions that include No.2, No.4 and No.6 in [Table 1](#).

NOTE [Annex A](#) gives the air relative humidities of various saturated solutions in equilibrium, and [Annex B](#) describes the preparation of various solutions.

Place the desiccator in the constant-temperature chamber (see [Figure 1](#)). The depth of saturated aqueous solution shall be 30 mm–50 mm.

Table 1 — Standard air relative humidities above saturated solutions in equilibrium

No.	Substance	Relative humidity	
		(%) ^a	
1	KOH	9	8
2	MgCl ₂ ·6H ₂ O	33	33
3	Mg(NO ₃) ₂ ·6H ₂ O	53	52
4	NaCl	75	75
5	KCl	85	84
6	KNO ₃	93	93
a Relative humidities in left column correspond to air temperature 23 °C. Relative humidities in right column correspond to air temperature 27 °C.			

7.2.2 Sorption curve

Weigh the weighing cup and lid when empty and dry. Put the test specimen into the weighing cup without the lid and dry it until constant mass in the drying oven at the temperature specified in ISO 12570.

Constant mass is reached if the change of mass between three consecutive weighings, each made at least 24 h apart, differs by less than 0,1 % of the total mass.

Put the test specimen in the weighing cup, with the lid beside it, into the desiccator containing the salt solution needed to give the appropriate relative humidity.

Periodically weigh the specimen until it is in equilibrium with the environment (constant mass). Immediately after removing the lid of the desiccator, put on the lid of the weighing cup, and move the weighing cup to the balance. After weighing the cup, return it to the desiccator with the lid beside it.

NOTE 1 [Annex C](#) gives an example of a detailed weighing procedure.

Repeat the procedure for increasing humidities. A minimum of four approximately evenly spaced humidities in increasing order shall be selected in the range of 30 % to 95 % relative humidity.

NOTE 2 It is possible that mould and mildew grow on specimens of wood based materials in atmospheres with relative humidities over 80 %. This might invalidate the test and can be prevented by adding a few drops of an appropriate fungicide to the solution.

7.2.3 Desorption curve

The starting point for desorption is a relative humidity of at least 95 %. This might be the last point of the sorption curve or might be reached by sorption from dried test specimen.


Put the test specimen in the weighing cup, with the lid beside it, into the desiccator containing the solution needed to give the appropriate relative humidity.

Periodically weigh the specimen until it is in equilibrium with the environment (constant mass). Immediately after removing the lid of the desiccator, put on the lid of the weighing cup, and move the weighing cup to the balance. After weighing the cup, return it to the desiccator with the lid beside it. Constant mass is reached if the change of mass between three consecutive weighings, each made at least 24 h apart, is less than 0,1 % of the total mass.

NOTE [Annex C](#) gives an example of a detailed weighing procedure.

Repeat the procedure for decreasing humidities. A minimum of four approximately evenly spaced humidities in decreasing order shall be selected in the range of 95 % to 30 % relative humidity.

NOTE [Annex D](#) gives an example of the method using a glass jar.



Key

- 1 constant temperature chamber
- 2 thermometer
- 3 lid of desiccator
- 4 desiccator
- 5 lid of weighing cup
- 6 weighing cup
- 7 test specimen
- 8 saturated salt solution
- 9 electronic balance

Figure 1 — Desiccator method

7.3 Climatic chamber method

7.3.1 Sorption curve

Put the test specimen, if necessary in the weighing cup, in the drying oven and dry it until constant mass at the temperature specified in ISO 12570. Constant mass is reached if the change of mass between three consecutive weighings, each made at least 24 h apart, is less than 0,1 % of the total mass.