

BETOONISEGU KATSETAMINE. OSA 6: TIHEDUS

Testing fresh concrete - Part 6: Density

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12350-6:2019 sisaldb Euroopa standardi EN 12350-6:2019 ingliskeelset teksti.	This Estonian standard EVS-EN 12350-6:2019 consists of the English text of the European standard EN 12350-6:2019.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 19.06.2019.	Date of Availability of the European standard is 19.06.2019.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.100.30

Standardite reproduutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 12350-6

June 2019

ICS 91.100.30

Supersedes EN 12350-6:2009

English Version

Testing fresh concrete - Part 6: Density

Essais pour béton frais - Partie 6 : Masse volumique

Prüfung von Frischbeton - Teil 6: Frischbetonrohdichte

This European Standard was approved by CEN on 29 April 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

	Page
European foreword	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	5
5 Apparatus	5
6 Sampling	6
7 Procedure	6
7.1 Calibration	6
7.2 Mass of density container	6
7.3 Filling the density container	6
7.4 Compacting the concrete	6
7.4.1 General	6
7.4.2 Mechanical compaction	7
7.4.3 Compacting by hand with compacting rod or bar	7
7.5 Surface levelling	7
7.6 Weighing	7
8 Calculation of density	8
9 Test report	8
10 Precision	8
Annex A (normative) Calibration of density container	10
A.1 Apparatus	10
A.2 Procedure	10
Bibliography	11

European foreword

This document (EN 12350-6:2019) has been prepared by Technical Committee CEN/TC 104 "Concrete and related products", the secretariat of which is held by SN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2019, and conflicting national standards shall be withdrawn at the latest by December 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12350-6:2009.

The compactions of specimens using hand tamping, vibrating table, or internal (poker) vibrator are accepted as equivalent. However, the use of an internal vibrator to compact specimens containing entrained air should be carried out with caution.

A procedure for calibrating the density container has been included as a normative Annex A.

This standard is one of a series on testing concrete.

EN 12350, *Testing fresh concrete*, consists of the following parts:

- *Part 1: Sampling and common apparatus*
- *Part 2: Slump test*
- *Part 3: Vebe test*
- *Part 4: Degree of compactability*
- *Part 5: Flow table test*
- *Part 6: Density*
- *Part 7: Air content – Pressure methods*
- *Part 8: Self-compacting concrete – Slump-flow test*
- *Part 9: Self-compacting concrete – V-funnel test*
- *Part 10: Self-compacting concrete – L-box test*
- *Part 11: Self-compacting concrete – Sieve segregation test*
- *Part 12: Self-compacting concrete – J-ring test*

The following amendments have been made to the 2009 edition of this standard:

- a) editorial revision;
- b) reference to common apparatus and specification given in EN 12350-1;
- c) option to include specified consistence class or consistence target value in report.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This document specifies a method for determining the density of compacted fresh concrete both in the laboratory and in the field.

It may not be applicable to very stiff concrete which cannot be compacted by normal vibration.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12350-1, *Testing fresh concrete — Part 1: Sampling and common apparatus*

EN 206, *Concrete — Specification, performance, production and conformity*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Principle

Fresh concrete is compacted into a rigid and watertight container of known volume and mass and is then weighed.

5 Apparatus

5.1 Common apparatus for fresh concrete testing

The apparatus listed below for the execution of this test method shall be in accordance with the specification given in EN 12350-1 and as specified below.

5.1.2 Density container, having the same specification and dimensions as the container specified in EN 12350-1.

5.1.3 Filling frame, filling may be simplified by using a filling frame fitted tightly to the density container.

5.1.4 Means of compacting the concrete, which may be one of the following:

- a) internal (poker) vibrator;
- b) vibrating table;
- c) compacting rod;
- d) compacting bar.

5.1.5 Balance or scales.