

Paints and varnishes - Determination of resistance to
filiform corrosion - Part 1: Steel substrates (ISO
4623-1:2018)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 4623-1:2018 sisaldab Euroopa standardi EN ISO 4623-1:2018 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 4623-1:2018 consists of the English text of the European standard EN ISO 4623-1:2018.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 14.11.2018.	Date of Availability of the European standard is 14.11.2018.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 87.040

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Paints and varnishes - Determination of resistance to
filiform corrosion - Part 1: Steel substrates (ISO 4623-
1:2018)

Peintures et vernis - Détermination de la résistance à la
corrosion filiforme - Partie 1: Subjectiles en acier (ISO
4623-1:2018)

Beschichtungsstoffe - Bestimmung der Beständigkeit
gegen Filiformkorrosion - Teil 1: Stahl als Substrat (ISO
4623-1:2018)

This European Standard was approved by CEN on 13 September 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 4623-1:2018) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2019, and conflicting national standards shall be withdrawn at the latest by May 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 4623-1:2002.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 4623-1:2018 has been approved by CEN as EN ISO 4623-1:2018 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Limitations	2
6 Sampling	2
7 Apparatus	2
8 Reagents	2
9 Test panels	2
9.1 Material and dimensions	2
9.2 Preparation and coating	2
9.3 Drying and conditioning	3
9.4 Thickness of coating	3
10 Procedure	3
10.1 Number of determinations	3
10.2 Scribing the test panels	3
10.3 Testing	4
10.3.1 General	4
10.3.2 Dipping technique	4
10.3.3 Salt fog technique	4
10.4 Inspection of test panels	5
11 Evaluation of the degree of filiform corrosion	5
12 Precision	5
13 Test report	6
Annex A (informative) Guidance notes on maintaining exposure conditions using saturated ammonium sulfate solution	7
Bibliography	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This second edition cancels and replaces the first edition (ISO 4623-1:2000), which has been technically revised. The main changes compared to the previous edition are as follows:

- a) the text has been aligned with ISO 4623-2;
- b) the introduction of ISO 4623-2 has been copied;
- c) the definition of filiform corrosion has been aligned with ISO 4623-2;
- d) in [10.2](#) a reference to ISO 17872 for the cutting tool has been added;
- e) in [10.3.3](#) the time of exposure of the test panels to neutral salt fog has been shortened from 24 h to 4 h;
- f) the supplementary test conditions previously in [Annex A](#) have been integrated into the test report;
- g) the text has been editorially revised and the normative references have been updated.

A list of all parts in the ISO 4623 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

A scribe mark cut through a coating of paints or varnishes on metal can give rise to various types of corrosion, such as blistering of the coating, corrosion of the metal under the coating, as well as filiform corrosion. Filiform corrosion tends to develop under specific conditions of temperature and relative humidity and when traces of acids, bases, or salts are present either under the paint coating or at breaks in the coating. These conditions are often found in marine and/or industrial environments. A certain amount of under-corrosion of the coating, starting from the scribe mark, will always occur. Filiform corrosion, however, is considered to be present only if the typical pattern in the form of threads is obvious.

Paints and varnishes — Determination of resistance to filiform corrosion —

Part 1: Steel substrates

1 Scope

This document describes a test procedure for assessing the protective action of coatings of paints or varnishes on steel against filiform corrosion arising from a scribed mark cut through the coating.

It is only suitable for assessing the performance of the coating/substrate combination tested. It is not suitable for predicting the performance of the coating on different substrates.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of test samples*

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 2808, *Paints and varnishes — Determination of film thickness*¹⁾

ISO 3270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing*

ISO 4618, *Paints and varnishes — Terms and definitions*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 filiform corrosion

type of corrosion proceeding under a coat of paint, varnish, or related product, in the form of threads, generally starting from bare edges or from local damage to the coating

Note 1 to entry: Usually the threads are irregular in length and direction of growth, but they can also be nearly parallel and of approximately equal length. They usually follow the extrusion direction and do not cross over one another. They need to be initiated by aggressive ions.

1) Under preparation. Stage at the time of publication ISO/DIS 2808:2018.