
**Graphic technology — Determination
of tack of paste inks and vehicles by a
rotary tackmeter**

*Technologie graphique — Détermination du tirant des encres, à l'aide
d'un tackomètre rotatif*



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus	3
5 Principle	6
6 Conditioning, sampling and sample preparation	6
6.1 Calibration.....	6
6.2 Conditioning (breaking-in) of the tackmeter rollers.....	7
6.3 Sampling.....	7
6.4 Sample conditioning.....	7
7 Procedure	7
7.1 Preparation and instrument settings.....	7
7.2 Settings for specific tests not mentioned explicitly in this document.....	8
7.3 Inking of the central roller.....	8
7.4 Measuring tack.....	9
8 Evaluation	10
9 Report	10
Annex A (informative) Reference testing	12
Annex B (normative) Measuring geometries	13
Annex C (normative) Breaking-in rollers	14
Bibliography	15

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 130, *Graphic technology*.

This second edition cancels and replaces the first edition (ISO 12634:1996), which has been technically revised.

The document has been entirely revised with regard to instrument specifications and test method settings.

Introduction

On the market, a number of three-roller tackmeters are available that differ in design features such as roller weight, geometry and composition of the distribution system. Instruments of different types do not give the same apparent tack readings. Instruments of the same type will only give apparent tack readings within tolerance, provided that they are maintained and calibrated properly and in the same manner.

Tack is a property indicative of internal cohesion of fluids and the adhesion to surfaces. It varies with measuring conditions, primarily separation velocity, splitting area, force applied, film thickness and temperature. Tack also varies with changes in other rheological properties of the fluid as a result of time and interactions with the separating surfaces.

This document refers to tack measurement of paste inks and their vehicles only, not involving fountain solution. During offset printing, the ink on a press may contain fountain solution and form an emulsion. The amount of fountain solution within the ink partly depends on the composition of both the ink and the fountain solution, the forces present, and the relative position of the ink in the roller train. The tack of an emulsion partly depends on the composition of both the ink and the fountain solution and the ratio of ink and fountain solution.

The tack value is a well-established criterion for assessing a paste ink or vehicle, although the parameter tack is poorly defined. The tack cannot be regarded as a material property that can be derived from basic physical phenomena. However, the tack influences the behaviour of ink in a printing press.

Parameters that affect tack include:

- dimensions, hardness and elasticity parameters of elastomeric rollers;
- surface properties of rollers;
- nip pressure;
- roller speed;
- temperature of rollers and environment;
- temperature of the sample;
- ink film thickness;
- influence of the ink or vehicle on the properties of the elastomeric coverage of the rollers (e.g. absorption of solvents);
- condition of the elastomeric rollers due to the cleaning process;
- condition of the elastomeric rollers due to long-term use;
- properties of the test sample.

The tack of printing inks and vehicles influences their transfer properties, as manifested by throughput in roll milling, picking of paper during printing and wet trapping in multicolour printing. Although a tack measurement does not completely predict the transfer performance of an ink or a vehicle, it provides a meaningful parameter for quality control, development and research.

Parameters that are affected by tack include:

- pick;
- ink trap;
- mottle.

Respecting all differences, this document specifies a method that allows users of comparable equipment to obtain comparable results when working under the same conditions.

The previous version of this document referred mainly to the manufacturers' recommendations for test method specifications such as speed, ink film thickness and temperature. As a result, there was a huge increase in the number of small differences according to user, region, instrument, etc. This new revision standardizes the settings across two platforms, Geometry A and Geometry B, for the purpose of communication. Individual users can still use the familiar settings for internal use. If the deviating settings are used for external communication, the deviation has to be described in the communication.

Mechanical instruments have been excluded from this document.

In this method, a procedure has been added to perform a periodic test with reference material to check deterioration of the materials used, such as rubbers and inks.

Graphic technology — Determination of tack of paste inks and vehicles by a rotary tackmeter

1 Scope

This document specifies the test procedure for determining the tack value of neat paste inks and vehicles which have low volatility and are unreactive under normal room conditions during the timespan required for testing.

This document contains a basic description of Inkometer®¹⁾ and Inkomat®²⁾ (Geometry A) and TackOscope®³⁾ and TackTester®⁴⁾ (Geometry B).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

breaking-in

<roller conditioning> preparation process for new rollers where these are running in an (or another) ink system to condition the *elastomer* (3.10) until constant readings are achieved

3.2

central roller

temperature controlled metallic roller used in a three-roller tack tester for ink distribution and as ink transfer roller to the *measuring roller* (3.7)

3.3

distribution roller

elastomer covered roller used in a three-roller tack tester for ink distribution over the *central roller* (3.2)

1) Inkometer® is an example of a suitable product available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of this product.

2) Inkomat® is an example of a suitable product available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of this product.

3) TackOscope® is an example of a suitable product available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of this product.

4) TackTester® is an example of a suitable product available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of this product.