
**Nickel alloys — Determination of lead
— Electrothermal atomic absorption
spectrometric method**

*Alliages de nickel — Détermination du plomb — Méthode par
spectrométrie d'absorption atomique électrothermique*



This document is a preview generated by EMS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Reagents.....	1
6 Apparatus.....	2
7 Instrument criteria.....	3
7.1 Preparation of solutions required for testing criteria.....	3
7.2 Characteristic mass.....	3
7.3 Minimum precision.....	3
7.4 Limit of detection.....	3
7.5 Linearity.....	4
8 Sampling and sample preparation.....	4
9 Procedure.....	4
9.1 Preparation of the test solution.....	4
9.2 Blank test.....	4
9.3 Preparation of the calibration solutions.....	4
9.4 Calibration and determination.....	4
9.4.1 Adjustment of the atomic absorption spectrometer.....	4
9.4.2 Atomic absorption measurements.....	5
9.5 Number of determinations.....	5
10 Expression of results.....	6
10.1 Calculation.....	6
10.2 Precision.....	6
10.2.1 Interlaboratory tests.....	6
10.2.2 Precision data.....	6
11 Test report.....	7
Annex A (normative) Optimization and checking of spectrometer performance criteria.....	8
Bibliography.....	15

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 155, *Nickel and nickel alloys*.

This first edition cancels and replaces ISO 11437-1:1994 and ISO 11437-2:1994, which have been merged and technically revised.

Nickel alloys — Determination of lead — Electrothermal atomic absorption spectrometric method

1 Scope

This document specifies an electrothermal atomic absorption spectrometric method for the determination of lead in the range of 1 µg/g to 10 µg/g in nickel alloys.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Principle

Dissolution of a test portion in a mixture of nitric acid and hydrofluoric acid, dilution of the test solution to a known volume, and transfer of an aliquot to a plastic vial.

Addition of a modifier to the aliquot of the test solution, and injection of a small volume of this solution into the electrothermal atomizer of an atomic absorption spectrometer.

Measurement of the atomic absorption of the 283,3 nm spectral line energy emitted by a lead hollow-cathode lamp and comparison with those of the calibration solutions.

5 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

5.1 Pure nickel, containing less than 1 µg/g of lead.

5.2 Nickel, base-solution 50 g/l.

Weigh, to the nearest 0,1 g, 25,0 g of pure nickel (5.1). Transfer to a 600 ml tall-form beaker and add 100 ml of water. Cautiously add 100 ml of nitric acid ($\rho_{20} = 1,41$ g/ml) in small portions, in such a manner that the dissolution remains under control. Cool the solution and transfer it to a 500 ml one-mark volumetric flask. Make up to the mark with water and mix.