INTERNATIONAL STANDARD

ISO 20313

> First edition 2018-01

St. Cats Navires et .

Navires et technologie maritime — Protection cathodique des navires



Reference number ISO 20313:2018(E)



© ISO 2018, Published in Switzerland

rroduced or utilized c
'te internet or an '
or ISO's memb All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Contents					
Fore	eword		v		
Intr	oductio	on	vi		
1	Scon	0e	1		
2		mative references			
3	Tern	ns and definitions	2		
4	Com	petence of personnel	3		
5	Design basis				
	5.1	General			
	5.2	Cathodic protection criteria			
	5.3	Design process			
	5.4	Design considerations			
		5.4.1 Cathodic protection zones of ship hull (external)			
		5.4.2 Internal cathodic protection zones			
		5.4.3 Component characteristics			
		5.4.4 Service conditions			
	5.5	Current demand			
		5.5.1 General 5.5.2 Design current density for bare steel			
		5.5.2 Design current density for bare steel5.5.3 Design current density for coated steel			
		5.5.4 Current demand	o		
	5.6	Cathodic protection systems	11		
	5.7	Electrical continuity			
	5.8	Fitting out period			
6	Impressed current system				
6	6.1	Objectives	12		
	6.2	Design considerations	12		
	6.3	Equipment considerations	12		
	0.5	6.3.1 Power source, monitoring and control systems			
		6.3.2 Anodes			
		6.3.3 Dielectric shields	16		
		6.3.4 Permanent reference and measurement electrodes			
		6.3.5 Cables and terminations			
		6.3.6 Cofferdams			
7	Galv	anic anode systems	17		
,	7.1	Objectives	17		
	7.2	Design considerations			
	7.3	Anode materials			
	7.4	Factors determining the anode current output and operating life			
	7.5	Location of anodes			
		7.5.1 External hull surfaces	19		
		7.5.2 Internal surfaces	20		
8	Com	missioning, operation and maintenance	23		
	8.1	Objectives			
	8.2	Measurement procedures			
	8.3	Commissioning: Galvanic systems			
	8.4	Commissioning: Impressed current systems			
		8.4.1 Visual inspection			
		8.4.2 Pre-energizing measurements	25		
		8.4.3 Initial energizing			
		8.4.4 Performance assessment			
	8.5	Operation and maintenance	26		

iii

ISO 20313:2018(E)

		8.5.1	General	
		8.5.2	Galvanic anode systems	
		8.5.3	Impressed current systems	
		8.5.4	Interaction with adjacent structures	
	8.6	Dry-doo	cking period	27
9	The pr	otectio	n of ships' hulls during fitting out and when laid up	28
			out period	
			period	
10	Docum	entatio	on	28
_			Ve S.	_
		,	c anode systems	
			sed current system	
	A (info	rmative]) Impressed current system for external hulls of ships based on two ection zones	
Annex	B (info	rmative] hulls an) Guidance on design current density values for cathodic protection of nd tanks	32
Annex	C (info	rmative`) Anode resistance, current and life duration formulae	34
	•	-	e) Electrical bonding systems	
) Monitoring of electrical bonding of a ship's propeller	
Annex	F (info	rmative)) Impressed current system for ships based on an aft (stern) system only	42
Annex	G (info	rmative]) Location of galvanic anodes in the stern area	43
	-		e) Electrochemical characteristics of impressed current anodes	
Annex	I (infor	mative)	Cofferdam arrangements	46
	I (infor	mative)	Cathodic protection of a moored ship using suspended galvanic anodes	49
Annex				
		-) Anode/cathode separation (dielectric shield) calculations	
Annex	K (info	rmative		51
Annex Annex	K (info	rmative rmative) Galvanic anode specifications	51 52
Annex Annex Annex	K (info	rmative rmative) ormative) Galvanic anode specifications e) Use of portable coupons	51 52 55
Annex Annex Annex	K (info	rmative rmative) ormative) Galvanic anode specificationse) Use of portable coupons	51 52 55

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following ad marin. URL: www.iso.org/iso/foreword.html.

This document was prepared by ISO/TC 8 Ships and marine technology, SC 8, Ship design.

Introduction

Cathodic protection is applied to ships to protect the immersed sections of the vessel from corrosion. This includes the external hull surface and the internal surfaces of tanks containing seawater, e.g. ballast tanks.

Cathodic protection, often in conjunction with coatings, can be applied by impressed current, galvanic anode techniques or a combination of both.

Cathodic protection works by applying direct current to the immersed surface to change the steel-toelectrolyte potential to values where the rate of corrosion is considered insignificant.

The General Principles of Cathodic Protection in Seawater are described in ISO 12473.

s nece Hull penetrations and cofferdams necessary for cathodic protection generally require Classification Society approval.

Ships and marine technology — Cathodic protection of ships

1 Scope

This document specifies protection criteria, and makes recommendations for design and specifications for both impressed current and galvanic anode cathodic protection systems for ships. Cathodic protection of external hull and ballast tanks are included.

This document is applicable to the immersed sections of hulls and tanks containing seawater for ships, boats, and other self-propelled floating vessels. It includes fixtures generally encountered on ship hulls such as:

- rudders;
- propellers;
- shafts;
- stabilizers;
- thrusters;
- sea chests;
- water intakes (up to the first valve).

It does not cover protection of floating structures that are not self-propelled.

This document is applicable to the cathodic protection of ship hulls fabricated principally from carbon manganese or low-alloy steels including fixtures of other ferrous or non-ferrous alloys such as stainless steels and copper alloys, etc.

This document is applicable to both coated and bare hulls and tanks; most hulls and tank internals are coated.

This document is not applicable to the cathodic protection of hulls principally made of other materials such as aluminium alloys, stainless steels or concrete.

This document is applicable to the hull and fixtures in seawater and all waters which could be encountered during a ship's world-wide deployment.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 8044, Corrosion of metals and alloys — Basic terms and definitions

ISO 9606-1, Qualification testing of welders — Fusion welding — Part 1: Steels

ISO 12944-1, Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 1: General introduction

ISO~12944-2, Paints~and~varnishes -- Corrosion~protection~of~steel~structures~by~protective~paint~systems -- Part~2:~Classification~of~environments

ISO 15607, Specification and qualification of welding procedures for metallic materials — General rules

ISO 20313:2018(E)

ISO 15609-1, Specification and qualification of welding procedures for metallic materials — Welding procedure specification — Part 1: Arc welding

ASTM B418, Type 1 Standard specification for cast and wrought galvanic zinc anodes

EN 12496, Galvanic anodes for cathodic protection in seawater and saline mud

EN 50162, Protection against corrosion by stray current from direct current systems

IMCA DO45, Code of Practice for Safe Use of Electricity Underwater

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8044 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

3.1

system life

design life of the cathodic protection system

3.2

anode design life

stated period for which the anode is required to be fully functional

3.3

immersed zone

zone located below the water line at draught corresponding to normal working conditions

3.4

underwater hull

immersed surface area of the hull at any given time

Note 1 to entry: Used to calculate current demand.

3.5

boot topping

section of the hull between light and fully loaded conditions

Note 1 to entry: Boot topping may be intermittently an immersed part of the structure which can be considered independently with respect to the cathodic protection design. A single zone can comprise a variety of components with differing design parameters.

3.7

submerged zone

zone including the immersed zone and the boot topping

3.8

driving voltage

difference between the steel-to-electrolyte potential and the sacrificial anode-to-electrolyte potential when the cathodic protection is operating

3.9

closed circuit potential

potential measured at a galvanic anode when a current is flowing between the anode and the surface being protected