

INTERNATIONAL STANDARD

ISO
9073-1

First edition
1989-07-01

Textiles — Test methods for nonwovens —

Part 1: Determination of mass per unit area

*Textiles — Méthodes d'essai pour nontissés —
Partie 1 : Détermination de la masse surfacique*



Reference number
ISO 9073-1 : 1989 (E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 9073-1 was prepared by Technical Committee ISO/TC 38, *Textiles*.

ISO 9073 consists of the following parts, under the general title *Textiles – Test methods for nonwovens*:

- *Part 1: Determination of mass per unit area*
- *Part 2: Determination of thickness*
- *Part 3: Determination of tensile strength and elongation*
- *Part 4: Determination of tear resistance*

© ISO 1989

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Introduction

Although nonwovens are classified within the textile industry, it should be recognized that nonwovens technologically share characteristics not only with textile products but also with paper and/or plastic products. There is an existing international textile test, ISO 3801. However, in order to meet the specific needs of nonwovens, alternative requirements to those listed in ISO 3801 are specified in this part of ISO 9073. These are

- a) a different sampling procedure;
- b) an alternative specification for dimensions of test piece;
- c) a greater accuracy for the balance.

This document is a preview generated by EVS

This document is a preview generated by EVS

This page intentionally left blank

Textiles — Test methods for nonwovens —

Part 1 : Determination of mass per unit area

1 Scope

This part of ISO 9073 specifies a method for the determination of mass per unit area of nonwovens.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 9073. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 9073 are encouraged to investigate the possibility of applying the most recent editions of the standards listed below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 139 : 1973, *Textiles — Standard atmospheres for conditioning and testing*.

ISO 186 : 1985, *Paper and board — Sampling to determine average quality*.

ISO 3801 : 1977, *Textiles — Woven fabrics — Determination of mass per unit length and mass per unit area*.

3 Principle

Measurement of the area and mass of a test piece and calculation of its mass per unit area in grams per square metre.

4 Apparatus

4.1 Apparatus for cutting the test pieces, chosen from among the following.

4.1.1 Die, which cuts a test piece of an area of at least 50 000 mm².

4.1.2 Template, with an area of at least 50 000 mm² (e.g. 250 mm × 200 mm) and a **razor blade**.

4.1.3 Steel rule, accurately graduated in millimetres, and a **razor blade**.

4.2 Balance, capable of determining the mass of a test piece to an accuracy of ± 0,1 % of the determined mass.

5 Sampling

Carry out sampling in accordance with ISO 186.

NOTES

1 The optimum sample size will vary with different nonwovens and should be agreed between purchaser and vendor. The size should preferably not be smaller than the size specified in 4.1 due to anisotropy of various nonwovens.

2 Attention is drawn to the fact that with nonwovens, sampling error may be greater than the testing error.

3 This method of sampling recognizes and makes provisions for "anisotropy" (differences in properties along various directions, principally machine and cross direction) in the final specimens. However, these specimens are random representatives of the material and in some cases it may be desirable to investigate systematic variations of properties (including anisotropy), for example across the width, or in certain positions along the length of a given reel. In all such cases, special provisions should be agreed between purchaser and vendor and recorded in the test report. A procedure for more detailed examination of variability within a given batch of material is available in TAPPI T 11-05-74 and may be found helpful. This publication may be obtained from: The Technical Association of Pulp and Paper Industries, 1 Dunwoody Park, Atlanta, Georgia 30338, USA.