

Welding consumables - Fluxes for submerged arc welding and electroslag welding - Classification (ISO 14174:2019)

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 14174:2019 sisaldab Euroopa standardi EN ISO 14174:2019 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 14174:2019 consists of the English text of the European standard EN ISO 14174:2019.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 15.05.2019.	Date of Availability of the European standard is 15.05.2019.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 25.160.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:  
Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

EUROPEAN STANDARD

**EN ISO 14174**

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2019

ICS 25.160.20

Supersedes EN ISO 14174:2012

English Version

## Welding consumables - Fluxes for submerged arc welding and electroslag welding - Classification (ISO 14174:2019)

Produits consommables pour le soudage - Flux pour le  
soudage à l'arc sous flux et le soudage sous laitier -  
Classification (ISO 14174:2019)

Schweißzusätze - Pulver zum Unterpulverschweißen  
und Elektroschlackeschweißen - Einteilung (ISO  
14174:2019)

This European Standard was approved by CEN on 8 May 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

## European foreword

This document (EN ISO 14174:2019) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2019, and conflicting national standards shall be withdrawn at the latest by November 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 14174:2012.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Endorsement notice

The text of ISO 14174:2019 has been approved by CEN as EN ISO 14174:2019 without any modification.

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Classification</b> .....	<b>1</b>
<b>5 Symbols</b> .....	<b>2</b>
5.1 Symbol for the product/process.....	2
5.2 Symbol for method of manufacture.....	2
5.3 Symbol for type of flux, characteristic chemical constituents.....	2
5.4 Symbol for applications, flux class.....	2
5.4.1 General.....	2
5.4.2 Flux class 1.....	3
5.4.3 Flux classes 2 and 2B.....	3
5.4.4 Flux class 3.....	3
5.4.5 Flux class 4.....	3
5.5 Symbol for metallurgical behaviour.....	5
5.5.1 General.....	5
5.5.2 Metallurgical behaviour, flux class 1.....	5
5.5.3 Metallurgical behaviour, flux classes 2 and 2B.....	5
5.5.4 Metallurgical behaviour, flux class 3.....	6
5.5.5 Metallurgical behaviour, flux class 4.....	6
5.5.6 Determination of symbols for metallurgical behaviour.....	6
5.6 Symbol for type of current.....	7
5.7 Symbol for diffusible hydrogen content in deposited weld metal (class 1 fluxes only).....	7
<b>6 Particle size range</b> .....	<b>8</b>
<b>7 Rounding procedure</b> .....	<b>8</b>
<b>8 Retest</b> .....	<b>8</b>
<b>9 Technical delivery conditions</b> .....	<b>9</b>
<b>10 Marking</b> .....	<b>9</b>
<b>11 Designation</b> .....	<b>9</b>
<b>Annex A (informative) Characteristic chemical constituents of flux — Example of determination from elemental analysis</b> .....	<b>11</b>
<b>Annex B (informative) Description of flux types</b> .....	<b>13</b>
<b>Bibliography</b> .....	<b>16</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

This third edition cancels and replaces the second edition (ISO 14174:2012), which has been technically revised. The main changes compared to the previous edition are as follows:

- Subclause [5.4.3](#) now clarifies burn-out;
- ISO 18724 has been added to [Clause 2](#);
- [Table 3](#) has been expanded;
- [Table 5](#) for flux class 2, welding current and voltage have been revised;
- an example of a Z option has been added;
- information on IIW Round robin testing of fluxes has been added to [Annex B](#) and as a bibliographical reference;
- Clause [B.16](#) has been corrected to include CaF<sub>2</sub> (to align with EN 760).

Any feedback, question or request for official interpretation related to any aspect of this document should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html). Official interpretations, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

# Welding consumables — Fluxes for submerged arc welding and electroslag welding — Classification

## 1 Scope

This document specifies requirements for classification of fluxes for submerged arc welding and electroslag welding for joining and overlay welding using wire electrodes, tubular cored electrodes, and strip electrodes.

NOTE This document was based on EN 760:1996.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3690, *Welding and allied processes — Determination of hydrogen content in arc weld metal*

ISO 14171, *Welding consumables — Solid wire electrodes, tubular cored electrodes and electrode/flux combinations for submerged arc welding of non alloy and fine grain steels — Classification*

ISO 14343, *Welding consumables — Wire electrodes, strip electrodes, wires and rods for arc welding of stainless and heat resisting steels — Classification*

ISO 18274, *Welding consumables — Solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys — Classification*

ISO 80000-1:2009, *Quantities and units — Part 1: General* Corrected by ISO 80000-1:2009/Cor 1:2011

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

## 4 Classification

Fluxes for submerged arc welding and electroslag welding for joining and overlay welding are granular, fusible products of mainly mineral origin, which are manufactured by various methods. Fluxes influence the chemical composition and the mechanical properties of the weld metal.

The classification of the fluxes is divided into seven parts:

- 1) the first part gives a symbol indicating the product/process (see 5.1);
- 2) the second part gives a symbol indicating the method of manufacture (see 5.2);
- 3) the third part gives a symbol indicating the type of flux, characteristic chemical constituents (see Table 1);