

Non-destructive testing - Ultrasonic thickness measurement (ISO 16809:2017)

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 16809:2019 sisaldab Euroopa standardi EN ISO 16809:2019 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 16809:2019 consists of the English text of the European standard EN ISO 16809:2019.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 05.06.2019.	Date of Availability of the European standard is 05.06.2019.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 19.100

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN ISO 16809

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2019

ICS 19.100

Supersedes EN 14127:2011

English Version

Non-destructive testing - Ultrasonic thickness measurement (ISO 16809:2017)

Essais non destructifs - Mesurage de l'épaisseur par
ultrasons (ISO 16809:2017)

Zerstörungsfreie Prüfung - Dickenmessung mit
Ultraschall (ISO 16809:2017)

This European Standard was approved by CEN on 8 April 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

The text of ISO 16809:2017 has been prepared by Technical Committee ISO/TC 135 "Non-destructive testing" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 16809:2019 by Technical Committee CEN/TC 138 "Non-destructive testing" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2019, and conflicting national standards shall be withdrawn at the latest by December 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14127:2011.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 16809:2017 has been approved by CEN as EN ISO 16809:2019 without any modification.

Contents

	Page
Foreword	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Measurement modes	1
5 General requirements	3
5.1 Instruments.....	3
5.2 Probes.....	3
5.3 Couplant.....	3
5.4 Reference blocks.....	3
5.5 Test objects.....	3
5.6 Qualification of personnel.....	4
6 Application of the technique	4
6.1 Surface conditions and surface preparation.....	4
6.2 Technique.....	4
6.2.1 General.....	4
6.2.2 Measurement during manufacture.....	5
6.2.3 In-service measurement of residual wall thickness.....	5
6.3 Selection of probe.....	6
6.4 Selection of instrument.....	6
6.5 Materials different from the reference material.....	6
6.6 Special measuring conditions.....	7
6.6.1 General.....	7
6.6.2 Measurements at temperatures below 0 °C.....	7
6.6.3 Measurements at elevated temperatures.....	7
6.6.4 Hazardous atmospheres.....	7
7 Instrument setting	7
7.1 General.....	7
7.2 Methods of setting.....	8
7.2.1 General.....	8
7.2.2 Digital thickness instruments.....	8
7.2.3 A-scan instrument.....	8
7.3 Checks of settings.....	9
8 Influence on accuracy	10
8.1 Operational conditions.....	10
8.1.1 Surface conditions.....	10
8.1.2 Surface temperature.....	10
8.1.3 Metallic coating.....	11
8.1.4 Non-metallic coating.....	11
8.1.5 Geometry.....	12
8.2 Equipment.....	12
8.2.1 Resolution.....	12
8.2.2 Range.....	13
8.3 Evaluation of accuracy.....	13
8.3.1 General.....	13
8.3.2 Influencing parameters.....	14
8.3.3 Method of calculation.....	14
9 Influence of materials	14
9.1 General.....	14
9.2 Inhomogeneity.....	14
9.3 Anisotropy.....	14

9.4	Attenuation	14
9.5	Surface conditions.....	14
9.5.1	General.....	14
9.5.2	Contact surface.....	15
9.5.3	Reflecting surface.....	15
9.5.4	Corrosion and erosion.....	15
10	Test report.....	16
10.1	General.....	16
10.2	General information.....	16
10.3	Measurement data.....	17
Annex A (informative) Corrosion in vessels and piping.....		18
Annex B (informative) Instrument settings.....		23
Annex C (informative) Parameters influencing accuracy.....		26
Annex D (informative) Selection of measuring technique.....		32
Bibliography.....		37

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 135, *Non-destructive testing*, Subcommittee SC 3, *Ultrasonic testing*.

This second edition cancels and replaces the first edition (ISO 16809:2012), which has been technically revised. The main changes compared to the previous edition are as follows:

- editorial improvements have been made;
- the terminology has been adapted to the latest edition of ISO 5577;
- Formulae (5) and (6) have been corrected.

Non-destructive testing — Ultrasonic thickness measurement

1 Scope

This document specifies the principles for ultrasonic thickness measurement of metallic and non-metallic materials by direct contact, based on measurement of time of flight of ultrasonic pulses only.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5577, *Non-destructive testing — Ultrasonic testing — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 5577 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Measurement modes

The thickness of a part or structure is determined by accurately measuring the time required for a short ultrasonic pulse generated by a transducer to travel through the thickness of the material once, twice or several times.

The material thickness is calculated by multiplying the known sound velocity of the material with the transit time and dividing by the number of times the pulse transits the material wall.

This principle can be accomplished by applying one of the following modes, see [Figure 1](#).

- 1) **Mode 1:** Measure the transit time from an initial excitation pulse to a first returning echo, minus a zero correction to account for the thickness of the probe's wear plate and the couplant layer (single-echo mode).
- 2) **Mode 2:** Measure the transit time from the end of a delay line to the first back wall echo (single-echo delay line mode).
- 3) **Mode 3:** Measure the transit time between back wall echoes (multiple-echo mode).
- 4) **Mode 4:** Measure the transit time for a pulse travelling from the transmitter to a receiver in contact with the back wall (through-transmission mode).