

TECHNICAL REPORT

CEN/TR 17310

RAPPORT TECHNIQUE

TECHNISCHER BERICHT

January 2019

ICS 91.100.30

English Version

Carbonation and CO₂ uptake in concrete

Carbonatation et absorption du CO₂ dans le béton

Karbonatisierung und CO₂-Aufnahme von Beton

This Technical Report was approved by CEN on 30 December 2018. It has been drawn up by the Technical Committee CEN/TC 104.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Carbonation, the uptake of carbon dioxide	5
4.1 Compounds, chemistry and notation	5
4.2 Carbonation	6
4.2.1 Carbonation reactions	6
4.2.2 Process of carbonation	7
4.2.3 Degree of carbonation	8
4.2.4 Effect of carbonation on cement paste structure	10
4.2.5 Carbonation rate	11
4.2.6 Carbonation rate controlling factors	11
4.2.7 Carbonation rate of concrete with blended cements or with additions	15
4.3 CO ₂ binding capacity in concrete, Degree of carbonation	16
4.3.1 General	16
4.3.2 Theoretical binding capacity of Portland cement	17
4.3.3 Normal binding capacity of Portland cement	17
4.3.4 Normal binding capacity of blended cements	18
4.4 Carbonation in different environments	19
4.4.1 General	19
4.4.2 Dry indoor concrete	19
4.4.3 Concrete exposed to rain	20
4.4.4 Concrete sheltered from rain	20
4.4.5 Wet or submerged concrete	20
4.4.6 Buried concrete	21
5 Practical experiences of CO₂ uptake in concrete life stages	21
5.1 CO ₂ uptake during product stage (module A)	21
5.2 CO ₂ uptake during use stage (module B)	22
5.3 CO ₂ uptake during end of life stage	29
5.3.1 CO ₂ uptake during end of life stage - demolition, crushing and waste handling (module C1-C3)	29
5.3.2 CO ₂ uptake during end of life stage - landfill (module C4)	32
5.4 CO ₂ uptake beyond the system boundary (module D)	32
6 Figures for "direct estimation" of CO₂ uptake in whole structures during use stage	33
6.1 General	33
6.1.1 General	33
6.1.2 CO ₂ uptake for a portal frame bridge	34
6.1.3 CO ₂ uptake for a residential building	35
6.2 Average CO ₂ uptake for construction types, strength classes and exposure	36
7 Additional information	37

7.1	CO ₂ uptake in the long term, beyond the service life of the structure.....	37
7.2	CO ₂ uptake of crushed concrete in new applications	38
8	Society perspective - Carbonation and CO ₂ uptake in mortar	38
9	National calculation models and methods	39
9.1	General	39
9.2	Calculation of Carbonation of concrete in use phase (Swiss approach)	39
9.2.1	General	39
9.2.2	Water/CaO.....	39
9.2.3	CO ₂ concentration, relative humidity and CO ₂ buffer capacity	39
9.2.4	A simple approach of assessing the CO ₂ uptake of concrete components	40
9.2.5	Ratio of CO ₂ uptake/CO ₂ emission as a function of thickness of concrete element.....	43
	Bibliography	45

European foreword

This document (CEN/TR 17310:2019) has been prepared by Technical Committee CEN/TC 104 “Concrete and related products”, the secretariat of which is held by SN.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document is a preview generated by EVS

1 Scope

This document provides detailed guidance on the carbonation and carbon dioxide (CO₂) uptake in concrete. This guidance is complementary to that provided in EN 16757, *Product Category Rules for concrete and concrete elements*, Annex BB.

Typical CO₂ uptake values for a range of structures exposed to various environmental conditions are presented. These values can be incorporated into EPDs for the whole life cycle for either: a functional unit, one tonne or one m³ of concrete, without necessarily having any detailed knowledge of the structure to be built.

In the rest of the document, the data will be given per m³.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Carbonation, the uptake of carbon dioxide

4.1 Compounds, chemistry and notation

4.1.1 Carbon dioxide: Chemically expressed as CO₂ and present in the atmosphere as a gas. When CO₂ is dissolved in water, H₂O, it may form carbonic acid, H₂CO₃, where this may release carbonate, CO₃²⁻, and bicarbonate, HCO₃⁻ ions.

4.1.2 Calcium hydroxide: Chemically expressed as Ca(OH)₂ and often called Portlandite. It is a product of the hydration of Portland cement and is always present in concrete. For simplicity, cement chemists often denote calcium hydroxide as CH. Calcium hydroxide is not very soluble in water but it does dissolve to the ions Ca²⁺ and 2OH⁻. The presence of calcium hydroxide in concrete is largely responsible for maintaining its alkaline environment, which is at a pH around 12,5. Around 25 % of hardened hydrated cement is Ca(OH)₂.

4.1.3 Calcium oxide: Chemically expressed as CaO. Portland cement clinker contains 61 % to 67 % CaO by oxide analysis, and where typically the assumed value is 65 %. Nearly all the calcium oxide in Portland cement is not present as calcium oxide but as part of more complicated compounds such as di-calcium silicates, tri-calcium silicates, tri-calcium aluminate and tetra-calcium alumina ferrite. Fortunately using the oxide analysis figure of 65 % CaO is sufficient for the calculation of potential carbonation without going into the more complex chemistry.

4.1.4 Calcium silicate hydrates, and other hydration products: When Portland cement reacts with water, that is when it hydrates, it forms calcium hydroxide and a larger proportion of complex hydration products where the bulk of these are made up of calcium and silica. The hydration products, or gel as described by concrete technologists, are called calcium-silica-hydrates, often simplified to CSH.