

---

---

**Plain bearings — Metallic multilayer  
plain bearings —**

Part 1:  
**Non-destructive ultrasonic testing  
of bond of thickness greater than or  
equal to 0,5 mm**

*Paliers lisses — Paliers lisses métalliques multicouches —*

*Partie 1: Contrôle non destructif aux ultrasons des défauts  
d'adhérence d'épaisseur supérieure ou égale à 0,5 mm*



This document is a preview generated by EMS



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Symbols</b> .....	<b>1</b>
<b>5 Test equipment</b> .....	<b>2</b>
5.1 Ultrasonic instrument.....	2
5.2 Probe.....	2
5.3 Reference block.....	2
<b>6 Preparation of test surface</b> .....	<b>2</b>
<b>7 Testing</b> .....	<b>2</b>
7.1 General.....	2
7.2 Testing with a back-wall echo.....	2
7.3 Testing without a back-wall echo.....	3
<b>8 Test classes</b> .....	<b>6</b>
<b>9 Defect groups</b> .....	<b>6</b>
<b>10 Evaluation</b> .....	<b>7</b>
10.1 General.....	7
10.2 Marking of defective areas.....	8
10.3 Designation.....	8
<b>Bibliography</b> .....	<b>9</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 2, *Materials and lubricants, their properties, characteristics, test methods and testing conditions*.

This fourth edition cancels and replaces the third edition (ISO 4386-1:2012), of which it constitutes a minor revision. The changes compared to the previous edition are as follows:

- Adjustment to the ISO Directives, including the implementation of [Clause 3 Terms and definitions](#).

A list of all parts in the ISO 4386 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Plain bearings — Metallic multilayer plain bearings —

## Part 1:

# Non-destructive ultrasonic testing of bond of thickness greater than or equal to 0,5 mm

## 1 Scope

This document specifies an ultrasonic testing method for determining bond defects between the bearing metal and the backing. The test can be performed on metallic multilayer plain bearings consisting of steel- or copper-based material backings lined with bearing metal based on lead and tin, with layer thicknesses greater than or equal to 0,5 mm. For cast iron backings, this document is applicable with restrictions.

The ultrasonic signal reflected by the bond interface between the bearing metal and the backing is used to determine bonding defects.

Ultrasonic testing is not possible on edge zones of sliding surface, flange sides, joint areas, oil holes, grooves, etc. in a range of less than half the diameter of the ultrasonic probe because of undefined reflections. The same applies to bearings with dovetail keying grooves at the bond. Ultrasonic testing of bond does not apply along the edges of the dovetails.

Evaluation of the bond on the visible transition from the backing to the bearing metal (on end faces or joint faces) is only practicable by the penetrant testing method specified in ISO 4386-3.

This document only describes in detail the pulse-echo method. Within the meaning of this document, the ultrasonic method only permits a qualitative evaluation of the bonding and not a quantitative determination of the bond strength. The ultrasonic bond test differs only between bond and bond defect.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4386-3, *Plain bearings — Metallic multilayer plain bearings — Part 3: Non-destructive penetrant testing*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

## 4 Symbols

The following symbol is used in this document.

*Ra* Surface roughness