
**Clothing for protection against heat
and flame — Determination of heat
transmission on exposure to both
flame and radiant heat**

*Vêtements de protection contre la chaleur et la flamme —
Détermination de la transmission de chaleur lors de l'exposition
simultanée à une flamme et à une source de chaleur radiante*



This document is a preview generated by EMS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	3
5 Apparatus	4
6 Precautions	8
7 Sampling	9
7.1 Specimen dimensions.....	9
7.2 Number of specimens.....	9
8 Conditioning and testing atmospheres	9
8.1 Conditioning atmosphere.....	9
8.2 Testing atmosphere.....	9
9 Test procedure	9
9.1 Initial set up and calibration procedures.....	9
9.1.1 Initial set up of the system and alignment of burner flames.....	9
9.1.2 Initial setting of the 50/50 mix of convective and radiant heat.....	9
9.1.3 Setting the radiant heat from the lamps.....	9
9.1.4 Setting the total exposure heat flux.....	10
9.2 Sensor care.....	10
9.2.1 Sensor care.....	10
9.2.2 Sensor inspection.....	10
9.2.3 Surface reconditioning.....	10
9.3 Specimen holder care.....	11
9.4 Computer processing of data.....	11
9.5 Test specimen mounting.....	12
9.5.1 Single layer specimens.....	12
9.5.2 Multilayer assembly specimens.....	12
9.6 Test specimen exposure when both TPI and HTI(DE) are measured.....	12
9.7 Test specimen exposure when only HTI(DE) is measured.....	13
10 Expression of results	13
10.1 Selection of analysis method.....	13
10.2 Thermal protection index analysis method.....	13
10.2.1 Time to onset of burn injury.....	13
10.2.2 Thermal protection index.....	13
10.3 HTI(DE) analysis method.....	14
10.4 Response to convective and radiant heat exposure.....	14
11 Interlaboratory test data	14
12 Test report	14
Annex A (informative) Availability of materials	15
Annex B (informative) Basis of sensor calibration	17
Annex C (informative) Interlaboratory test data	18
Bibliography	19

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 94, *Personal safety — Personal protective equipment*, Subcommittee SC 13, *Protective clothing*.

This second edition cancels and replaces the first edition (ISO 17492:2003), which has been technically revised. It also incorporates the Technical Corrigendum ISO 17492:2003/Cor.1:2004. The main changes compared with the previous edition are as follows:

- technical modifications and rewording have been made to all clauses, including to [Annexes A](#) and [B](#);
- [Clauses 5](#) to [12](#) have been renumbered;
- modifications have been made to [Figures 1](#), [2](#) and [3](#).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The measurement of the thermal energy transferred from the exterior of a material to the interior when exposed to a thermal hazard can be a significant factor in determining the level of protection or insulation provided by an assembly. While full-scale test methods are a better means of determining how an assembly performs, small scale tests such as those described in ISO 6942 and ISO 9151 can be used in establishing benchmarks of performance for the materials from which these assemblies are made. These tests enable the user of a material to anticipate how the properties of a particular material could affect the performance of the assembly when exposed to a high heat flux.

The purpose of an assembly for thermal protection is to prevent or reduce the potential for skin burn injury to the wearer. The performance of a product can be determined by comparing the total exposure energy to that which is transferred through the protective material to a known point where the thermal exposure would produce a burn injury in human tissue. The total exposure energy required to cause the onset of a second-degree burn in human tissue is identified as the thermal protection index (TPI). In the TPI analysis of the data, the specimen is exposed to steady heat until the energy transferred through the specimen is equivalent to the energy that would cause the onset of a second-degree burn injury (e.g. a blister).

Other uses include comparison of the insulation from a high-temperature exposure in terms other than the response of human tissue to heat exposure. For these uses, an alternate method of evaluating the heat transfer is provided. The total energy transferred that causes a temperature rise of the copper sensor by 12 °C and 24 °C is determined as the heat transfer index (HTI). In the HTI analysis of the data, the specimen is exposed to heat until a specified amount of energy is transferred. This is a measure of the insulation performance and thermal capacity of the specimen.

Unlike what is described in ISO 6942 or ISO 9151, the heat source in this test method is approximately 50 % radiant heat and 50 % convective heat. This equalized radiant/convective output is set to a thermal energy exposure having a heat flux of 84 kW/m². The magnitude of this heat flux is intended to determine the performance of the specimen when exposed to both the high temperature radiation and hot gases that exist in actual fire situations. The level of this heat flux represents a moderately high industrial or emergency fire-fighting exposure that requires the use of a protective material.

This document can be used to measure and describe the properties of materials, products or assemblies in response to both convective and radiant heat under controlled laboratory conditions. It is not recommended to use this document to describe or appraise a fire hazard or fire risk of materials, products or assemblies under actual fire conditions. However, the results of this test method can be used as elements of a fire-risk assessment that takes into account all of the factors pertinent to an assessment of the fire hazard of a particular end use.

NOTE 1 This test method does not necessarily correlate to the heat-insulation performance of vertically oriented flame-resistant textile materials when exposed to convective and radiant heat or used in actual clothing configurations.

NOTE 2 The performance of materials made of flame-resistant fibres can be determined by the amount of heat energy transferred through the specimen and by observing any changes affected by the exposure on the specimen. The TPI and the HTI measure the accumulated thermal energy received by a sensor, which is an indication of the ability of the material to inhibit the transfer of heat.

NOTE 3 A human tissue burn (blister) is predicted to result when the total thermal energy transmitted by the material reaches the second-degree burn threshold identified by the Stoll curve.

NOTE 4 The TPI or the HTI for flame-resistant materials can be used to establish anticipated thermal performance levels for single layer or multilayer constructions or assemblies.

NOTE 5 Different specimen-mounting conditions, which are determined by the number of layers of material in the test specimen, are provided in this method. Each condition emphasizes a different thermal characteristic of the sample and represents the way in which the material is used in the end-use application.

NOTE 6 The spaced configuration, with a spacer placed between the back surface of the specimen and the sensor, reflects applications in which there is an air space or gap between the specimen and the protected surface. This spaced configuration also eliminates the cooling effect, which occurs due to specimen contact with the sensor and allows the specimen to heat to a temperature during the test the same as that which might occur in an actual fire exposure. This mounting condition gives a measure of the insulation performance and thermal capacity of the specimen and air gap as a combination.

NOTE 7 The contact configuration, with the sensor in contact with the specimen, gives a measure of the insulation performance and thermal capacity of the specimen and reflects applications in which the textile is in contact with the protected surface.

This document is a preview generated by EVS

Clothing for protection against heat and flame — Determination of heat transmission on exposure to both flame and radiant heat

1 Scope

This document specifies a test method for measuring the heat transferred through horizontally mounted flame-resistant textile materials when exposed to a combination of convective and radiant heat. The exposure conditions are adjusted to be approximately a 50/50 mixture of pure convective heat and pure radiant heat. The total exposure heat flux is 84 kW/m².

This test method is applicable to any type of sheet material used either as a single layer or in a multilayer construction when all structures or sub-assemblies are made of flame-resistant materials. It does not apply to materials that are not flame resistant.

This test method does not apply to the evaluation of materials exposed to any other type of thermal energy sources, such as radiant heat only or flame contact only. ISO 6942 is applicable when evaluating materials for exposure to radiant heat only. ISO 9151 is applicable when evaluating materials due to flame contact only.

NOTE Some, but not all, textiles materials can ignite and continue to burn after exposure to the convective and radiant heat produced by this test method.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <http://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1

break-open

formation of a hole in the material during thermal exposure

3.2

burn injury

burn damage that occurs at various levels of depth within human tissue

Note 1 to entry: Burn injury in human tissue occurs when the tissue is heated and kept at an elevated temperature for a critical period of time. The amount of burn injury (first, second or third degree) depends upon both the level of the elevated temperature and the duration. The material performance in this document is related to a second-degree burn injury and is determined by the amount of thermal energy transferred through the specimen that is sufficient to cause the onset of a second-degree burn. The onset of a second-degree burn injury involves damage to the epidermis and part of the dermis.