
**Biological evaluation of medical
devices —**

Part 9:
**Framework for identification
and quantification of potential
degradation products**

Évaluation biologique des dispositifs médicaux —

*Partie 9: Cadre pour l'identification et la quantification des produits
potentiels de dégradation*



This document is a preview generated by EMS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principles for design of degradation studies	2
4.1 General.....	2
4.2 Preliminary considerations.....	3
4.3 Study design.....	3
4.4 Characterization of degradation products from medical devices.....	4
5 Study report	4
Annex A (normative) Consideration of the need for degradation studies	6
Annex B (informative) Degradation study considerations	8
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 194, *Biological and clinical evaluation of medical devices*.

This third edition cancels and replaces the second edition (ISO 10993-9:2009), which has been technically revised.

The main changes compared to the previous edition are as follows:

- a) biodegradation changed to degradation;
- b) information on test methods amended to consider nanomaterials and relevant material specific standards.

A list of all parts in the ISO 10993 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document is intended to present the general principles on which the specific material investigations to identify and quantify degradation products described in ISO 10993-13 (polymers), ISO 10993-14 (ceramics) and ISO 10993-15 (metals and alloys) are based.

Information obtained from these studies is intended to be used in the biological evaluations described in the remaining parts of ISO 10993.

The materials used to construct medical devices can form degradation products when exposed to the biological environment, and in the body these products might behave differently to the bulk material.

Mechanical wear, which is not in scope of this document, causes mostly particulate debris, whereas non-mechanical degradation can lead to the release of free ions or to different kinds of reaction products in the form of organic or inorganic compounds.

The degradation products can be either reactive or stable and without biochemical reaction with their environment. Accumulations of substantial quantities of stable degradation products can, however, have physical effects on the surrounding tissues. Degradation products might remain at the location of their generation or might be transported within the biological environment by various mechanisms.

The level of biological tolerability of degradation products depends on their nature and concentration, and should be primarily assessed through clinical experience and focused studies. For theoretically possible, new and/or unknown degradation products, relevant testing is necessary. For well-described and clinically accepted degradation products, further investigation might not be necessary.

Note that the safety and efficacy of a medical device can be compromised as a result of any unintended or premature degradation, which should be considered in the risk management of the device.

This document can be applied to the degradation of materials used in any kind of product that falls within the definition of "medical device" in ISO 10993-1, even if such products are subject to different regulations from those applying to medical devices, e.g. the scaffold in a tissue engineered medical product, or a carrier matrix to deliver drugs or biologics.

Biological evaluation of medical devices —

Part 9:

Framework for identification and quantification of potential degradation products

1 Scope

This document provides general principles for the systematic evaluation of the potential and observed degradation of medical devices through the design and performance of *in vitro* degradation studies. Information obtained from these studies can be used in the biological evaluation described in the ISO 10993 series.

This document is applicable to both materials designed to degrade in the body as well as materials that are not intended to degrade.

This document is not applicable to:

- a) the evaluation of degradation which occurs by purely mechanical processes; methodologies for the production of this type of degradation product are described in specific product standards, where available;

NOTE Purely mechanical degradation causes mostly particulate matter. Although this is excluded from the scope of this document, such degradation products can evoke a biological response and can undergo biological evaluation as described in other parts of ISO 10993.

- b) leachable components which are not degradation products;
- c) medical devices or components that do not contact the patient's body directly or indirectly.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10993-1, *Biological evaluation of medical devices — Part 1: Evaluation and testing within a risk management process*

ISO 10993-2, *Biological evaluation of medical devices — Part 2: Animal welfare requirements*

ISO 10993-13, *Biological evaluation of medical devices — Part 13: Identification and quantification of degradation products from polymeric medical devices*

ISO 10993-14, *Biological evaluation of medical devices — Part 14: Identification and quantification of degradation products from ceramics*

ISO 10993-15, *Biological evaluation of medical devices — Part 15: Identification and quantification of degradation products from metals and alloys*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 10993-1 and the following apply.