

METALLMATERJALID. DEFORMEERITAVUSGRAAFIKU  
MÄÄRAMINE LEHT- JA RIBAMATERJALILE. OSA 1:  
DEFORMEERITAVUSDIAGRAMMI MÕÕTMINE JA  
RAKENDAMINE TÖÖKOJAS

Metallic materials - Determination of forming-limit  
curves for sheet and strip - Part 1: Measurement and  
application of forming-limit diagrams in the press shop  
(ISO 12004-1:2020)

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 12004-1:2020 sisaldab Euroopa standardi EN ISO 12004-1:2020 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 12004-1:2020 consists of the English text of the European standard EN ISO 12004-1:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 04.11.2020.	Date of Availability of the European standard is 04.11.2020.
Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 77.040.10

**Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele**

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autoriõiguse kaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

**The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation**

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about standards copyright protection, please contact the Estonian Centre for Standardisation and Accreditation: Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

EUROPEAN STANDARD

EN ISO 12004-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2020

ICS 77.040.10

Supersedes EN ISO 12004-1:2008

English Version

**Metallic materials - Determination of forming-limit curves  
for sheet and strip - Part 1: Measurement and application  
of forming-limit diagrams in the press shop (ISO 12004-  
1:2020)**

Matériaux métalliques - Détermination des courbes  
limites de formage pour les tôles et bandes - Partie 1:  
Mesurage et application des diagrammes limites de  
formage dans les ateliers d'emboutissage (ISO 12004-  
1:2020)

Metallische Werkstoffe - Bestimmung der  
Grenzformänderungskurven für Bleche und Bänder -  
Teil 1: Messung und Anwendung von  
Grenzformänderungsdiagrammen in Stanzereien (ISO  
12004-1:2020)

This European Standard was approved by CEN on 15 October 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

## European foreword

This document (EN ISO 12004-1:2020) has been prepared by Technical Committee ISO/TC 164 "Mechanical testing of metals" in collaboration with Technical Committee CEN/TC 459/SC 1 "Test methods for steel (other than chemical analysis)" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2021, and conflicting national standards shall be withdrawn at the latest by May 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 12004-1:2008.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Endorsement notice

The text of ISO 12004-1:2020 has been approved by CEN as EN ISO 12004-1:2020 without any modification.

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Symbols and abbreviated terms</b> .....	<b>1</b>
<b>5 Principle</b> .....	<b>1</b>
<b>6 Test conditions</b> .....	<b>2</b>
<b>7 Procedure</b> .....	<b>3</b>
<b>8 Interpretation of results</b> .....	<b>3</b>
<b>9 Test report</b> .....	<b>4</b>
<b>Annex A (informative) Modification to forming-limit curves</b> .....	<b>5</b>
<b>Annex B (informative) Examples of grid patterns currently in use</b> .....	<b>6</b>
<b>Bibliography</b> .....	<b>8</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 2, *Ductility testing*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 459/SC 1, *Test methods for steel (other than chemical analysis)*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 12004-1:2008), which has been technically revised.

The main changes compared to the previous edition are as follows:

- 1) The title was changed to have three elements.
- 2) [Clauses 2](#) and [3](#) were added from the previous edition, and the subsequent sections were renumbered.
- 3) The description of when to use this document (ISO 12004-1) or ISO 12004-2 was revised in the Introduction.
- 4) Throughout the document the use of engineering strain was clarified.
- 5) [Subclause 6.2](#) was extended to include what was the subsequent Clause in the previous version.
- 6) The former note was moved to part of [Clause 7](#), since it gives permission to use another method.
- 7) The text in [Annex A](#) and the figure captions in [Annex B](#) were clarified.

A list of all parts in the ISO 12004 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

A forming-limit diagram (FLD) is a diagram containing measured major/minor strain points on a formed part.

An FLD can distinguish between safe and necked, or failed, points. The transition from safe to failed points is defined by the forming-limit curve (FLC).

To determine the forming limit of materials, two different methods are possible.

1) Strain analysis of failed press shop components to determine component and process dependent FLCs

In the press shop, strain paths to reach these points are generally not known. Such an FLC depends on the material, the component, and the chosen forming conditions. This method is described in this document and is not intended to determine one unique FLC for each material.

2) Determination of FLCs under well-defined laboratory conditions

For evaluating formability, one unique FLC for each material in several strain states can be measured. The determination of FLC must be specific and uses multiple linear strain paths. The ISO 12004-2 is intended for this type of material characterization.

# Metallic materials — Determination of forming-limit curves for sheet and strip —

## Part 1:

## Measurement and application of forming-limit diagrams in the press shop

### 1 Scope

This document specifies a procedure for developing forming-limit diagrams and forming-limit curves for metal sheets and strips of thicknesses from 0,3 mm to 4 mm.

### 2 Normative references

There are no normative references in this document.

### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 4 Symbols and abbreviated terms

The symbols and abbreviated terms used in forming-limit diagrams are specified in [Table 1](#), and examples of grid patterns used are given in [Annex B](#).

**Table 1 — Symbols and abbreviated terms**

Symbol	Definition	Unit
$l_0$	Original gauge length of grid pattern	mm
$l_1$	Final length in major strain direction	mm
$l_2$	Final length at 90° to major strain direction	mm
$e$	Engineering strain	%
$e_1$	Major engineering strain	%
$e_2$	Minor engineering strain (90° to major)	%
FLD	Forming-limit diagram	—
FLC	Forming-limit curve	—

### 5 Principle

A pattern of precise gauge lengths of appropriate size is applied to the flat surface of a metal sheet test piece, then the test piece is formed until fracture, and the percent change in the gauge length in the major direction and in the minor strain direction at 90° to this is measured in order to determine the