

Plastics - Determination of dynamic mechanical properties - Part 3: Flexural vibration - Resonance-curve method (ISO 6721-3:2021)

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 6721-3:2021 sisaldab Euroopa standardi EN ISO 6721-3:2021 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 6721-3:2021 consists of the English text of the European standard EN ISO 6721-3:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 03.03.2021.	Date of Availability of the European standard is 03.03.2021.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 83.080.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN ISO 6721-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2021

ICS 83.080.01

Supersedes EN ISO 6721-3:1996

English Version

Plastics - Determination of dynamic mechanical properties
- Part 3: Flexural vibration - Resonance-curve method (ISO
6721-3:2021)

Plastiques - Détermination des propriétés mécaniques
dynamiques - Partie 3: Vibration en flexion - Méthode
en résonance (ISO 6721-3:2021)

Kunststoffe - Bestimmung dynamisch-mechanischer
Eigenschaften - Teil 3: Biegeschwingung -
Resonanzkurven-Verfahren (ISO 6721-3:2021)

This European Standard was approved by CEN on 14 February 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 6721-3:2021) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2021, and conflicting national standards shall be withdrawn at the latest by September 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 6721-3:1996.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 6721-3:2021 has been approved by CEN as EN ISO 6721-3:2021 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative reference	1
3 Terms and definitions	1
4 Principle	1
5 Test apparatus	2
5.1 General	2
5.2 Clamps or suspension fibres	2
5.3 Exciter and detector	2
5.4 Temperature-controlled enclosure	3
5.5 Gas supply	3
5.6 Temperature-measurement device	3
5.7 Devices for measuring test specimen dimensions	4
6 Test specimens	4
6.1 General	4
6.2 Shape and dimensions	5
6.3 Preparation	5
7 Number of test specimens	5
8 Conditioning	5
9 Procedure	5
9.1 Test atmosphere	5
9.2 Measurement of specimen cross-section	5
9.3 Measurement of specimen density	5
9.4 Mounting the test specimens and adjustment of the transducers	6
9.4.1 Method A	6
9.4.2 Method B	6
9.4.3 Adjustment of the transducers	6
9.5 Varying the temperature	6
9.6 Varying the frequency	6
9.7 Recording the resonance curve	6
10 Expression of results	7
10.1 Symbols	7
10.2 Calculation of flexural storage modulus, E'_f	7
10.3 Calculation of flexural loss factor, $\tan \delta_f$	8
10.4 Calculation of flexural loss modulus, E''_f	8
10.5 Plotting the complex modulus as a function of temperature	8
11 Precision	8
11.1 Storage modulus	8
11.2 Loss factor	8
11.3 Precision of the methods	9
12 Test report	9
Annex A (informative) Interlaboratory testing	10
Bibliography	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 6721-3:1994), which has been technically revised. It also incorporates the Technical Corrigendum ISO 6721-3:1994/Cor 1:1995.

The main changes compared to the previous edition are as follows:

- the document has been revised editorially;
- the normative references have been updated;
- the NOTE in [Clause 3](#) has been moved to [Clause 4](#);
- the method of specimen density measurement has been defined.

A list of all parts in the ISO 6721 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastics — Determination of dynamic mechanical properties —

Part 3: Flexural vibration — Resonance-curve method

1 Scope

This document specifies a bending-vibration method based upon resonance curves for determining the flexural complex modulus E_f^* of homogeneous plastics and the damping properties of laminated plastics intended for acoustic insulation, for example systems consisting of a metal sheet coated with a damping plastic layer, or sandwich systems consisting of two sheet-metal layers with an intermediate plastic layer. For many purposes, it is useful to determine these properties as a function of temperature and frequency.

2 Normative reference

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method*

ISO 1183-3, *Plastics — Methods for determining the density of non-cellular plastics — Part 3: Gas pycnometer method*

ISO 6721-1, *Plastics — Determination of dynamic mechanical properties — Part 1: General principles*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6721-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

A specimen is submitted to forced bending vibrations in the frequency range between about 10 Hz and 1 000 Hz. The resonance curve (see ISO 6721-1) is determined and, from the curve obtained, the flexural storage modulus E'_f is calculated in the range above 0,5 MPa and the loss factor given by $\tan \delta = E''_f/E'_f$ is calculated in the range between about 10^{-2} and 10^{-1} (see NOTE). The test frequency can be varied by making measurements at more than one vibrational order. The measurement range for the flexural loss modulus E''_f is determined by that of the loss factor and by the value of the storage modulus.