This document is a preview generated by EVS

Paints and varnishes - Evaluation of properties of coating systems related to the spray application process - Part 2: Colour stability, process hiding power, re-dissolving, overspray absorption, wetting, surface texture and mottling (ISO 28199-2:2021)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

This document is a preview generated by EVS

See Eesti standard EVS-EN ISO 28199-2:2021 sisaldab Euroopa standardi EN ISO 28199-2:2021 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 28199-2:2021 consists of the English text of the European standard EN ISO 28199-2:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 30.06.2021.	Date of Availability of the European standard is 30.06.2021.
Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 87.040

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

NORME EUROPÉENNE

EUROPÄISCHE NORM

EN ISO 28199-2

June 2021

ICS 87.040

Supersedes EN ISO 28199-2:2009

English Version

Paints and varnishes - Evaluation of properties of coating systems related to the spray application process - Part 2: Colour stability, process hiding power, re-dissolving, overspray absorption, wetting, surface texture and mottling (ISO 28199-2:2021)

Peintures et vernis - Évaluation des propriétés des systèmes de revêtement liées au mode d'application par pulvérisation - Partie 2 : Stabilité des couleurs, pouvoir masquant du procédé, détrempe, absorption des pertes de peinture à la pulvérisation, mouillage, texture superficielle et marbrures (ISO 28199-2:2021)

Beschichtungsstoffe - Beurteilung der durch Spritzapplikation bedingten Eigenschaften von Beschichtungssystemen - Teil 2: Farbstabilität, Prozessdeckvermögen, Anlösen, Spritznebelaufnahme, Benetzung, Oberflächenstruktur und Wolkigkeit (ISO 28199 2:2021)

This European Standard was approved by CEN on 6 June 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2021 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN ISO 28199-2:2021 E

This document is a preview generated by EVS

European foreword

This document (EN ISO 28199-2:2021) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 “Paints and varnishes” the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2021, and conflicting national standards shall be withdrawn at the latest by December 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 28199-2:2009.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 28199-2:2021 has been approved by CEN as EN ISO 28199-2:2021 without any modification.

This document is a preview generated by EVS

Contents

Page

Foreword ... **iv**
Introduction ... **v**
1 Scope ... **1**
2 Normative references ... **1**
3 Terms and definitions ... **1**
4 Colour stability/colour evaluation ... **1**
4.1 General ... 1
4.2 Evaluation ... 1
5 Process hiding power ... **3**
5.1 General ... 3
5.2 Evaluation ... 3
6 Re-dissolving ... **4**
6.1 General ... 4
6.2 Evaluation ... 4
7 Overspray absorption ... **5**
7.1 General ... 5
7.2 Evaluation ... 5
8 Wetting ... **6**
8.1 General ... 6
8.2 Evaluation ... 6
9 Surface texture ... **7**
9.1 General ... 7
9.2 Evaluation ... 7
9.2.1 General evaluation ... 7
9.2.2 Evaluation of base coats ... 7
9.2.3 Evaluation of clear coats ... 8
10 Mottling ... **9**
10.1 General ... 9
10.2 Evaluation ... 9
10.2.1 Measurement techniques ... 9
10.2.2 Visual evaluation ... 10
11 Test report ... **10**
Bibliography ... **11**

This document is a preview generated by EVS

© ISO 2021 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 139, *Paints and varnishes,* in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 28199-2:2009), which has been technically revised.

The main changes compared to the previous edition are as follows:

— the assessment of mottling (see 10.2) has been divided into measuring techniques and visual evaluation;

— limit values have been introduced for long-wavelength and short-wavelength surface textures (see 9.2.1);

— the normative references have been updated;

— the document has been editorially revised.

A list of all parts in the ISO 28199 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This document is a preview generated by EVS

 © ISO 2021 – All rights reserved

Introduction

In many areas (e.g. car manufacture, industrial coatings, coatings for plastics) the coating materials used are adapted to the specific application equipment and technologies of the particular user. A coating material is, therefore, to be understood as a semi-manufactured product that only receives its final form in combination with the specific application conditions. The adaptation to the application conditions is therefore decisive for the quality of the coated product.

The test methods specified in the ISO 28199 series are based on studies by a Working Group of the European Council for Automotive R&D (EUCAR).

They may be used for evaluation of coating materials in research, development and production with regard to their suitability and safety for industrial processes, and error analysis. The properties of coating materials and coatings to be evaluated depend on the film thickness, so a coating system of increasing thickness is applied to a test panel under defined conditions.

The following characteristics are measured (see ISO 28199-1):

— film thickness in accordance with ISO 2808;

— surface texture;

— colour in accordance with ISO 18314-1;

— mottling;

— gloss in accordance with ISO 2813.

In combination with visual assessment, the following properties are determined:

— colour stability, process hiding power, re-dissolving, overspray absorption, wetting, surface texture and mottling (this document);

— tendency to sagging, formation of bubbles, pinholing and hiding power (see ISO 28199-3).

This document is a preview generated by EVS

© ISO 2021 – All rights reserved

Paints and varnishes — Evaluation of properties of coating systems related to the spray application process —

Part 2: Colour stability, process hiding power, re-dissolving, overspray absorption, wetting, surface texture and mottling

This document is a preview generated by EVS

1 Scope

This document specifies methods for the determination of colour stability/colour evaluation, process hiding power, re-dissolving, overspray absorption, wetting, surface texture and mottling of coating materials applied to a test panel under defined conditions, using spray application process.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 28199-1:2021, *Paints and varnishes — Evaluation of properties of coating systems related to the spray application process — Part 1: Vocabulary and preparation of test panels*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 28199-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

4 Colour stability/colour evaluation

4.1 General

Colour stability is determined by evaluation of the values measured for a wedge-shaped base coat and constant-thickness clear coat, obtained in accordance with ISO 28199-1:2021, 9.4.

4.2 Evaluation

Plot the colour space values determined for the wedge-shaped base coat and constant-thickness clear coat in accordance with ISO 28199-1:2021, 9.4, against the film thickness of the base coat, and evaluate the curve. Determine the lowest (t_{min}) and the highest (t_{max}) film thicknesses at which the curve is approximately parallel to the X-axis. With regard to parallelism, a tolerance range or a minimum gradient is agreed. Figures 1 and 2 show examples of lightness (L^*) plotted against film thickness. The Y-axis can also show the colour values a*, b^*, C^* and h.

© ISO 2021 – All rights reserved