
**Paper, board and corrugated
fibreboard — Description and
calibration of fixed platen
compression-testing equipment**

*Papier, carton et carton ondule — Description et étalonnage du
matériel pour essai de compression à plateau fixe*



This document is a preview generated by EUS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	1
6 Verification and calibration	2
6.1 General.....	2
6.2 Upper and lower platen conditions.....	2
6.3 Operation speed.....	2
6.4 Load cell measurement system.....	2
7 Calibration report	2
Bibliography	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

This third edition cancels and replaces the second edition (ISO 13820:2014), which has been technically revised:

The main changes are as follows:

- the title of this document has been changed;
- “fixed platen” has been added to the scope;
- former 4.2, 5.2 and Annex A have been removed;
- [Clause 6](#) has been restructured with additional sub-clauses added for clarity;
- the bibliography has been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document describes the fixed-platen compression tester used for carrying out compression tests on paper, board, and corrugated fibreboard. This equipment develops compressive forces at a constant rate of strain. This is the primary equipment used in modern test labs, preferred because of its reliability, its ability to test over the range of test levels likely to be found, and because the characteristics of existing instruments have been well defined and universally accepted.

Another instrument, known as the beam-deflection compression tester, develops compressive forces between one platen driven at constant speed and another platen resting on a deformable beam. With this type neither rate of stress nor rate of strain is constant. The two instrument types produce different results^{[1][2][3][7]}. The extent of the difference depends on the test being conducted and on the characteristics, particularly the elastic characteristics, of the material being tested. The beam-deflection tester has been inadequately defined in past International Standards for compression tests; among existing instruments there have been different loading rates, different beam stiffnesses, and therefore different rates of strain. It is no longer described in this document.

The testing equipment referred to in this document is used for tests described in ISO 3035^[1], ISO 3037^[2], ISO 7263^[3], ISO 12192^[4], ISO 13821^[5], and ISO 16945^[6], among others.

Paper, board and corrugated fibreboard — Description and calibration of fixed platen compression-testing equipment

1 Scope

This document specifies the essential characteristics and the principles of calibration of fixed platen compression testing equipment used in the testing of paper, board, and corrugated fibreboard.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

The characteristics and calibration of the compression testing machine are described.

5 Apparatus

5.1 Fixed-platen compression testing machine, operating on the constant rate of deformation (strain) principle and incorporating the following features.

5.2 An upper and a lower platen, each large enough to completely accommodate the test piece and sufficiently rigid to resist significant deformation by the compressive forces.

The platens shall be mounted so as to have not more than 0,05 mm relative movement in the horizontal plane and their surfaces shall be parallel to each other, within 0,05 mm per 100 mm of platen surface. The surface of the platens shall be flat to the extent that the lowest and highest points are within 0,05 mm of the average surface.

Some tests require the surface finish of the platen to be such as to prevent slippage of the test piece during the test. Emery cloth, grade 00 or its equivalent (type 240 in Europe, crocus cloth in Canada), secured to the surface of the platens with contact adhesive or with low-compressibility double-sided pressure-sensitive tape (see last paragraph in this subclause), or matte finish of the platen surfaces, or any equivalent means, can be used to achieve this, provided the requirements for parallelism are met.

The emery cloth shall be replaced as soon as any damage is observed. A knife or other sharp instrument shall not be used to remove the emery cloth or other material adhering to the platens.