

This document is a preview generated by EVS

Copper and copper alloys - Copper cathodes



EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 1978:2022 sisaldab Euroopa standardi EN 1978:2022 ingliskeelset teksti.	This Estonian standard EVS-EN 1978:2022 consists of the English text of the European standard EN 1978:2022.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 21.09.2022.	Date of Availability of the European standard is 21.09.2022.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.150.30

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Copper and copper alloys - Copper cathodes

Cuivre et alliages de cuivre - Cathodes en cuivre

Kupfer und Kupferlegierungen - Kupfer-Kathoden

This European Standard was approved by CEN on 15 August 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
Introduction.....	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions.....	5
4 Designations.....	6
4.1 Material.....	6
4.1.1 General.....	6
4.1.2 Symbol.....	6
4.1.3 Number.....	6
4.2 Product.....	6
5 Ordering information.....	7
6 Requirements.....	7
6.1 Composition.....	7
6.2 Electrical properties.....	7
6.3 Dimensions and tolerances.....	8
6.4 Surface condition.....	8
7 Sampling.....	10
8 Test methods.....	10
8.1 Analysis.....	10
8.1.1 Routine analysis.....	10
8.1.2 Analysis in cases of dispute.....	10
8.2 Electrical resistivity.....	11
8.2.1 Routine determination of electrical resistivity.....	11
8.2.2 Determination of electrical resistivity in cases of dispute.....	11
8.3 Retests.....	11
8.4 Rounding of results.....	11
9 Declaration of conformity and inspection documentation.....	11
9.1 Declaration of conformity.....	11
9.2 Inspection documentation.....	11
10 Marking.....	12
Annex A (normative) Methods for use in cases of dispute, for the sampling of cathodes and for the preparation of analysis samples.....	13
Annex B (informative) Information on electrical resistivity and conductivity relationships.....	16
Bibliography.....	17

European foreword

This document (EN 1978:2022) has been prepared by Technical Committee CEN/TC 133 “Copper and copper alloys”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2023, and conflicting national standards shall be withdrawn at the latest by March 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1978:1998.

In comparison with the previous edition, the following technical modifications have been made:

- a) The reference to EN 1655 has been replaced by EN ISO/IEC 17050-1 and EN ISO/IEC 17050-2.

This is one of a series of European Standards for products manufactured from refined copper grades. Other products are specified as follows:

- EN 1976, *Copper and copper alloys - Cast unwrought copper products*
- EN 1977, *Copper and copper alloys - Copper drawing stock (wire rod)*

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Introduction

This document was prepared to combine the various requirements and methods of test for copper cathodes, previously dealt with in a range of separate national standards.

Copper cathodes are intended for melting. Cu-CATH-1 (CR001A) is primarily intended for the production of high conductivity copper, such as for drawing stock. Cu-CATH-2 (CR002A) is intended for the production of other wrought products for electrical and general purposes.

This document is a preview generated by EVS

1 Scope

This document specifies the composition and property requirements for cathodes of two copper grades, designated Cu-CATH-1 (CR001A) and Cu-CATH-2 (CR002A).

Annex A (normative) describes methods for sampling cathodes for use in cases of dispute between the purchaser and the supplier. Annex B (informative) gives information on the relationships between electrical resistivity and conductivity of copper.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60468, *Method of measurement of resistivity of metallic materials*

EN 16117-2, *Copper and copper alloys - Determination of copper content - Part 2: Electrolytic determination of copper in materials with copper content higher than 99,80 %*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

cathode

flat, unwrought product made by electrolytic deposition

3.2

lot

quantity of copper cathodes weighing over 25 t and up to and including 200 t, consisting of one consignment, or part of one consignment, produced by one refinery

3.3

bundle

total amount of a certain number of cathodes, typically 20 to 60, stacked together and secured, generally by steel bands

3.4

sample of cathodes

number of cathodes randomly selected from the lot, and considered in total to be representative of the lot

3.5

cathode sample

portion of one of the sampled cathodes (see 3.4) obtained by systematic cutting of vertical strips