
**Plastics — Evaluation of the adhesion
interface performance in plastic-metal
assemblies —**

**Part 5:
Fracture energy**

*Plastiques — Évaluation des performances de l'interface d'adhérence
dans les assemblages plastique-métal —*

Partie 5: Énergie de rupture

This document is a preview generated by ELS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Test specimens	2
4.1 Shape and size.....	2
4.2 Procedure for test specimen preparation.....	3
5 Test procedure	5
5.1 Test machine.....	5
5.2 Loading rigs.....	5
5.3 Displacement measurement.....	7
5.4 Measurements of test specimen dimensions.....	7
5.5 Conditioning.....	8
5.6 Test procedure.....	8
6 Evaluation of the fracture energy	8
7 Failure pattern and test validation	9
8 Precision	11
9 Test report	11
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

A list of all parts in the ISO 19095 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

There is a growing demand for reliability of metal-plastic joints to make lightweight cars and aircraft, which leads to fuel savings and reduced carbon dioxide emissions. Dissimilar joints of plastics and metals is also an important technology for manufacturing high-performance, low-cost electronic components.

Against this background of industrial trends, new bonding technologies are being developed and test methods for assessing the joint performance of metal-plastic assemblies manufactured in various bonding processes need to be standardized.

ISO 19095-1 through ISO 19095-4 were developed for the metal-plastic assemblies to assess the joint strength, sealing properties and environmental durability.

This document provides a test method to evaluate metal-plastic interfacial fracture energy and to characterize the failure behaviour of joints. This test is therefore useful for qualifying a joint's ability to resist fracture in order to ensure joint integrity.

Plastics — Evaluation of the adhesion interface performance in plastic-metal assemblies —

Part 5: Fracture energy

SAFETY STATEMENT — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices. It is recognized that some of the materials permitted in this document might have a negative environmental impact. As technological advances lead to more acceptable alternatives for such materials, they will be eliminated to the greatest extent possible. At the end of the test, care should be taken to dispose of all waste in an appropriate manner.

1 Scope

This document specifies a method of testing the adhesion in plastic-metal joints produced by several techniques: adhesive bonding, direct joining of thermoplastics by injection or compression moulding, or other methods. More specifically this testing method provides a measure of the joint resistance to fracture in the region between plastic and metal adherends.

This method can only be used for comparing adhesives, surface treatments, bonding conditions and effects of environmental conditions. The results cannot be used for engineering design purposes.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 5893, *Rubber and plastics test equipment — Tensile, flexural and compression types (constant rate of traverse) — Specification*

ISO 10365, *Adhesives — Designation of main failure patterns*

ISO 17212, *Structural adhesives — Guidelines for the surface preparation of metals and plastics prior to adhesive bonding*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>